

Table 4. Pressure variation of the fundamental elastic constants in several forms.  $d\ln C/dP$  is in units of  $10^{-3} \text{ kbar}^{-1}$ .

	$dC/dP$	$d\ln C/dP$	$d\ln C/d\ln r$
$C_{11}$	4.54	1.74	- 9.9
$C_{44}$	1.03	1.26	- 7.1
$(C_{11}-C_{12})/2$	1.01	1.95	-11.1
$B_s$	3.19	1.66	- 9.5
$B_T$	3.20	1.68	- 9.6