

TABLE I

Summary of Activation Volumes for Creep in Indium

Specimens	T(°C)	P <sub>1</sub> (kbars)	P <sub>2</sub> (kbars)	Number of Slope Ratios	V <sub>c</sub> (cm <sup>3</sup> /mole)
1	67.2	0.41	2.90	30	10.8
2	95.0	0.83	3.59	25	14.2
3	100.5	0.83	3.59	29	11.4
4	101.3	0.83	3.59	15	11.9
5	101.3	0.83	3.59	24	11.8
6	98.6	0.83	3.59	28	12.6
7	111.0	0.83	3.59	27	11.4
8	105.5	2.14	4.00	15	11.5
9	97.5	4.21	5.17	32	12.2
10	111.3	3.18	5.16	40	12.5
11	115.8	4.14	5.52	18	11.6