

dependent by about 15 to 20% over the temperature range 300–400 °C. For zinc, even though ΔV is temperature dependent, $\Delta K^{10,11}$ is found to be temperature independent. Hence it seems that the correlation between ΔV_f and ΔK for zinc as given in the above functional forms is not valid. Both ΔK and ΔV are admittedly quantities that describe the interaction between the diffusing defect and its neighboring atoms. However, the exact form of the relation connecting these two quantities is still not well known. On the other hand, it does not rule out the possibility that a relation between ΔK and ΔV for a monovacancy mechanism could in principle make ΔK temperature dependent, in view of the presently measured temperature dependence of ΔV . The trend and magnitude of this temperature dependence would of course depend on the form of the functional relation between ΔK and ΔV .

3. Activation Volumes and Nachtrieb's "Law of Corresponding States"

Nachtrieb, based on the assumption that the diffusion coefficient is a function only of the melting temperature $T_m(p)$, derived the relation³²

$$\Delta V = \frac{\Delta H}{T_m^0} \frac{dT_m}{dp},$$

where $T_m(p)$ is the melting temperature of the metal at pressure p . $T_m(p)$ can be approximated by a linear equation of the form

$$T_m(p) = T_m^0 + \frac{dT_m}{dp} p.$$

T_m^0 is the melting point of the metal at zero pressure. For most metals, dT_m/dp is a constant, over the range 0–10 kbar. Taking $\Delta H = 22.5$ kcal/mole, $T_m^0 = 693$ °K, and $dT_m/dp = b = 4.2$ °C/kbar,⁴³ this relation gives $\Delta V = 5.7$ cm³/mole, whereas we presently measure $\Delta V \approx 4$ cm³/mole. Nachtrieb theorized that a plot of $\ln D$ vs $T_m(p)/T$ should be a straight line. This is equivalent to assuming that the diffusion coefficient is a function of the melting temperature $T_m(p)$ only. Therefore, according to Nachtrieb,

$$\left(\frac{\partial \ln D}{\partial (T_m/T)} \right)_T = \left(\frac{\partial \ln D}{\partial (T_m/T)} \right)_p = \left(\frac{\partial \ln D}{\partial (T_m/T)} \right)_{p=0}.$$

Thus,

$$\Delta V/Rb = \Delta H(p)/R(T_m^0 + bp) = \Delta H(0)/RT_m^0. \quad (21)$$

To obtain a straight line, Eq. (21) has to be valid. Equation (21) would indeed be valid if ΔV were temperature independent. However, in this investigation we obtain $(\partial \Delta V / \partial T)_p \neq 0$. Thus, the condition for Nachtrieb's law of corresponding states to hold is not fulfilled for zinc. It is there-

fore not surprising that when a trial plot of $\ln D$ vs T_m/T was attempted a series of straight-line segments of different slopes with discontinuous jumps resulted. In a later paper,³⁴ Nachtrieb mentions that Eq. (21) is only approximate and will be in error to the extent that the entropy of activation is strongly pressure dependent. This is equivalent to saying that it is in error to the extent that the activation volumes are temperature dependent.

F. Discussion of Experimental Precision

According to Eq. (1), ΔV is experimentally determined by measuring the slope of an isotherm of $\ln D$ vs p . Since D has an exponential dependence on the temperature T , the quantity $(\partial \ln D / \partial p)_T$ can only be measured to a precision of approximately 1% by reproducing, under high pressure, diffusion-zone temperature, and hence the temperature of points constituting a particular isotherm, to within 0.2 °C. This corresponds to a relative error in D for points on the same isotherm of about 0.5%. Since the " $\kappa\gamma$ " term is only about 3–4% of ΔV , an uncertainty of 10% in its calculated value introduces an uncertainty of only a few tenths of a percent in ΔV . Similarly, the " RT " factor can easily be determined to within a fraction of a percent by simply knowing the absolute temperature T to about a degree. Additional random errors encountered in lathe sectioning, weighing, and counting of the radiotracer activity contribute a total uncertainty to D of about another 0.5%. A random error of about 0.5% in the measurement of pressure due to hysteresis effects in the manganin resistance coil of the pressure cell, when added to the aforementioned errors, gives a cumulative uncertainty in ΔV of about 1.5%. This is in agreement with the uncertainty of 2% obtained from the least-squares estimate of the slopes of the isotherms.

Previous measurements of Norton and Tomizuka,⁴⁴ of activation volumes in zinc at 410 °C, give $\Delta V_a = 4.7 \pm 0.7$ cm³/mole and $\Delta V_v = 4.3 \pm 0.2$ cm³/mole. These values are in good agreement with the results of the present experiment.

VI. SUMMARY

The results of the present experiment can be summarized as follows: (i) The activation volumes are temperature dependent and are of the form $\Delta V = AT$. Hence, the thermal coefficient of expansion of an activated vacancy in zinc is given by $\alpha_v = 1/T$, and is approximately equal to $15\alpha_0$. (ii) The activation entropy is pressure dependent, and to within the experimental uncertainty, one of the Maxwell's thermodynamic equations; namely,

$$\left(\frac{\partial \Delta S}{\partial p}\right)_T = - \left(\frac{\partial \Delta V}{\partial T}\right)_p,$$

is well obeyed for a diffusing defect. (iii) The activation enthalpy ΔH , to within the experimental uncertainty, is found to be pressure independent, i. e., $(\partial \Delta H / \partial p)_T \approx 0$.

The results that are found in this investigation and for those in cadmium,³⁰ are significantly different from those in previous experiments. Obviously, much more refined measurements have

to be made for other metals to establish the generality of the above results.

ACKNOWLEDGMENTS

The authors are grateful to Professor H. B. Huntington for many stimulating discussions and suggestions concerning this work. Many hours of helpful discussions with Dr. B. J. Buescher and Dr. R. N. Jeffery are deeply appreciated. Also acknowledged are the timely and critical comments of Professor David Lazarus.

*Work supported by the U. S. Atomic Energy Commission.

†This paper is based on a thesis submitted to the Physics Department at Rensselaer Polytechnic Institute by L. C. C. in partial fulfillment of the requirements for the Ph. D. degree.

¹N. L. Peterson, in *Solid State Physics*, edited by F. Seitz, D. Turnbull, and H. Ehrenreich (Academic, New York, 1969), Vol. 22, p. 415.

²D. Lazarus, in *Solid State Physics*, edited by F. Seitz and D. Turnbull (Academic, New York, 1960), Vol. 10, p. 71.

³R. Feder and A. S. Nowick, *Phys. Rev.* **109**, 1959 (1958).

⁴R. O. Simmons and R. W. Balluffi, *Phys. Rev.* **117**, 52 (1960).

⁵R. W. Balluffi, K. H. Lie, D. N. Seidman, and R. W. Siegel, in *Vacancies and Interstitials in Metals*, edited by A. Seeger, D. Schumacher, W. Schilling, and J. Diehl (Elsevier, New York, 1970), p. 125.

⁶J. S. Koehler, in Ref. 5, p. 169.

⁷C. P. Flynn, J. Bass, and D. Lazarus, in *Lattice Defects in Quenched Metals*, edited by R. M. J. Cotterill, M. Doyama, J. J. Jackson, and M. Meshii (Academic, New York, 1965), p. 639.

⁸H. M. Gilder and L. C. Chhabildas, *Phys. Rev. Letters* **26**, 1027 (1971).

⁹G. A. Shirn, E. S. Wajda, and H. B. Huntington, *Acta Met.* **1**, 513 (1953).

¹⁰N. L. Peterson and S. J. Rothman, *Phys. Rev.* **163**, 645 (1967).

¹¹A. P. Batra, *Phys. Rev.* **159**, 487 (1967).

¹²H. M. Gilder, B. J. Buescher, and L. Chhabildas, in *Proceedings of the Europhysics Conference on Atomic Transport in Solids and Liquids*, Marstrand, Sweden (unpublished).

¹³R. N. Jeffery and D. Lazarus, *J. Appl. Phys.* **41**, 3186 (1970).

¹⁴L. M. Levinson and F. R. N. Nabarro, *Acta Met.* **15**, 785 (1967).

¹⁵A. S. Nowick and G. J. Dienes, *Phys. Status Solidi* **24**, 461 (1967).

¹⁶L. A. Girifalco, *Scripta Met.* **1**, 5 (1967).

¹⁷R. H. Dickerson, R. C. Lowell, and C. T. Tomizuka, *Phys. Rev.* **137**, A613 (1965).

¹⁸F. R. Bonanno and C. T. Tomizuka, *Phys. Rev.* **137**, A1264 (1965).

¹⁹Y. Adda and J. Philibert, *La Diffusion dans les Solides* (Presses Universitaires de France, Paris, 1966), p. 837.

²⁰M. Beyeler and Y. Adda, *J. Phys. (Paris)* **29**, 345

(1968).

²¹R. O. Hull and C. J. Wernlund, in *Modern Electroplating* (Electrochemical Society, New York, 1942), p. 365.

²²We are thankful to Sylvania Electric, Towanda, Pa., for the supply of molybdenum foils and disks.

²³B. J. Buescher and H. M. Gilder, *J. Appl. Phys.* **43**, 211 (1972).

²⁴C. T. Tomizuka, in *Methods of Experimental Physics*, edited by K. Lark-Horovitz and V. A. Johnson (Academic, New York, 1959), Vol. 6A, p. 364.

²⁵G. A. Alers and J. R. Neighbors, *J. Phys. Chem. Solids* **7**, 58 (1958).

²⁶E. Grüneisen and E. Goens, *Z. Physik* **29**, 141 (1925).

²⁷H. M. Gilder and G. N. Wallmark, *Phys. Rev.* **182**, 771 (1969).

²⁸W. A. Harrison, *Phys. Rev.* **129**, 2512 (1963).

²⁹*Metals Handbook*, 8th ed., edited by T. Lyman (American Society for Metals, Metals Park, Ohio, 1961), p. 48.

³⁰B. J. Buescher and H. M. Gilder (private communication).

³¹N. H. Nachtrieb, J. A. Weil, E. Catalano, and A. W. Lawson, *J. Chem. Phys.* **20**, 1189 (1952).

³²N. H. Nachtrieb, H. A. Resing, and S. A. Rice, *J. Chem. Phys.* **31**, 135 (1959).

³³J. B. Hudson and R. E. Hoffman, *Trans. AIME* **221**, 761 (1961).

³⁴N. H. Nachtrieb and C. Coston, in *Physics of Solids at High Pressure*, edited by C. T. Tomizuka and R. M. Emrick (Academic, New York, 1965), p. 336.

³⁵R. M. Emrick, *Phys. Rev.* **122**, 1720 (1961).

³⁶B. J. Buescher and R. M. Emrick, *Phys. Rev. B* **1**, 3922 (1970).

³⁷R. W. Keyes, *J. Chem. Phys.* **29**, 467 (1958).

³⁸R. W. Keyes, in *Solids Under Pressure*, edited by W. Paul and D. M. Warschauer (McGraw-Hill, New York, 1963), p. 71.

³⁹A. W. Lawson, S. A. Rice, R. D. Corneliussen, and N. H. Nachtrieb, *J. Chem. Phys.* **32**, 447 (1960).

⁴⁰C. Zener, in *Imperfections in Nearly Perfect Crystals*, edited by W. Shockley (Wiley, New York, 1952), p. 289.

⁴¹L. W. Barr and J. N. Mundy, in *Diffusion in Body-Centered Cubic Metals* (American Society for Metals, Cleveland, Ohio, 1965), p. 171.

⁴²A. D. LeClaire, *Phil. Mag.* **14**, 1271 (1966).

⁴³Paul Seimers and Edward Hom, Senior Laboratory Project, Rensselaer Polytechnic Institute, Troy, N. Y., 1971 (unpublished).

⁴⁴M. A. Norton and C. T. Tomizuka, *Bull. Am. Phys. Soc.* **15**, 390 (1970).