ABSTRACT

The experimental fusion curves for lead and zinc have been obtained to 105,000 atmospheres. The fusion point in lead was detected by means of a sharp change in electrical resistance accompanied by a sharp rise in temperature, using the lead sample as its own heater. In zinc the fusion points were detected by heating the sample indirectly and observing latent heat on a temperature vs. time strip-chart recording. The melting point of lead rises smoothly from the normal value of 327.3° C to 730° C at 105,000 atmospheres. The melting point of zinc also rises smoothly from 419.5°C to 670° C at 105,000 atmospheres. No phase transitions were observed for lead or zinc.

Simon's equation was fitted to each of the afore mentioned fusion curves with the results that for lead a = 7,560 atmospheres and c = 3.38. For zinc a = 16,400 atmospheres and c = 4.19.

The maximum deviation between the experimental curve and the curve from Simon's equation is 5.7% for lead and 0.7% for zinc.

APPROVED

H. Tracy Hall, Chairman Advisory Committee

Harvey Fletcher, Jr., Member Advisory Committee