EARTH AND PLANETARY SCIENCE LETTERS 10 (1971) 316-324. NORTH-HOLLAND PUBLISHING COMPANY

PRESSURE COEFFICIENTS OF ELASTIC CONSTANTS FOR POROUS MATERIALS: CORRECTION FOR POROSITY AND DISCUSSION ON LITERATURE DATA

D.H. CHUNG

Department of Earth and Planetary Sciences, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139, USA

Received 16 October 1970 Revised version received 22 December 1970

An empirical scheme, by which one can correct porosity effects on pressure coefficients of elastic constants for porous materials, is presented. The underlying idea for the scheme is our recognition of experimental observations that the rate of change of ultrasonic transit-times with hydrostatic pressure in a porous medium is independent of small porosity at a pressure range of 2 to 10 kb, a range of pressure most commonly utilized in acoustic experiments. The scheme has been successfully tested with two polycrystalline forsterite samples of 1.65% and 6.09% porosities, two polycrystalline corundum samples with about 0.3% porosity each, and one polycrystalline rutile sample with 0.89% porosity, for all of which the corresponding single-crystal data are available. In the light of the present work, most of the elasticity data obtained on polycrystalline samples may require revision; for example, the literature value of dK_s/dp for hematite with 0.4% porosity is 4.53, which after the porosity correction becomes 4.91, while dK_s/dp reported as 4.80 for a forsterite sample with 6.09% porosity becomes 5.19 with the porosity correction. It is concluded that the scheme presented here may be useful as a working tool for experimentalists dealing with the elasticity of polycrystalline materials.

1. Introduction

One of the more important objectives of geophysics is to transform, uniquely, the elasticity of the Earth into parameters of composition, pressure, and temperature of earth materials. Accurate data on these equation-of-state parameters measured in the laboratory on carefully characterized minerals and rocks are therefore essential in the interpretation of geophysical field-data as well as in our understanding of solid state properties of these materials. Laboratory measurements of these data can be made either on single-crystals or on dense-formed polycrystalline samples. The frequent limitation of the unavailability of single-crystal specimens large enough for acoustic measurements to be made upon themhinders the laboratory determination of these data.

With advances in ceramic fabrication process (see, for example, Crandall et al. [1]), some polycrystalline aggregates can be fabricated into quasi-isotropic bodies with a density comparable to the single-crystal density*. Clearly, however, most polycrystalline

* Since the writer's success in 1961 in hot-pressing corundum samples with small porosities and the subsequent correlation for a correspondence between single-crystal and polycrystalline elastic properties (Chung [2] and see also Anderson [3, p. 912; 4, p. 491]) much progress has been made regarding the elasticity of polycrystalline oxides and silicates. O.L. Anderson and his associates at Lamont-Doherty Geological Observatory made use of this idea extensively (see, for example, ref. [19] for a summary). The following examples in chronological order of development may be listed: (a) periclase with about 0.1% porosity, see Chung [5, 33], Anderson [4, p. 51], and Anderson and Schreiber [6, 34]; (b) spinels with about 1% porosity, see Chung et al. [7]; (c) forsterite with 6.09%, see Schreiber and Anderson [8]; (d) zincite with about 1% porosity, see Chung and Buessem [9], and also Soga and Anderson [10]; (e) lime with 1.8% porosity, see Soga [11]; (f) hematite with 0.4% porosity, see Liebermann and Schreiber [12]; (g) rutile with 0.89% porosity, see Chung and Simmons [13]; (h) quartz with 0.15% porosity, see Chung and Simmons [13]; (i) olivine of various (Fe/Mg) ratios, see Chung [14]; (j) fayalite with about 2.5% porosity, see Fujisawa [15] and Chung [14]; (k) (Fe₂SiO₄) spinel, see Mizutani et al. [16].

MAY 24 1971

samples prepared by hot-pressing or sintering method contain residual pores along the interstices of adjacent mineral grains; the porosity may frequently be as high as 5 to 10%, although values of a few percent or less are more common. When acoustic measurements are made on porous polycrystalline samples, the values must be corrected before being used to predict the intrinsic behavior of material deep in the Earth, which undoubtedly is pore-free.

Effects of porosity upon pressure derivatives of the elastic moduli are complicated not only by the manner in which the porosity-sensitive moduli change with pressure, but also by the change of porosity with pressure. In an earlier discussion of this problem, Chung and Simmons [17, p. 5318] suggested that for porosity less than 1% (d ln M/dp) = (d ln M^O/dp) is a good approximation (where M is a modulus and the superscript $(^{O})$ refers to the value at zero-porosity. Based on Mackenzie's work [18], Anderson et al. [19, p. 507] found (by differentiating Mackenzie's expression for the bulk modulus) an expression for dK_S^{0}/dp in terms of dK_S/dp measured on a porous sample. Walsh [20] in his recent analysis on the same problem pointed out that Mackenzie [18] developed his theory using linear elasticity in which $K_{\rm S}^{\rm o}$ and $\mu^{\rm o}$ are independent of stress and that a simple differentiation of Mackenzie's expression as was done in [19] could not result in a correct expression for dK_S^{o}/dp . Walsh [20] then used Murnaghan's theory of finite strains to find expressions for dK_S^{o}/dp in terms of the second and third-order elastic constants of the solid material. Use of Walsh's expressions for porous materials requires these high-order elastic constants of solid under discussion; frequent unavailability of these constants limits further application.

In this paper, the writer suggests a practical method for correcting porosity effects on pressure coefficients of the elastic parameters of porous materials. The present scheme has been successfully tested with two independent sets of porous forsterite samples having different porosities. The scheme was also tested with porous corundum and rutile samples successfully. The scheme described here may be a useful tool for experimentalists working with polycrystalline materials.

2. Scheme

The quantity of interest in the acoustic experiments, in which pressure is a variable, is the first derivative of an isotropic elastic modulus M with respect to hydrostatic pressure evaluated at zeropressure; this will be denoted here after as $\{dM/dp\}_{p=0}$. This derivative is an isothermal one, although the velocity-of-sound measurements involve an adiabatic process. Thus, the acoustic data resulting from such experiments are *thermodynamically mixed* isothermal pressure derivatives of the adiabatic modulus. For a modulus M_j , where the subscript j refers to either compressional or shear mode, we have

$$M_j = 4\rho \, \ell^2 \, (f_j)^2 \tag{1}$$

where ρ and l are the density and length of the specimen at the initial condition, respectively, and f_j is the corrected pulse repetition frequency in the *j*th mode. Taking logarithms and differentiating both sides with respect to pressure,

$$\frac{\mathrm{d}\ln M_j}{\mathrm{d}p} = \frac{\mathrm{d}\ln\rho}{\mathrm{d}p} + 2\left(\frac{\mathrm{d}\ln\varrho}{\mathrm{d}p}\right) + \frac{\mathrm{d}\ln\left(f_j\right)^2}{\mathrm{d}p} \tag{2}$$

Since $(d \ln \ell/dp) = (d \ln V/dp)/3$ for the isotropic medium and $(d \ln \rho/dp) = -(d \ln V/dp) \equiv 1/K_T$, where V is the volume, and after evaluating the derivatives at zero-pressure, we have

$$\left\{\frac{\mathrm{d}M_{j}}{\mathrm{d}p}\right\}_{p=0} = \left\{\frac{M_{j}}{3K_{T}}\right\}_{p=0} + \left\{M_{j}R_{j}\right\}_{p=0}$$
(3)

where $R_j = d(f_{jp}/f_{j0})^2/dp$ and this is obtained by fitting $(f_{jp}/f_{j0})^2$ versus pressure data to a straight line by the method of least squares. K_T is the isothermal bulk modulus and it is related to the adiabatic bulk modulus K_S by $K_T = K_S/(1 + \alpha T\gamma_G)$, where α is the coefficient of volume expansion, γ_G is Grüneisen's ratio, and T is temperature in °K. Thus it is clear from eq. (3) that the measurements of isotropic compressional and shear velocities of sound at a reference temperature and ultrasonic pulse-repetition-frequencies corresponding to these velocities as a function of pressure (also at the reference temperature) yield the values of $\{dM_j/dp\}_{p=0}$.

The use of eq. (3) for porous materials involves a two-step correction:

(a) For a polycrystalline sample with a known porosity, V_p and V_s are measured in the usual way. The elastic properties as one measures on a polycrystalline sample, are the *apparent* properties of the sample; they may or may not be corresponding to the intrinsic elastic properties of the sample being studied. Certain hot-pressed samples often contain microcracks, for example, and effects of these microcracks on the elastic properties of the samples should receive the careful attention of the investigator. Helpful references to these effects are Brace [21], Walsh [22], and Nur and Simmons [23]. The most commonly practised method of finding the intrinsic elastic properties of such samples is to measure both P and S velocities as a function of hydrostatic pressure to about 7 to 10 kb, as is frequently done (see, for example [13; 16, p. 2743]); from these $V_i(p)$ data, velocities at zero-pressure are found by extrapolation of high-pressure results back to the zero-pressure point. These velocities found at the origin in this manner correspond to the zero-pressure values for that porous sample; from these data, isotropic elastic properties at zero-porosity can be evaluated. Weil [24, p. 217] and Walsh [22] discussed how elastic properties of non-porous polycrystalline materials can be evaluated from the elastic data obtained on a porous sample. The Weil-Hashin expressions for the shear and bulk moduli with constants k_1 and k_2 , which are a function only of Poisson's ratio σ_S , are recommended. Mackenzie's [18] expressions can be used as well. Thus, for $\sigma_{\rm S} = \sigma_{\rm S}^{\rm o}$, we obtain $\mu^{\rm o}$, $K_{\rm S}^{\rm o}$, $V_p^{\rm o}$, and $V_{\rm S}^{\rm o}$. (b) It was observed [17, 26] that the quantity R_i in

(b) It was observed [17, 26] that the quantity R_j in the second term of eq. (3) is independent to the first order of small porosity at a pressure range of 2 to 10 kb, a range most commonly utilized in acoustic experiments. The theoretical justification for this observation is difficult, if not impossible, without making assumptions as to size, shape, and orientations of pores in the polycrystalline aggregate. In addition, even for a pore-free aggregate, the task of determining the microscopic state of stress distribution is hopelessly difficult, due to numerous superimposed effects which originate from the properties of the constituting mineral grains and from the boundaries between them. For these reasons, no satisfactory general model for the elasticity of porous materials has yet been developed, in spite of numerous investigations (see for a review [24, p. 217; 22]). An earlier analysis [17, p. 5320], based on Walsh's work for the rate of change of pores with pressure, indicates that, for a polycrystalline corundum with a porosity $\theta = 0.3\%$, the quantity $(d\theta/dp)$ estimated at the origin is in the order of -3×10^{-6} per kb. This value is small, and it is well within the scatter of most experimental data; thus, suggesting the observation may be justified for small properties (say θ less than one or two percent).

Additional support for the observation made in the earlier paragraph follows from the work of Walsh [22] and Brace [21]. As shown by Walsh and Brace, the pressure p^* required to close a cavity having the aspect ratio a is

$$p^* = aY \tag{4}$$

where Y is Young's modulus of the solid material surrounding the cavity. The values of Young's modulus for oxides and silicates of interest to geophysics are at least 1000 kb or greater (see Birch [25]). If pores are spherical, as in many polycrystalline samples prepared by sintering or by hot-pressing, the aspect ratio α is one; this means then that the pressure required to close the pores is 1000 kb or higher, depending upon the stiffness of the materials. This is a very high pressure as compared to the range of pressure involved in acoustic experiments. It would appear then that an application of 2 to 10 kb pressure to a sample containing spherical pores is too small a pressure for pore closure to affect the quantity R_{j} .

Thus, with experimental quantity R_j determined on a porous sample, one should be able to find the pressure coefficients of compressional, shear, and bulk moduli of the non-porous material from eqs. (5) and (6).

$$\{\frac{dM_{j}^{o}}{dp}\}_{p=0} = \{\frac{M_{j}^{o}}{3K_{T}^{o}}\}$$

$$+ \{M_{j}^{o} \cdot \frac{d}{dp}(f_{jp}/f_{j0})^{2}\}_{p=0}$$
(5)

318

Sample property			Polycry	Single-crystal data**			
	Unit	Porous	Nonporous	Porous	Nonporous		
ρ	g/cm ³	3.021	3.217	3.164	3.217	3.222	3.224
V_p	km/sec	7.586	7.608	8.459	8.534	8.594	8.569
VS	km/sec	4.359	4.369	4.938	4.977	5.033	5.015
φ	$(km/sec)^2$	32.24	32.42	39.03	39.82	40.08	39.89
σs	none	0.254	0.240	0.241	0.240	0.242	0.240
L_{S}	kb	1739	1862	2264	2343	2379	2367
u	kb	574	614	772	<u>797</u>	816	810.8
K _S	kb	973.6	1043	1235	1281	1291	1286
$dL_{\rm S}/dp$	none	6.53	6.94	7.27	7.51	7.40	7.77
$d\mu/dp$	none	1.30	1.32	1.80	1.85	1.82	1.80
dK_S/dp	none	4.80	5.19	4.87	5.04	4.97	5.37
R_p	per kb	0.0	0341	0.00294			-
R _S	per kb	0.00182		0.00206			
Reference †	÷ A		A		В	С	D

Table 1 Isotropic elastic properties of forsterite.

* Data entered under "porous" are the original experimental values reported by authors cited, and values listed under "nonporous" are corrected for porosity in accordance with the scheme presented in this paper.

** VRH values based on single-crystal data reported by authors cited.

† (A) Schreiber and Anderson [8]. Based on the same data, Anderson et al. [19, p. 494] list the value of $(dK_S/dp) = 4.87$ while in another report by Soga and Anderson [10, p. 2987] it gives 5.08. To avoid the apparent confusion, we used the original data presented by Schreiber and Anderson [8, p. 763]. (B) Chung [26]. (C) Graham and Barsch [27]. (D) Kumazawa and Anderson [28].

$$\left\{\frac{dK_{\rm S}^{\rm o}}{dp}\right\}_{p=0} = \left\{\frac{dL_{\rm S}^{\rm o}}{dp}\right\}_{p=0} -\frac{4}{3}\left\{\frac{d_{\mu}^{\rm o}}{dp}\right\}_{p=0}$$
(6)

where L_S^{o} , μ^{o} ; and K_S^{o} are the porosity-corrected values from step (a) and the superscript (^o) refers to the zero-porosity.

3. Testing of the scheme: examples.

3.1. Forsterite

Table 1 presents the isotropic elastic parameters of two porous samples of forsterite before and after the porosity correction. The first set of these acoustic data is due to Schreiber and Anderson [8] and the second set to Chung [26]. The polycrystalline sample used by Schreiber and Anderson has 6.09% porosity, whereas Chung's sample contains 1.65% porosity [14]. To be noted here is that values of dK_S/dp for porous forsterite samples found in [8] and [26] are 4.80 and 4.87, respectively; with the porosity correction according to the present scheme, these values become 5.19 and 5.04. As they are clearly seen from table 1, the porosity-corrected values compare very well with 4.97 [27] and 5.37 [28], the corresponding values determined on gem-quality forsterite single-crystals. The elasticity data at ambient conditions reported originally by Schreiber and Anderson [8] differ from the single-crystal data reported by Graham and Barsch [27] and Kumazawa and Anderson [28] as well as from Chung's [26] polycrystalline data. The probable reason here may be due to the presence of a secondary phase in their "forsterite" sample. The

Sample property	Unit		Polyc	Single-crystal data**				
		Porous	Nonporous	Porous	Nonporous	Potous		
p rest	g/cm ³	3.972	3.986	3.974	3.986	3.03)	3.986	
Vp	km/sec	10.845	10.865	10.845	10.889		10.847	
V _S	km/sec	6.373	<u>6.383</u>	6.377	6.398		6.402	
φ 0.005	(km/sec) ²	63.47	63.72	63.39	64.00		63.02	
σS	none	0.236	0.236	0.234	0.234		0.233	
LS	kb	4672	4705	4674	4726		4690	
μ 8.11	kb	1613	1624	1616	<u>1632</u>		1634	
KS	kb	2521	2540	2519	2551		2512	
dL_S/dp	none	6.33	6.36	6.51	6.57		6.58	
$d\mu/dp$	none	1.76	1.77	1.77	1.79		1.73	
dK_S/dp	none	3.98	<u>4.01</u>	4.16	4.19		4.27	
R _n	per kb		0.001222		0.001259			
R _S	per kb		0.000958		0.000960		-156	
Reference †		3	A	1224	В			1 manufat

	Table 2		
Isotropic elastic	properties	of	corundum.

* Data entered under "porous" are the original experimental values reported by authors cited, and values listed under "nonporous" are corrected for porosity in accordance with the scheme presented in this paper.

** VRH values based on single-crystal data reported by Wachtman et al. [36] and Gieske and Barsch [30].

† (A) Schreiber and Anderson [29]. (B) Chung and Simmons [17].

experience of this author indicates that the presence of secondary phases affects considerably the secondorder elastic constants, but effects of these secondary phases on the pressure derivatives (particularly the value of dK_S/dp) are relatively small [26]. The unusually low values of both P and S velocities and the elastic constants as observed by Schreiber and Anderson [8] on their "forsterite" sample are believed to be associated with the presence of "barium aluminum silicate", the presence of which was noted by these authors.

3.2. Corundum

Table 2 lists two independent sets of the isotropic elastic parameters of polycrystalline corundum samples before and after the porosity correction. The first set of these acoustic data is due to Schreiber and Anderson [20] on a Lucalox alumina sample with 0.35% porosity, and the second set is due to Chung and Simmons [17] on a hot-pressed alumina sample with 0.35% porosity (Chung [2]; Anderson [3, p. 912; 4, p. 491]). Two sets of the acoustic data are generally in good agreement. It is noted that, with the porosity correction in accordance with the present scheme, values of the pressure derivatives compare well. It is also noted that these porosity-corrected values of the pressure derivatives compare very well with the corresponding values found on single-crystal corundum [30].

3.3. Rutile

Chung and Simmons [13] reported acoustic data on two porous rutile samples, one with 25% porosity and the other with 0.89% porosity. The property measured under pressure on the sample with 25% porosity was considered anomalous*, and these data

* It was noted earlier that the measured elastic properties of sample 1 (with 25% porosity) were considered anomalous.

320

D.H. Chung, Pressure coefficients of elastic constants for porous materials

Isotropic elastic properties of rutile.						
Sample		Polycrystall	Single-crystal data**			
property	Unit	Porous	Nonporous			
ρ	g/cm ³	4.212	4.250	4.260		
Vp	km/sec	9.146	<u>9.193</u>	9.261		
V _S	km/sec	5.102	5.122	5.137		
φ	$(\text{km/sec})^2$	48.96	49.53	50.59		
σs	none	0.264	0.274	0.272		
L_{S}	kb	3524	3592	3654		
μ	kb	1096	1115	1124		
KS	kb	2062	2105	2155		
dL_S/dp	none	7.57	7.7	7.80		
$d\mu/dp$	none	0.91	0.9	0.78		
dK_S/dp	none	6.35	6.4	6.76		
R_p	per kb	0.00198	4			
R _S	per kb	0.00067	9	-		

	Та	ble 3	
Isotropic	elastic	properties	of rutile.

* Data from Chung and Simmons [13].

** VHR values based on single-crystal data reported by Manghani [31].

will not be used in the present discussion. Table 3 presents the acoustic data obtained on a rutile sample with 0.89% porosity. The porosity-correction has been made to these data, and they are compared in the table with the corresponding data of gem-quality rutile single-crystals [31]. The comparison between the porosity-corrected polycrystalline data and the single-crystal data is generally satisfactory.

4. Discussion and conclusion

Examples with forsterite, corundum, and rutile given above indicate that the scheme presented in this paper seems to correct porosity effects on the pressure derivatives of the elastic constants of porous materials.

One-fourth of the volume of this sample was pores; with application of pressure, the pressure medium (petroleum ether in this case) undoubtedly penetrates into the pores. The property measured in such a sample is then some property of a "solid-liquid" composite under the pressure. Examination of the original data (see [13], p. 136) reveals that the shear waves were more critically affected.

Validity of the proposed scheme is essentially established. The scheme could be a useful tool for experimentalists working with the elasticity of polycrystalline materials.

The elastic constants and their pressure derivatives of 10 compounds of interest to geophysical and geochemical theories have been tabulated by Anderson et al. [19]. Acoustic data on seven out of these ten compounds are based on porous polycrystalline samples they studied, in which the porisity ranges from 0.11% for periclase to 6.09% for forsterite. The writer applied the present scheme of correcting porosity effects to their acoustic data; the results are tabulated in table 4. Also entered in the table are the elasticity data by this writer for periclase, corundum, quartz, rutile, and forsterite. Effect of the porosity correction is generally small. Most severely affected quantities are $d\mu/dp$ and dK_S/dp for hematite (with 0.4% porosity) and forsterite (with 6.09%). The dK_S/dp value as reported originally by Liebermann and Schreiber [12] for hematite is 4.53, which after the porosity correction becomes 4.91, while dK_S/dp , reported originally as 4.80 by Schreiber and Anderson [8] for their forD.H. Chung, Pressure coefficients of elastic constants for porous materials

Material		Before correction							After correction				
Ref.*		Density I	Density Porosity		ensity Porosity		an and an and a second second		Carolina and				Famile
		ρ (g/cm ³)	θ (%)	μ (kb)	KS	$\frac{\mathrm{d}\mu}{\mathrm{d}p}$	$\frac{\mathrm{d}K_{\mathrm{S}}}{\mathrm{d}p}$	ρ_0 (g/cm ³)	μ ⁰ (kb)	KS ^o	$\frac{d\mu^{O}}{dp}$	$\frac{\mathrm{d}K_{\mathrm{S}}^{\mathrm{O}}}{\mathrm{d}p}$	
MgO	a. m	3.5797	0.11	1288	1624	2.62	4.58	3.583	1291	1627	2.74	4.43	
MgO	b	3.582	0.03	1293	1644	2.41	4.28	3.583	1293	1644	2.41	4.28	
CaO	c, m	3.285	0.30	761	1059	1.64	5.23	3.345	789	1099	1.69	5.42	
ZnO	d, m	5.624	0.90	442	1394	-0.69	4.78	5.675	450	1437	-0.70	4.88	
BeO	e, m	3.000	0.26	1618	2201	0.88	5.52	3.008	1626	2213	0.88	5.54	
œAl2	0 ₃ f, m	3.972	0.35	1613	2521	1.76	3.98	3.986	1624	2540	1.77	4.01	
œAl ₂	O ₃ g	3.974	0.30	1616	2519	1.77	4.16	3.986	1632	2551	1.79	4.19	
α-Fe ₂	03 h, m	5.2539	0.40	910	2066	0.73	4.53	5.274	9 17	2088	0.89	4.91	
œ-SiO	2	2.545	0.15		0.77	0.17	6.50			070	0.5		
Tio	1	2.645	0.15	446	311	0.47	6.53	2.649	447	378	0.5	6.5	
Mo S]	4.212	0.89	1096	2062	0.91	0.33	4.250	1115	2105	0.9	0.4	
Mg ₂ S	k. m	3.021	6.09	574	974	1.30	4.80	3.217	614	1043	1.32	5.19	
Mg ₂ S	iO ₄ 1	3.164	1.65	772	1235	1.80	4.87	3.217	797	1281	1.85	5.04	
Fe ₂ Si	0 ₄ 1	4.287	2.41	502	1144	0.64	5.49	4.393	536	1220	0.62	5.92	

 Table 4

 Comparison of the elastic parameters before and after the porosity correction.

* (a) Schreiber and Anderson [34].

(b) Chung and Simmons [33].

(c) Soga [11].

(d) Soga and Anderson [10].

(e) Soga [35].

(f) Schreiber and Anderson [29].

(g) Chung and Simmons [17].

(h) Liebermann and Schreiber [12].

(i) Chung and Simmons [13].(j) Chung and Simmons [13].

(k) Schreiber and Anderson [8].

(l) Chung [26].

(m) Anderson et al. [19, table 1].

sterite sample, becomes 5.19 with the porosity correction. Furthermore, as is evident from table 4, the $d\mu/dp$ value for hematite reported originally in [12] as 0.73 undergoes a 22% change with the porosity correction.

On the basis of their original experimental data obtained on ten model compounds, Anderson et al. [19, figs. 3 to 10] and Anderson and Liebermann [32] discussed patterns relating the elastic properties of oxides and silicates. Their extensive discussions were based on the *apparent* elastic properties of various samples, including the seven porous polycrystalline specimens. Any discussion of the general patterns relating the elastic properties requires the intrinsic properties of model solids characterizing the elasticity of those materials. In view of table 4, then, all those correlations and patterns observed previously [19, 32] for the elastic properties of model oxides and silicates may have to be revised.

The conclusion of this paper is then that a more realistic establishment of the general patterns relating the elastic properties requires the *intrinsic* properties of model solids characterizing the elasticity of those materials. In transforming the elasticity of the Earth into solid-state parameters of composition, pressure, and temperature, the properties needed are the intrinsic elastic properties of earth materials (not the apparent properties as one measures on a porous sample).

Acknowledgements

I wish to acknowledge W.F. Brace, J.B. Walsh, A. Nur, and S. Solomon for reading the paper and for their discussions. J.B. Walsh is also acknowledged for sending me a preprint copy of his paper before publication. This research was supported by the National Science Foundation Grant GA-11091.

Notation

Symbols	Units	Meaning
V_p	km/sec	Velocity of compressional waves
Vo	km/sec	Velocity of compressional waves
P		at zero-porosity
VS	km/sec	Velocity of shear waves
VS	km/sec	Velocity of shear waves at zero-
		porosity
V_i	km/sec	Velocity of <i>j</i> th mode
M_{i}	kb	Elastic modulus of <i>j</i> th mode
M_i^{o}	kb	Elastic modulus of <i>j</i> th mode at
,		zero-porosity
L_{S}	kb	Longitudinal modulus given by
2		$(\text{density} \times V_p^2)$
$L_{\rm S}^{\rm o}$	kb	Longitudinal modulus at zero-
~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~~		porosity
μ	kb	Shear modulus
$\mu^{o}$	kb	Shear modulus at zero-porosity
K _S	kb	Adiabatic bulk modulus
KS	kb	Adiabatic bulk modulus at zero-
		porosity
$K_T$	kb	Isothermal bulk modulus
$K_T^0$	kb	Isothermal bulk modulus at zero-
_		porosity
Y	kb	Young's modulus
$\sigma_{\rm S}$	None	Poisson's ratio
$\sigma_{\rm S}^{\rm O}$	None	Poisson's ratio at zero-porosity
$f_i$	Hz/sec	Pulse-repetition frequency (PRF)
,		of <i>j</i> th mode

$f_n$	Hz/sec	PRF of compressional mode
fs	Hz/sec	PRF of shear mode
P	None	Compressional mode
S	None	Shear mode
a	None	Aspect ratio
р	kb	Pressure
Т	°K	Temperature
α	per °K	Coefficient of volume expansion
θ	None	Volume fraction of pores.

# References

- W.B. Crandall, D.H. Chung, and T.J. Gray, Mechanical properties of fine-grained hot-pressed alumina, Chapter 22, in: Mechanical Properties of Engineering Ceramics, eds. W. Kriegel and H. Palmour (Interscience, New York 1961), 349-379.
- [2] D.H. Chung, Elastic and anelastic properties of finegrained polycrystalline alumina, Bull. Ceram. Res. 26 (1961) 1-87.
- [3] O.L. Anderson, A simplified method for calculating the Debye temperature from elastic constants, J. Phys. Chem. Solids 24 (1963) 909-917.
- [4] O.L. Anderson, Determination and some uses of isotropic elastic constants of polycrystalline aggregates, using single-crystal data, Chapter 2, in: Physical Acoustics, vol. 3B, ed. W.P. Mason (Academic Press, New York, 1965) 43-95.
- [5] D.H. Chung, Elastic moduli of single-crystal and polycrystalline MgO, Phil. Mag. 8, 89 (1963) 833-841.
- [6] O.L. Anderson and E. Schreiber, The pressure derivatives of the sound velocities of polycrystalline magnesia J. Geophys. Res. 70 (1965) 5241-5248.
- [7] D.H. Chung, P.O. Benson, and W.B. Crandall, Elastic properties of polycrystalline magnesium-aluminate spinels, Prog. Rept. No. 6, Contract DA-31-124-ARO (D-23), Army Research Office, Durham, N.C. (1963).
- [8] E. Schreiber and O.L. Anderson, Pressure derivatives of the sound velocities of forsterite, with 6% porosity, J. Geophys. Res. 72 (1967a) 762-764; and a correction (1967b) 3751.
- [9] D.H. Chung and W. R. Buessem, The VHR approximation and the elastic moduli of polycrystalline ZnO, TiO₂, and α-Al₂O₃, J. Appl. Phys. 39 (1968) 2777-2782.
- [10] N. Soga and O.L. Anderson, Anomalous behavior of the shear sound velocity under pressure for polycrystalline ZnO, J. Appl. Phys. 38 (1967) 2985-2988.
- [11] N. Soga, Elastic properties of CaO under pressure and temperature, J. Geophys. Res. 73 (1968) 5385-5390.
- [12] R.C. Liebermann and E. Schreiber, Elastic constants of polycrystalline hematite, J. Geophys. Res. 73 (1968) 6585-6590.

#### D.H. Chung, Pressure coefficients of elastic constants for porous materials

- [13] D.H. Chung and G. Simmons, Pressure derivatives of the elastic parameters of quartz and rutile, Earth Planet. Sci. Letters 6 (1969) 134-138.
- [14] D.H. Chung, Effects of (Fe/Mg) ratio on P and S wave velocities in olivine, J. Geophys. Res., in press. 75 (1970)7353
- [15] H. Fujisawa, Elastic Properties of polycrystalline olivine, Trans. AGU 51 (1970) 418 (abstract only).
- [16] H. Mizutani, Y. Hamano, Y. Ida, and S. Akimoto, Compressional-wave velocities in fayalite, Fe₂SiO₄ spinel, and coesite, J. Geophys. Res. 75 (1970) 2741-2747.
- [17] D.H. Chung and G. Simmons, The pressure and temperature derivatives of the elastic moduli of polycrystalline alumina, J. Appl. Phys. 39 (1968) 5316-5326.
- [18] J.K. Mackenzie, The elastic constants of a solid containing spherical holes, Proc. Phys. Soc. (London) 63B (1950) 2-11.
- [19] O.L. Anderson, E. Schreiber, R.C. Liebermann, and N. Soga, Some elastic constant data on minerals relevant to geophysics, Rec. Geophys. 6 (1968) 491-524.
- [20] J.B. Walsh, First pressure derivative of bulk modulus for porous materials, submitted to J. Appl. Phys.
- [21] W.F. Brace, Some new measurements of linear compressibility of rocks, J. Geophys. Res. 70 (1965) 391-398.
- [22] J.B. Walsh, The effect of cracks on the compressibility of rocks, J. Geophys. Res. 70 (1965) 381-390.
- [23] A. Nur and G. Simmons, The origin of small cracks in igneous rocks, Int. J. Rock Mech. Min. Sci. 7 (1970) 307-314.
- [24] N.A. Weil, Parametric effects governing the mechanics of ceramic materials, in: High Temperature Technology, ed.
   N.K. Hiester (Butterworth Publishers Inc., Washington, D.C., 1964), 189-233.
- [25] F. Birch, Compressibility; elastic constants, in: Handbook of Physical Constants, Geol. Soc. Am. Memoir 97, ed. S.P. Clark Jr., Section 7 (1966).

- [26] D.H. Chung, Elasticity and equations of state of olivine: Effects of the iron/magnesium ratio, to be published. JER
- [27] E.K. Graham, Jr., and G.R. Barsch, Elastic constants of single-crystal forsterite as a function of temperature and pressure, J. Geophys. Res. 74 (1969) 5949-5960.
- [28] M. Kumazawa and O.L. Anderson, Elastic moduli, pressure derivatives, and temperature derivatives of singlecrystal olivine and single-crystal forsterite, J. Geophys. Res. 74 (1969) 5961-5972.
- [29] E. Schreiber and O.L. Anderson, Pressure derivatives of sound velocities of polycrystalline alumina, J. Am. Ceram. Soc. 49 (1966) 184-190.
- [30] J.H. Gieske and G.R. Barsch, Pressure dependence of the elastic constants of single-crystalline aluminum oxide, Phys. Status Solidi 29 (1968) 121-131.
- [31] M.H. Manghani, Elastic constants of single-crystal rutile under pressure to 7.5 kb, J. Geophys. Res. 74 (1969) 4317-4328; correction in J. Geophys. Res. 75 (1970) 2151.
- [32] O.L. Anderson and R.C. Liebermann, Elastic constants of oxide compounds used to estimate the properties of the earth's interior, in: On the Application of Modern Physics to the Earth and Planetary Interiors, ed. S.K. Runcorn (Wiley, New York, 1969), pp. 425-448.
- [33] D.H. Chung and G. Simmons, Elastic properties of polycrystalline periclase, J. Geophys. Res. 74 (1969) 2133-2135.
- [34] E. Schreiber and O.L. Anderson, Revised data on polycrystalline MgO, J. Geophys. Res. 73 (1968) 2837-2838.
- [35] N. Soga, Elastic constants of BeO as a function of pressure and temperature, J. Am. Ceram. Soc. 52 (1969) 246-249.
- [36] J.B. Wachtman, Jr., W.E. Tefft, D.G. Lam, Jr., and R.P. Stinchfield, Elastic constants of synthetic single-crystal corundum at room temperature, J. Res. NBS (USA) 64 A (1960) 213-228.

(1) And A. Res. 72 (1986) 27 (2017) and 2007) and (1997) 221. (2017) And and W. R. Dimession (1997) Wile opproxim (2017) Antipartic moduli of ballow purpling 2010).

(a) how a cold the Anderson. Normation Polyagian of the condent condendation index processing polyadiana.

tra entening talini Cont la california adulto en el 11 (11) Sur estado de la california de la californi

ld^y Mone M Mage M Mage M

324