




Fig. 3. Results obtained from 2-wire resistance measurements on increasing and decreasing pressure for $\text{BaPb}_{0.5}\text{Bi}_{0.5}\text{O}_3$.

slope change on increasing and decreasing pressure supports the suggestion that it is related to a phase

change, as opposed to simple intergranular resistance effects in the polycrystalline sample.

Sleight *et al.*² discussed the possible schematic energy level diagram for BaPbO_3 . They postulated that the 6s band would split above $x = 0.35$ in the compounds $\text{BaPb}_{1-x}\text{Bi}_x\text{O}_3$ and thus cause their semiconducting properties. In the light of the above considerations it would seem that the application of sufficient pressure could cause the band gap to close.

The bismuth ions were earlier⁴ thought to have the unusual 4+ valency. Such a situation would probably have yielded a metallic BaBiO_3 . From the latest structural data⁵ available for BaBiO_3 , using X-ray and neutron diffraction techniques, the true valence state appears to be $\text{Ba}_2\text{Bi}^{3+}\text{Bi}^{5+}\text{O}_6$. This valence situation would appear to be better suited to the semiconducting properties of the compound.

Acknowledgements — The authors would like to thank Dr. A.W. Sleight for helpful discussions and samples which were used to check the present results. This work was carried out under Contract NSF-MRL 6478, and under the auspices of JSPS Grant 4R023 and NSF Grant 01P74-2195B.

RÉFÉRENCES

1. JAYARAMAN A., *Ann. Rev. Mat. Sci.* **2**, 121 (1972).
2. SLEIGHT A.W., GILLSON J.L. & BIERSTEDT P.E., *Solid State Commun.* **17**, 27 (1975).
3. MEYERS M.B., DACHILLE F. & ROY R., *Rev. Sci. Instrum.* **34**, 401 (1963).
4. DE HAIR J. TH. W. & BLASSE G., *Solid State Commun.* **12**, 727 (1973).
5. SLEIGHT A.W. (unpublished results — personal communication).