

approximated (in the model assumed) by

$$\lim_{\Delta E \rightarrow 0} (\Delta E)^{-1} \sum_{\substack{\text{states } j \\ \text{in} \\ \Delta E}} |c_{\ell, m}^t(j, \underline{k})|^2 \times \text{constant}$$

$$= \sum_{\substack{\text{Sheets } j \\ \text{of} \\ \text{Fermi} \\ \text{Surf.}}} \iint \frac{dS_j}{|\nabla_{\underline{k}} E_j(\underline{k})|} |c_{\ell, m}^t(j, \underline{k})|^2 \times \text{constant},$$

for a single polarization and direction of the emitted x-ray.

In this expression,

$$\ell = \begin{array}{ll} 1 & \text{for K-emission (metal or non-metal)} \\ 2 & \text{for L-emission (metal)} \\ 1 & \text{for M-emission (metal),} \end{array}$$

\underline{m} is determined by the x-ray polarization (assumed to be circular or parallel to the z axis), and the expansion coefficients $c_{\ell m}^t$ are those for the APW sphere t around the atom in which the transition occurs. For unpolarized x-rays averaged over all angles of emission, the expression becomes proportional to the "partial density of states,"

$$Z_{\ell}^t(E) = \sum_{\text{Sheets}} \iint \frac{dS_j}{|\nabla_{\underline{k}} E_j(\underline{k})|} \sum_{\underline{m}} |c_{\ell, m}^t(j, \underline{k})|^2,$$

which is just the expression for density of states except that

the contribution of each state is weighted by the ℓ -component of its charge in the sphere t of interest [4]. This information is readily available from a self-consistent APW calculation.

The experimental data are reproduced in Fig. 8 and 9. In Fig. 10 is shown the decomposition of the $\text{Ti-L}_{\text{II,III}}$ emission from TiC, based on the assumption that the two components have the same shape and are separated in energy by the atomic Ti-L_{II} , Ti-L_{III} splitting. The experimental spectra are compared to the computed spectra (arbitrary units for both, no broadening included in the computed curves) in Fig. 11-13 for TiC and in Fig. 14-16 for NbC. In all cases, the calculated Fermi energy has been made coincident with the experimentally determined Fermi energy. For TiC, the curves are also shown with a relative shift of 0.6 eV from this position (dashed curves in Fig. 11 and 13, dot-dash in Fig. 12) which gives even better agreement. The shift to the dashed curve for $\text{Nb-M}_{\text{IV,V}}$ is to correct for a calibration error in Holliday's data, which was reported by Ramqvist, et. al. [25]. The agreement in all curves is seen to be excellent, if allowance is made for the broadening in the experimental data, which is not included in the theoretical curves.