

THE INFLUENCE OF HYDROSTATIC AND SHOCK
PRESSURE ON THE BCC \rightarrow (HCP, FCC)
TRANSFORMATION IN Fe-Mn ALLOYS

by

Aristos Christou
Materials Science Division
Naval Weapons Laboratory
Dahlgren, Va. 22448

(Received September 24, 1971)

1. Introduction

The pressure-induced phase transformations in iron-rich Fe-Mn alloys have been studied by the shock technique⁽¹⁻³⁾ and by the hydrostatic pressure technique⁽⁴⁾. Christou and Brown⁽²⁾ have found that the addition of manganese to iron decreases the shock transition pressure from 133 kbar for pure iron to less than 70 kbar for Fe-14 wt% Mn. For alloys up to 7 wt%, the FCC phase is stabilized, while the ϵ (HCP) phase is stabilized for the Fe-14 wt% Mn alloy. Saturation magnetization studies have detected a reduction in magnetization due to the high pressure phase.

Biles and Marder⁽⁴⁾ have studied the hydrostatic pressure induced transformation in Fe-Mn and have showed that for Fe-4.9 wt% Mn, Fe-9.6 wt% Mn and Fe-13.9 wt% Mn, the effect of manganese is to promote the formation of the HCP phase. In addition, in the case of Fe-13.9 wt% Mn and Fe-17.7 wt% Mn alloys, none of the HCP transformed back to BCC as the pressure was released. It is of interest to compare the two pressure-induced transformations (shock and hydrostatic pressure) and to explain the difference in the high pressure crystal structure of the two transformations.

2. The Shock-Induced Transformation

It has been shown⁽²⁾ that the addition of manganese to iron has modified the temperature-pressure diagram by increasing the field of stability of the FCC and HCP phase. Therefore, the shock loading of a BCC-martensite structure with an appropriate solute content results in an $\alpha \rightarrow \gamma$ or $\alpha \rightarrow \epsilon$ transformation. Figures 1 and 2 show that the triple point has been lowered to about 90 kbar for Fe-7 wt% Mn and 70 kbar for Fe-14 wt% Mn, thereby stabilizing the FCC and HCP fields with respect to the BCC phase. The T_0 -P (equilibrium temperature-pressure) lines for the Fe-7 wt% Mn and Fe-14 wt% Mn alloys as a first approximation were drawn parallel to the phase lines for pure iron, and were also made to pass through the two experimentally known states (T_0 , P=0 and T_c , P_c). The temperature T_c is the temperature of the compressed solid at P_c , the transformation pressure, calculated using the equations of McQueen et al⁽⁵⁾. The calculation of the initial T_0 -P slope (P=0, $T=T_0$) for Fe-7 wt% Mn and Fe-14 wt% Mn is based on the Clausius-Clapyron equation. The initial PT slope for the $\alpha \rightarrow \gamma$ transformation has the following values:

$$\left(\frac{dT}{dP}\right)^{\alpha \rightarrow \gamma} = -10.5 \text{ } ^\circ\text{K/kbar}$$

The enthalpy change $\Delta H_{\alpha \rightarrow \gamma}$ and the entropy change $\Delta S_{\alpha \rightarrow \gamma}$ are functions of temperature and solute concentration. Therefore, the slope of the T_0 -P curve will deviate from the slope of the pure iron phase lines.

On the temperature-pressure diagrams of Figures 1 and 2 we may superimpose the Fe-Mn T_H -P states, where T_H is the temperature rise induced in Fe-7 wt% Mn and Fe-14 wt% Mn by the passage of a shock wave. To calculate T_H we must take into account the Rankine-Hugoniot equations,⁽⁶⁾

$$E_H - E_0 = 1/2 P_H (V_0 - V) \quad (1)$$

where E is the total energy of the Fe-Mn alloy per unit mass. The internal energy may be approximated by the equation,

$$E \approx u(V) + 3 NkT \quad (2)$$

In equation (2) $u(V)$ is the ground state energy of the solid, T is the temperature, V is the volume, k is Boltzman constant and N is the number of atoms per gram. It can be shown⁽⁶⁾ that:

$$u(V) = \phi(V) + \left(\frac{V_0}{V}\right)^\gamma \sum_i \frac{1}{2} h\nu_i \quad (3)$$

where $\phi(V)$ is the cohesive energy, $\gamma = 1.6$, and ν are the phonon frequencies.

Equations (1) and (2) may be combined in order to obtain the expression for T_H :