

## SHOCK INDUCED DENSITY CHANGES

## IN METASTABLE BCC PHASES

A. Christou\*

Laboratory for the Research on the Structure of Matter  
and School of Metallurgy and Materials Science  
University of Pennsylvania  
Philadelphia, Pa.

(Received August 3, 1971; Revised February 18, 1971)

## 1 INTRODUCTION

The effect of shock deformation on martensitic transformations in metastable BCC systems was studied in order to determine whether the high pressure phase may be retained after relief. The system chosen for this investigation was BCC Fe-Mn. For the Fe-Mn alloys (0.38, 4.10, 7.37, 14 wt. pct. Mn, .007 wt. pct. C), initial studies<sup>(1,2)</sup> indicate that at pressures up to 300 kbar, the stability of the denser high temperature FCC phase increases, with a subsequent decrease in the amount of BCC martensite. Consequently, shock loading Fe-Mn alloys which have been subzero quenched to form a metastable martensitic BCC ( $\alpha'$ ) should result in a pressure induced  $\alpha'\gamma$  or  $\epsilon$ (HCP) transformation, with  $\gamma$  or  $\epsilon$  retained on relief.

For purposes of comparison, we have shock loaded another BCC alloy,  $\beta$ -brass (51.2 wt. pct. Zn) which is metastable with regard to deformation. Massalski and Barrett<sup>(3)</sup> have studied the effect of cold work on the martensitic transformation in  $\beta$ -brass with compositions from 39.7 to 51.5 wt. pct. zinc. They have concluded that  $\beta$ -brass alloys with 37.0 to 42.0 wt. pct. zinc are metastable with regard to cooling and deformation, while  $\beta$ -brass with above 42.0 pct. zinc is metastable with regard to deformation only.

The present work is an investigation of residual density changes that occur in shock loaded BCC alloys. The results are related to shock induced martensitic transformations.

## 2 EXPERIMENTAL DETAILS

The Fe-Mn specimens were subzero quenched from 900°C which is above the  $M_s$  temperature.  $\beta$ -brass was quenched into liquid nitrogen from above the Curie temperature. The shock defor-

---

\*Present address: Materials Science Division, NWL, Dahlgren, Va.

mation was accomplished in the usual manner.<sup>(4)</sup> The  $\beta$ -brass shocked samples were recovered from a liquid nitrogen bath. The specimens were shock loaded at pressures of 90, 150, and 300 kb. Shock induced density changes were measured using a displacement technique. Density changes of  $\pm 0.0002 \text{ g/cm}^3$  were detectable. The specimens were placed in a sealed case to ensure constancy of temperature. Crystal structure and shock induced phase changes were determined by x-ray diffraction of powdered Fe-Mn and  $\beta$ -brass using  $M_oK_{\alpha}$  radiation for Fe-Mn and copper for  $\beta$ -brass.

### 3. EXPERIMENTAL RESULTS AND DISCUSSION

Density measurements of the shock loaded Fe-Mn specimens clearly indicate that the high pressure phase has been retained in the alloys Fe-4Mn to Fe-14Mn, shock loaded at pressures above 90kb. The maximum density change occurred after shock deformation at 300 kb. The residual density changes are believed to be due to an  $\alpha' \rightarrow \gamma$  or  $\alpha' \rightarrow \epsilon$  martensitic transformation since, as shown in Table I, the density change was much less in the alloys that were initially furnace cooled prior to shock deformation. X-ray diffraction patterns of the shock deformed alloys were taken and for the Fe-14Mn alloy, three diffraction lines of BCC Fe-Mn, (110), (200), and (211), were observed. At 300 kb, six lines were clearly identified as the HCP,  $\epsilon$  phase. The x-ray diffraction results are summarized in Table I.

TABLE I

Density and X-ray Diffraction Data of Shock-Deformed Fe-Mn Alloys

Alloy (quenched initially)		Density Ratio†		Principle Phase
		Quenched	Furnace Cooled	
Fe-.38 Mn	90 kb	1.0002	1.0001	BCC
	150 kb	1.0002	1.0002	BCC
	300 kb	1.0002	1.0002	BCC
Fe-4 Mn	90 kb	1.0023	1.0002	BCC
	150 kb	1.0097	1.0006	FCC
	300 kb	1.0146	1.0007	FCC
Fe-7 Mn	90 kb	1.0028	1.0003	BCC
	150 kb	1.0218	1.0006	FCC
	300 kb	1.0427	1.0007	FCC
Fe-14 Mn	300 kb	1.0449	1.0009	HCP

$$\dagger \text{ Density ratio} = \frac{\text{Shocked density}}{\text{Unshocked density}}$$