CHUN-DH 69-0614

JOURNAL OF GEOPHYSICAL RESEARCH

Vol. 74, No. 8, April 15, 1969

JAN

1970

Brief Report

Elastic Properties of Polycrystalline Periclase

D. H. CHUNG AND GENE SIMMONS

Department of Geology and Geophysics, Massachusetts Institute of Technology Cambridge, Massachusetts 02139

New data on the variation with pressure of the elastic parameters of a hot-pressed specimen of MgO are reported. Within the uncertainty of the measurements the elastic constants are independent of direction but the pressure derivatives are not.

The elastic parameters of periclase (stoichiometric MgO) are important for several reasons. Because flawless centimeter-sized single crystals, both natural and synthetic, are available, data of very high precision can be obtained with the usual ultrasonic techniques. Polycrystalline aggregates that have been hot-pressed to nearly theoretical density yield equally precise data. Such data can be used to model the behavior of ionic materials, to test the forms of equations of state, to test the validity of both the Voigt-Reuss-Hill approximation and the improved limits of the Hashin-Shtrikman bounds, and so on. Of equal importance in geophysics is the consideration that periclase is a rockforming mineral and may be present in the mantle as a separate phase.

The recent publication by Schreiber and Anderson [1968] of a new set of elastic data on polycrystalline MgO that differ considerably from their earlier data [Anderson and Schreiber, 1965] prompts us to publish additional data obtained on another hot-pressed specimen.

The elastic properties of a hot-pressed cube of polycrystalline periclase, cut from one of the eight specimens used in an earlier study of elastic constants at room temperature of this material [*Chung*, 1963], were measured as a function of hydrostatic pressure to about 10 kb with the McSkimin pulse-superposition method. The microstructural characteristics of this specimen were described in detail in *Chung* [1963]. The chemical purity was 99.7% MgO. The specimen density was 3.582 g/cm^s at 25°C. The

Copyright © 1969 by the American Geophysical Union.

experimental procedure followed in the present work was described previously [Chung and Simmons, 1968].

The primary data measured in our ultrasonic experiments were (1) P and S velocities in three mutually perpendicular directions of the specimen at 25°C, and (2) pulse-repetition frequencies corresponding to these velocities as a function of hydrostatic pressure to 10 kb. The frequencies were linear with pressure. The first pressure derivatives of *isotropic* elastic moduli were then found from

$$\left(\frac{dM_i}{dP}\right)_{P=0} = \left(\frac{M_i}{3K_T}\right)_{P=0} + \left[M_i \cdot \frac{d}{dP} \left(\frac{F_{iP}}{F_{i0}}\right)^2\right]_{P=0}$$
(1)

where F_{j_0} and F_{j_P} are the corrected pulserepetition frequencies at zero pressure and at pressure P, respectively. K_T is the isothermal bulk modulus (i.e., $K_T = K_s/(1 + \alpha T\gamma)$, where the quantity $(1 + \alpha T\gamma)$ is 1.0147 at 25°C) and M_j is an elastic modulus. The subscript j refers to either longitudinal or shear modulus. From the values of $\{dM_j/dP\}_{P=0}$ we calculated values of the first pressure derivatives of velocities from

$$\left\{ \left(\frac{\partial V_i}{\partial P} \right)_T \right\}_{P=0} = \left\{ \frac{1}{2\rho_0 V_i} \cdot \left[\left(\frac{\partial M_i}{\partial P} \right)_T - \frac{\rho_0 (1 + \alpha T \gamma) (V_i)^2}{K_s} \right] \right\}_{P=0}$$
(2)

where ρ_0 is the initial density of the specimen.

CHUNG AND SIMMONS

	Specimen Directions †			D 11771	
Elastic Properties*	I	п	III	(Arithmetic Mean)	
V_{v} , km/sec	9.717	9.690	9.687	9.698	
V _s , km/sec	6.028	6.004	5.995	6.009	
$\rho_0, V_p^2, 10^{11} \text{ dynes/cm}^2$	33.821	33.634	33.613	33.689	
$\rho_0 V_{s^2}$, 10 ¹¹ dynes/cm ²	13.016	12.912	12.874	12.934	
K_{\star} , 10 ¹¹ dynes/cm ²	16.467	16.418	16.448	16.444	
$V_{n'}$, 10 ⁻³ (km/sec)/kb	8.10	7.71	7.58	7.80	
$V_{*}', 10^{-3} (\rm km/sec)/kb$	3.93	3.72	3.60	3.75	
$(\rho V_p^2)'$	7.72	7.43	7.34	7.50	
$(\rho V_{*}^{2})'$	2.50	2.40	2.34	2.41	
K.'	4.39	4.23	4 22	4 28	

TABLE 1. Experimental Elastic Data for Polycrystalline Periclase $\rho_0 = 3.582$ g/cm³, at 25 °C.

* Primes denote the isothermal derivative with respect to pressure.

† Three directions are orthogonal; direction I is parallel to the pressing direction.

In Table 1 the results of these calculations along with the measured quantities are summarized. Direction I is parallel to the direction of hotpressing.

It should be noted that for the three orthogonal directions the largest differences in P and S velocities at room conditions were 0.3 and 0.5% of the mean values. These differences are about the same size as the estimated measurement errors; at room conditions, therefore, this specimen was considered elastically isotropic. Note that dV_P/dP and dV_s/dP depend on direction, and each shows about 8% difference. Because these differences are more than twice the size of the estimated experimental errors, we infer that the specimen is anisotropic with respect to the velocity derivatives. Pressure derivatives of elastic properties measured in one direction only of a hot-pressed specimen may not yield correct isotropic values of the aggre-

Properties*	Chung [1963]	Anderson and Schreiber [1965]	Soga and Anderson [1966]	Chung and Buessem [1967]†	Schreiber and Anderson [1968]	Present Work
$\rho_0, g/cm^3$	3.581	3.5800	3.581	3.5819	3.5797	3.582
V_{n} , km/sec	$9.68(\pm 0.06)$	9.7662	9.723	$9.693(\pm 0.025)$	9.6605	$9.698(\pm 0.020)$
V _s , km/sec	$6.00(\pm 0.03)$	5.9635	6.039	$6.008(\pm 0.012)$	5.9974	$6.009(\pm 0.010)$
$V_{p}', 10^{-3} (\text{km/sec})/\text{kb}$		7.71			8.66	$7.80(\pm 0.11)$
$V_{s'}$, 10 ⁻³ (km/sec)/kb		4.35			4.23	$3.75(\pm 0.08)$
K.'		3.916			4.58	4.28
$\sigma', 10^{-5} (\text{kb})^{-1}$		5.63			19.5	18.4
σ	0.18	0.203	0.186	0.187	0.186	0.187
4. 1011 dvnes/cm ²	$12.90(\pm 0.10)$	12.73	13.06	12.93	12.88	12.934
$K_{\rm eq}$ 10 ¹¹ dynes/cm ²	16.0	17.17	16.44	16.41	16.24	16.444
K_T , 10 ¹¹ dynes/cm ²		16.91				16.206
K_T'		3.94				4.35‡

TABLE 2. Comparison of Elastic Data from Several Sources All data are at 25°C.

* Primes denote isothermal pressure derivatives.

[†] Based on *Chung's* [1966] measurements but taken an arithmetic mean of three values determined on the three orthogonal directions of the specimen.

‡ Calculated from Bs' by using Overton's [1962] equation.