gate. We believe the mean value is likely to be near the correct value for this aggregate.

The present data are compared in Table 2 with some recent data from the literature. For the pressure derivatives of isotropic elastic parameters, our data differ significantly from the corresponding values reported by Anderson and Schreiber [1965] and by Schreiber and Anderson [1968]. Apparently, Anderson and Schreiber measured the properties of their hot-pressed specimens in one direction only. Yet a typical hot-pressed aggregate of polycrystalline periclase often exhibits preferred orientation of the crystal grains [see, for example, Tagai et al., 1967] with obvious effects on the elastic properties. We suggest that the apparent differences among the several sets of data reported by Anderson and Schreiber and by us here are possibly attributable to this preferred orientation produced by hot-pressing. Of course, the elastic properties may vary from sample to sample, but the important point of this paper is that, at least in certain respects, hot-pressed aggregates may be anisotropic and measurements on such samples should be made in more than one direction.

Acknowledgments. Sincere thanks are expressed to Francis Birch and Don L. Anderson for their comments.

Financial support was provided by the National Aeronautics and Space Administration under grant NGR-22-009-176.

REFERENCES

- Anderson, O. L., and E. Schreiber, The pressure derivatives of the sound velocities of polycrystalline magnesia, J. Geophys. Res., 70, 5241, 1965.
- Chung, D. H., Elastic moduli of single-crystal and polycrystalline MgO, *Phil. Mag.*, 8(89), 833, 1963. (See Table 3 on page 840.)
- Chung, D. H., Elastic anisotropy of single-crystals and the polycrystalline isotropic elastic moduli of solids, Ph.D. thesis, Pennsylvania State University, University Park, March 1966.
- Chung, D. H., and W. R. Buessem, The Voigt-Reuss-Hill approximation and elastic moduli of polverystalline MgO, CaF₂. β-ZnS. ZnSe. and CdTe, J. Appl. Phys., 38, 2535, 1967. (See Table 1 on page 2536.)
- Chung, D. H., and Gene Simmons, The pressure and temperature dependence of the isotropic elastic moduli of polycrystalline alumina, J. Appl. Phys., 39, 5316, 1968.
- Overton, W. C., Relation between ultrasonically measured properties and the coefficients in the solid equation of state, J. Chem. Phys., 37, 116, 1962. (See equation 7 on page 117.)
- Schreiber, E., and O. L. Anderson, Revised data on polycrystalline magnesium oxide, J. Geophys. Res., 73, 2837, 1968.
- Soga, N., and O. L. Anderson, High-temperature elastic properties of polycrystalline MgO and Al₂O₈. J. Am. Ceram. Soc., 49, 355. 1966.
- Tagai, H., T. Zisner, T. Mori, and E. Yasuda. Preferred orientation in hot-pressed magnesia, J. Am. Ceram. Soc., 50, 550, 1967.

(Received June 17, 1968; revised July 25, 1968, and December 27, 1968.)