

the bulk modulus of pore-free polycrystalline aggregates is given by

$$B^* = \frac{1}{2} (B_1 + B_2) \quad (7)$$

where B_1 is given by Eq. (4) and

$$B_2 = -V \cdot \frac{dp}{dV} \bigg|_{\epsilon_{ij}(C_{ijkl}, \tilde{R}) = \bar{\epsilon}} = f_2(c_{\mu\nu}) \quad (8)$$

where $c_{\mu\nu}$ are the single-crystal second-order elastic stiffnesses, ϵ_{ij} are the strain tensors, and f_2 is a functional constant which depends on the crystal symmetry. Hence, the appropriate Murnaghan parameters for the polycrystalline materials are

$$B_O^* = \{B^{*T}\}_{p=0} \quad (9)$$

and $B_O^{*'} = \{(B^{*T})'\}_{p=0} \quad (10)$

where, as before, the prime refers to the isothermal pressure derivative.

Note that B_1 and B_2 are the well-known Reuss and Voigt limits, respectively; for crystals of general symmetry, rigorous expressions for B_1 and B_2 are as follows [9]: