

Table 2. The Murnaghan parameters evaluated at different boundary conditions.
All values are at $T = \sim 300$ °K.

Material	$\gamma_{G(\text{thermal})}$	$\frac{T\gamma_G}{B^S} \left(\frac{\partial B^S}{\partial T} \right)_p$		$\{B_1\}_{p=0}$	$\{B^*\}_{p=0}$		$\left\{ \frac{dB_1}{dp} \right\}_{p=0}$	$\left\{ \frac{dB^*}{dp} \right\}_{p=0}$
				$(\times 10^{-11} \text{ dyn/cm}^2)$				
Mg	1.55 ^(a)	0.13	B^S	3.555	3.555	$(\partial B^S / \partial p)_S$	4.30	4.30
			B^T	3.439	3.440	$(\partial B^T / \partial p)_T$	4.17	4.17
Cd	2.20 ^(a)	0.13	B^S	4.858	5.316	$(\partial B^S / \partial p)_S$	6.41	6.27
			B^T	4.581	5.012	$(\partial B^T / \partial p)_T$	6.28	6.14
CdS	1.09 ^(b)	?	B^S	6.176	6.177	$(\partial B^S / \partial p)_S$	?	?
			B^T	6.154	6.155	$(\partial B^T / \partial p)_T$	4.15	4.15
α -Quartz	0.75 ^(c)	0.04	B^S	3.741	3.766	$(\partial B^S / \partial p)_S$	6.38	6.47
			B^T	3.714	3.738	$(\partial B^T / \partial p)_T$	6.34	6.43
α -Al ₂ O ₃	1.34 ^(d)	0.03	B^S	25.441	25.457	$(\partial B^S / \partial p)_S$	4.35	4.34
			B^T	25.281	25.296	$(\partial B^T / \partial p)_T$	4.32	4.31

- (a) J. G. Collins and G. K. White, in Progress in Low-Temperature Physics (C.J. Gorter, Editor), Vol. 4. p. 450, North-Holland Publishing, Amsterdam (1964).
- (b) Estimated from data cited by J. A. Corll, Phys. Rev. 157, 623 (1967).
- (c) G. K. White, Cryogenics 4, 2 (1964).
- (d) D. H. Chung and G. Simmons, J. Appl. Phys. (in press, 1968).