6. *n*-Tetradecafluoroheptene-1

Samples of polymer prepared at 8,100 atm. under γ-irradiation flow at temperature of 100°C; those prepared at 17,000 atm. do not flow at 200°C. Maximum conversion of monomer to polymer is 15%. *Transfer* limits the molecular weight, the transfer constant apparently increases with temperature.[3]

7. 1,1,2-Trifluorovinylphenyl Ether

Under γ-irradiation, the monomer polymerizes more slowly at 145°C than at 102°C. At 191°C the *dimer* forms to the complete exclusion of polymer.[3]

REFERENCES

1. H.T. Hall, J.D. Barnett, Final Report, 1 June 60-30 May 62, Grant DA-ORD-42, Brigham Young Univ.

2. D.W. Brown, L.A. Wall, "Radiation-Induced Polymerization of Propylene at High Pressure." National Bureau of Standards (manuscript).

3. D.W. Brown, L.A. Wall, "The Radiation-induced Polymerization of n-Tetradecafluoroheptene-1; 1,1,2-Trifluorovinylphenyl Ether, and 1,2,3,4,5-Pentafluorophenyl 1,1,2-Trifluorovinyl Ether at High Pressures." National Bureau of Standards (manuscript).

4. W.H. Mears et al., Status Report No. 1, 1 May 62 - 30 Sept 62, Contract DA-30-069-ORD-3551, Allied Chemical Corp., General Chemical Div.

5. H. Eyring and A.F. Gabrysh, Status Report No. 2, 1 Apr 62 - 30 Sept 62, Grant DA-ARO(D)-31-124-G243, Univ. of Utah.

6. L.A. Wall et al., Status Report No. 1, 1 June 60 - 31 Mar 61, ARO(D) Proposal 2703, National Bureau of Standards.

7. L.A. Wall et al., Status Report No. 2, 1 Apr 61 - 30 Sept 61 ARO(D) Proposal 2703, National Bureau of Standards.

8. L.A. Wall et al., Status Report No. 3, 1 Oct 61 - 20 Apr 62, ARO(D) Proposal 2703, National Bureau of Standards.

Prepared by George B. Cox