

## Indium Antimonide: the Metallic Form at Atmospheric Pressure

A. J. Darnell  
W. F. Libby

## Indium Antimonide: the Metallic Form at Atmospheric Pressure

Abstract. *The crystal structure of metallic indium antimonide at atmospheric pressure and  $-197^{\circ}\text{C}$  is essentially identical with that of white tin at  $26^{\circ}\text{C}$ .*

Compression of group IV elements and of group III-V and group II-IV binary compounds transforms them into metals (1-3). The phase change is marked by a large increase in density and a rise in the number of equivalent near neighbors from four, which is characteristic of these materials at low pressure, to six, which is characteristic of the new phase (4). The work of Drickamer and his co-workers (3) and of Kennedy and his co-workers (1) has clearly demonstrated the generality of the phenomenon.

Jamieson has examined the crystal structure of the metallic form of indium antimonide under high pressure and found it to be analogous to that of white tin. We now report a low-pressure study that shows the structure to be essentially identical with that of ordinary metallic tin.

The metallic form of InSb may be obtained at low pressures by cooling the material while it is under pressure and then reducing the pressure. The metallic form was first made as described previously (1-3) by application of pressures a few kilobars in excess of the transition pressure of 23 kb at a temperature of about  $95^{\circ}\text{C}$ . Periods of several hours were used to insure complete conversion.

Liquid nitrogen was then used to cool the entire assembly of press and sample. When the temperature of the sample had dropped to well below  $210^{\circ}\text{K}$  ( $-63^{\circ}\text{C}$ ) the pressure was released, and the sample was removed from the cylinder, which contained tungsten carbide. We found that the material was a very good metal with a very low resistance, comparable to that of aluminum at temperatures between  $77^{\circ}$  and  $210^{\circ}\text{K}$ . It was very shiny and metallic and extremely hard, somewhat like tool steel. It was found, empirically, to be stable for weeks, so long as it was kept at temperatures below  $-63^{\circ}\text{C}$ , and it was even possible to machine it.

An x-ray diagram was taken by the Debye-Scherrer technique at  $77^{\circ}\text{K}$ . The spectrum with  $\text{CuK } \alpha$  radiation is giv-

Table 1. Lattice spacings of white (or  $\beta$  tin) and metallic indium antimonide, InSb(II). The unit-cell dimensions for Sn( $\beta$ ) at  $26^{\circ}\text{C}$  and InSb (II) at  $-197^{\circ}\text{C}$  are, respectively,  $a$ ,  $5.831$  and  $5.72 \pm 0.16 \text{ \AA}$ ;  $c$ ,  $3.182$  and  $3.18 \pm 0.03 \text{ \AA}$ . The corresponding densities are, respectively,  $7.286$  and  $7.54 \pm 0.16 \text{ g/cm}^3$ .

<i>hkl</i>	Sn( $\beta$ ), $d(\text{\AA})$ ,	InSb(II), $d(\text{\AA})$ ,
	Cu. $1.5405 \text{ \AA}$	Cu. $1.5405 \text{ \AA}$
200	2.915	2.90
101	2.793	2.78
220	2.062	2.05
211	2.017	2.02
301	1.659	1.65
112	1.484	1.48
400	1.458	
		1.44*
321	1.442	

\* Unresolved.

en in Table 1, together with the lattice spacings of ordinary white tin (5).

It is clear from these data that the two structures are identical to within  $0.02 \text{ \AA}$  in the spacings for the body-centered tetragonal lattice (6).

A. J. DARNELL

W. F. LIBBY

Department of Chemistry, University of California, Los Angeles 24

### References and Notes

1. A. Jayaraman, R. C. Newton, G. C. Kennedy, *Nature* **191**, 1288 (1961); ———, "High pressure studies on diamond and zinc blende structures: melting and polymorphism," presented at the Diamond Symposium in Paris, May 1962.
2. B. J. Alder and R. H. Christian, *Phys. Rev. Letters* **8**, 367 (1961).
3. H. L. Suchan and H. G. Drickamer, *J. Chem. Phys.* **31**, 355 (1959); S. Minomura and H. G. Drickamer, *J. Phys. Chem. Solids* **23**, 451 (1962); G. A. Samara and H. G. Drickamer, *ibid.*, p. 457; ———, *J. Chem. Phys.* **37**, 408 (1962).
4. J. C. Jamieson, "Phase transitions under pressure of the semiconductor metal types and the earth's interior," Abstr. 1962 Ann. Meeting Geol. Soc. Am., p. 76A.
5. H. E. Swanson and E. Tatge, *Natl. Bur. Std. U.S. Circ.* **539** (1953), vol. 1, pp. 24-26.
6. Supported by the Directorate of Chemical Sciences, Air Force Office of Scientific Research under contract No. AF 49 (638)-901 and grant AF-AFOSR-245-63).

26 February 1963