

## REFERENCES

1. P. W. Bridgman, *Studies in Large Plastic Flow and Fracture*, McGraw-Hill, New York (1952).
2. P. W. Bridgman, The Effects of Pressure on the Tensile Properties of Several Metals and Other Materials, *J Appl Phys*, 24 (1953) 560.
3. P. W. Bridgman, The Tensile Properties of Several Special Steels and Certain Other Materials Under Pressure, *J Appl Phys*, 17 (1946) 201.
4. S. I. Ratner, Change of Mechanical Properties of Metals Under Hydrostatic Pressure, *Zh Tekh Fiz*, 19, 3 (1949) 408.
5. B. I. Beresnev, L. F. Vereshchagin, Y. N. Ryabinin, and L. D. Livshits, *Some Problems of Large Plastic Deformation in Metals Under High Pressure*, Pergamon Press (1963).
6. T. Pelczynski, The Influence of Hydrostatic Pressure on the Plastic Deformation Properties of Metals, *Arch Hutnictwa*, 7, 1 (1962) 3.
7. L. W. Hu, Determination of the Plastic Stress-Strain Relations in Tension of Nittany No. 2 Brass Under Hydrostatic Pressure, *Proceedings of 3rd International Congress of Applied Mechanics* (1958) 557.
8. A. Bobrowsky and E. Stack, Deformation of Metals Under High Pressure, *Proceedings of AIME Conference on Metallurgy at High Pressure and High Temperature* (1964).
9. T. E. Davidson, J. C. Uy, and A. P. Lee, The Tensile Fracture Characteristic of Metals Under Hydrostatic Pressures to 23 Kilobars, *Acta Met*, 14 (1966) 937.
10. H. Ll. D. Pugh, The Mechanical Properties and Deformation Characteristics of Metals and Alloys Under Pressure, *Proceedings of International Conference on Materials*, American Society for Testing Materials (1964).
11. H. Ll. D. Pugh, Recent Developments in Cold Forming, *Bulleid Memorial Lecture*, Vol. III, University of Nottingham (1965).
12. T. E. Davidson, The Structure and Stress State Sensitivity of Fracture Mechanisms in Two-phase Materials, Ph.D. Thesis, Rensselaer Polytechnic Institute, October 1967.

## Technical Papers for ASM Transactions Quarterly

The ASM Transactions Committee is inviting technical papers for consideration at its September meeting. Papers for this meeting should be submitted before 19 August 1968.

Manuscripts in triplicate, plus one set of unmounted original photographs and original tracings should be sent to the attention of John Parina, Staff Liaison, Transactions Committee, American Society for Metals, Metals Park, Ohio 44073.




Fig. 9. Fibrous to total fracture area vs pressure for Fe - C materials.

fracture mode to progressively convert to one of planar shear (12). Such a shift in fracture mode may not change the macroscopic fracture appearance, but is observed by electron fractographic examination.

### CONCLUSIONS

1. The effect of pressure upon the ductility of a series of annealed and spheroidized Fe - C materials ranging in carbon content from 0.004 to 1.1% C is highly structure sensitive in terms of the amount, shape and distribution of the cementite phase.

2. Annealed 0.004% C and spheroidized 0.40, 0.83 and 1.1% C materials exhibit a linear relationship between true strain to fracture and pressure with the slope decreasing with increasing carbon content.

3. Annealed 0.40, 0.83 and 1.1% C materials exhibit a polynomial relationship between pressure and true strain to fracture with the slope increasing with increasing pressure. The slope at low pressure and that for the best fit linear relationship for these material decreases with increasing carbon content. The slope at high pressure approaches that for the spheroidized materials.

4. The elongation as a function of pressure increases rapidly at lower pressures, then levels, or tends to level off, at higher pressures in all but the brittle annealed 1.1% C material. The leveling off of the increase in elongation is attributed to the pressure only affecting the area reduction in the necked region and not the uniform strain. In the 1.1% C

material, the elongation progressively increases with no leveling off even at 23.8 kbars. This is a combined effect of an effective increase in uniform strain, since brittle fracture is retarded, plus the contribution of the area reduction in necking.

5. No single or linear relationship exists for the materials investigated between pressure coefficient of ductility and strain hardening coefficient. A linear relationship does exist for the annealed 0.004% C and the spheroidized 0.40, 0.83 and 1.1% C materials, the remaining annealed materials falling far off this linear relationship.

6. No linear or continuous relationship exists between the ratio of fibrous to total fracture area as a function of pressure in those materials exhibiting a cup-cone type fracture at atmospheric pressure. There is a general decrease in the area ratio going to zero for all of the materials at high pressure. The pressure at which the fracture converts entirely to planar shear generally increases with increasing strength.

### ACKNOWLEDGMENTS

Appreciation is expressed to the Materials Research Institute, Rensselaer Polytechnic Institute, and to the Benét Research and Engineering Laboratory, Watervliet Arsenal, for the use of their facilities. Appreciation is also expressed to Mr. H. Nazarian for his assistance in the conduction of the high-pressure tests.