

radius of curvature to induce fracture. Where fracture did not occur the bent whiskers reverted to the initial shape when the constraint was removed. The results of bend tests on whiskers of different cross-section are given in Table 1.

From direct observations of the whiskers during bending and from the results of Table 1 it was concluded that:

(a) The maximum strength and flexibility were associated with whiskers of small cross-section and large length:diameter ratios. These whiskers also possessed smooth and apparently defect-free surfaces.

(b) Whiskers with an hexagonal cross-section had poor strength.

(c) When the bending moment was applied on the shortest side of a whisker section the whisker showed low strength.

(d) The presence of an oil film appeared to improve the strength of the whiskers, possibly by reducing the chance of surface damage.

(e) All whiskers fractured within the elastic limit.

Tensile testing. The tensile strength of whiskers was measured with an 'Instron' tensile testing machine with a load cell giving full-scale deflexion for 400 g. The whiskers were mounted on a reinforced cardboard holder with an accurately punched gauge length of 1 cm. Some of the

whiskers tested had a taper of about 2° over the gauge-length; for these the cross-sectional area was taken as the average of the minimum and maximum measured. Although more than 50 specimens were mounted and tested, only 8 of these fractured within the gauge-length; a large percentage of fractures occurred at the base of the mounting resin. The results are given in Table 2.

All fractures occurred without plastic deformation taking place. The fracture surfaces showed that all the fractures were conchoidal. The lower strength of the whiskers of hexagonal cross-section is not completely understood and, although these may contain axial voids, examination of the fracture surfaces did not reveal this phenomenon. Excluding specimen number 2, the mean value of the experimental tensile fracture stress of the first six specimens is 1.0×10^6 lb./in.², that is, about 2 per cent E . Transmission electron microscope examination of a large number of thin whiskers and platelets has not, so far, provided conclusive evidence of the presence of dislocation.

¹ Sutton, W. H., and Chorne, J., *Met. Eng. Quart. Amer. Soc. Met.*, 3, 44 (1963).

² Cottrell, A. H., *Proc. Roy. Soc., A*, 282, 2 (1964).

³ Kelly, A., *Proc. Roy. Soc., A*, 282, 63 (1964).

⁴ Evans, P. E., and Davies, T. J., *Nature*, 197, 597 (1963).

OPENING ELECTRICAL CONTACT: BOILING METAL OR HIGH-DENSITY PLASMA?

By PROF. F. LLEWELLYN JONES, C.B.E.*, and M. J. PRICE

Department of Physics, University College of Swansea, University of Wales

THE processes occurring at the opening of a low-voltage (~ 4 V) electrical contact have considerable fundamental physical interest as well as having practical importance in the field of electronic and communication engineering. It is well known¹ that, starting with the electrodes closely pressed together in the fully closed position, the opening process leads to a constriction of the current stream lines, which can produce intense local heating and melting of the penultimate microscopic region of contact. The maximum temperature in the contact is related to the potential difference by the ψ , θ theorem:

$$\psi = \left[2 \int_0^{0_m} \frac{\lambda}{\alpha} d\theta \right]^{1/2} \quad (1)$$

where ψ = a generalized potential equal to the electrical potential in the absence of thermo-electric effects, θ = temperature, λ = thermal conductivity and α = electrical conductivity. Thus, on gradual separation of the electrodes the constriction resistance increases and the temperature rises up to and past the melting-point of the metal. On continuing the withdrawal the molten volume increases and gets drawn out into a microscopic bridge of molten metal joining the solid electrodes; the contacts finally separate and the circuit opens only when the bridge is broken. The rupture process, however, can be very complicated and lead to transfer of metal from one electrode to the other, a process which, when continually repeated, can lead to the 'pip' and 'crater' formation which renders the contacts useless after some time. There is evidence^{1,2} to show that the matter transferred per operation ($\sim 10^{-12}$ cm³ in a 5-amp circuit) is related to the size of the molten metal bridge (width $\sim 10^{-4}$ cm/amp), so that the stability, growth and final rupture of the bridge are a matter of importance,

not only from practical considerations, but also from the point of view of the physical properties of metals in the molten state and at high temperatures.

In the first place, an important condition of equilibrium, at least in the earlier stages, is that which depends on the application of surface tension forces. The shapes of the bridges would then be surfaces of revolution satisfying the equation:

$$\Delta p = T \left(\frac{1}{R_1} + \frac{1}{R_2} \right) \quad (2)$$

and these are unduloids, catenoids or nodoids according as Δp is positive, zero or negative respectively³. Photographs of static microscopic bridges have indeed confirmed that these stable shapes can be attained¹. In the later stages of opening Δp will be negative, and experiment has established that the final stable shape is usually the nodoid. The ψ , θ theorem shows that the hottest region of the microscopic molten metal bridge between like electrodes will probably be the narrow neck and, at first sight, it might appear that this is the region at which the bridge is most likely to break. However, detailed investigation of this final process raises some important problems in the physics of metals at high temperatures, and, in particular, near their boiling points.

Mechanisms of Break

It can be seen at once from the ψ , θ theorem that the mechanism of rupture of the molten metal bridge involves the physical properties of the metal, not at any one temperature, but over a wide range of temperatures up to boiling-point, and a number of different processes of rupture are possible.

In the first place, continued separation of the electrodes and the drawing out of the bridge increases the contact resistance R_c ; consequently, the contact voltage V_c ($= R_c I_c$) for a given circuit current I_c continually rises.

* Present address: Scientific Research Council, Radio and Space Research Station, Datchet, Buckinghamshire.