

Mg₂Si and Mg₂Ge.) Such a small charge is consistent with the covalent nature of the bonding in these compounds, yet it is large enough to account for the infrared reflectivity spectrum which is characteristic of an ionic compound.

Calculations of the lattice vibration frequencies in Mg₂Sn could be compared with experiment only by comparing the calculated and experimental Debye curves. Good agreement was attained when the polarizability of the Sn was taken into account. The sharp minimum in the Debye temperature near 20°K was found to be due to a low-lying transverse acoustic mode. Inelastic neutron scattering has revealed such a mode in Ge^(18,27) and GaAs.^(18,28) More experimental information, such as the Raman spectrum, multiple phonon absorption frequencies, and inelastic neutron scattering, is necessary to provide a more accurate description of the phonons in Mg₂Sn, but, the results of the present investigation are thought to give a reasonable first approximation.

Acknowledgments—The authors would like to acknowledge the assistance of Mr. H. R. SHANKS in the early part of the experimental work and especially for measuring the thermal expansion coefficient. The authors would also like to thank L. D. CROSSMAN for growing the crystals.

REFERENCES

1. WHITTEN W. B., CHUNG P. L. and DANIELSON G. C., *J. Phys. Chem. Solids* **26**, 49 (1965).
2. CHUNG P. L., WHITTEN W. B. and DANIELSON G. C., *J. Phys. Chem. Solids* **26**, 1753 (1965).
3. KAHAN A., LIPSON H. G. and LOEWENSTEIN E. V., *Proc. 7th Int. Conf. Phys. of Semicond.*, Paris, 1067 (1964).
4. JELINEK F. J., SHICKEL W. D. and GERSTEIN B. C., *Thermal Study of Group II-IV Semiconductors. II. Heat Capacity of Mg₂Sn In the Range 5-300°K.*, *J. Phys. Chem. Solids* **28**, 267 (1967).
5. MORRIS R. G., REDIN R. D. and DANIELSON G. C., *Phys. Rev.* **109**, 1909 (1958).
6. KOENIG P., LYNCH D. W. and DANIELSON G. C., *J. Phys. Chem. Solids* **20**, 122 (1961).
7. HELLER M. W. and DANIELSON G. C., *J. Phys. Chem. Solids* **23**, 601 (1962).

8. WHITTEN W. B. and DANIELSON G. C., *Proc. 7th Int. Conf. Phys. of Semicond.*, Paris, 537 (1964).
9. CROSSMAN L. D. and TEMPLE P. A., *Bull. Am. Phys. Soc.* **11**, 1121 (1965).
10. WILLIAMS J. and LAMB J., *J. Acoust. Soc. Am.* **30**, 308 (1958).
11. MCSKIMIN H. J., *J. appl. Phys.* **24**, 988 (1953).
12. NBS Circular 539, Vol. V, p. 41.
13. SHANKS H., Private communication.
14. HUNTINGTON H. B., *Solid State Physics* **7**, 218 (1958).
15. WILLARDSON R. K. and BEER A. C., *Semiconductors and Semimetals*, Vol. 2, p. 56, Academic Press, New York (1966).
16. LYDDANE R. H., SACHS R. G. and TELLER E., *Phys. Rev.* **59**, 673 (1941).
17. DICK B. G. and OVERHAUSER A. W., *Phys. Rev.* **112**, 90 (1958).
18. See for example, *Lattice Dynamics, Proc. Int. Conf. Denmark*, Ed. by WALLIS R. F. (1963).
19. MOOSER E. and PEARSON W. B., *J. Electronics* **1**, 629 (1956).
20. BLUNT R. F., FREDERIKSE H. P. R. and HOSLER W. R., *Phys. Rev.* **100**, 663 (1955).
21. LICHTER B. D., *J. electrochem. Soc.* **109**, 819 (1962).
22. KARO A. M. and HARDY J. R., *Phys. Rev.* **129**, 2024 (1963).
23. KELLERMANN E. W., *Phil. Trans. R. Soc. (London)* **A238**, 513 (1940).
24. GANESAN S. and SRINIVASAN R., *Can. J. Phys.* **40**, 74 (1962).
25. SZIGETI B., *Trans. Faraday Soc.* **45**, 1955 (1949).
26. SZIGETI B., *Proc. R. Soc. A* **204**, 51 (1950).
27. BROCKHOUSE B. N. and IYENGAR P. K., *Phys. Rev.* **111**, 74 (1958).
28. DOLLING G. and WAUGH J. L. T., *Lattice Dynamics, op. cit.*, p. 19.

APPENDIX

Following GANESAN and SRINIVASAN⁽²⁴⁾ we define the matrix of force constants between one ion and another. The matrix can be written most generally as

$$D = \begin{pmatrix} \phi_{xx} & \phi_{xy} & \phi_{xz} \\ \phi_{yx} & \phi_{yy} & \phi_{yz} \\ \phi_{zx} & \phi_{zy} & \phi_{zz} \end{pmatrix}$$

where, for example, $\phi_{xy} = (\partial^2 \phi / \partial x \partial y)$ is evaluated at the equilibrium separation. ϕ is the two-body potential associated with the short range forces between one ion and another.

We list the matrix of force constants for the Sn core-Sn shell, nearest neighbor Mg-Sn, next nearest