

[655]

CORRESPONDENCE

Evidence for a Third Phase of Mercury

By P. R. DOIDGE and A. R. EASTHAM

Department of Physics, University of Surrey, London, S.W.11

[Received 16 March 1968 and after revision 7 May 1968]

ABSTRACT

It has been found that tensile deformation at liquid helium temperature partially transforms α -mercury to a γ phase which is distinguished from the α and β phases by having a lower superconducting critical field curve and a lower transition temperature ($T_{c\gamma} = 3.74 \pm 0.05^\circ\text{K}$ compared with the values found by Schirber and Swenson (1961), $T_{c\alpha} = 4.153^\circ\text{K}$ and $T_{c\beta} = 3.949^\circ\text{K}$). Resistance measurements show that the γ phase transforms back to α -mercury at about 53°K .

The simple rhombohedral α phase of mercury remains unchanged at atmospheric pressure down to liquid helium temperatures (Barrett 1957). Bridgman (1935) first observed a transition under pressure to the β phase, which was found to have a body-centred tetragonal structure by Atoji, Schirber and Swenson (1959). Swenson (1958) found that this β phase, once formed, was stable at atmospheric pressure up to 79°K , at which temperature it transformed back to the α phase. High pressure was found to be necessary and in addition shear was helpful in forming the β phase, and Schirber and Swenson (1962) suggested that the transformation was martensitic in nature. In the present investigation we have found that simple tensile deformation of α -Hg at 4.2°K partially transforms it to a phase which has a lower superconducting transition temperature and critical field curve than those of either the α or β phases as found by Schirber and Swenson (1961); we therefore call it the γ phase.

For superconducting magnetization measurements rod specimens 7 cm long and 2.4 mm diameter were prepared from triply distilled mercury having about 1 p.p.m. non-gaseous impurities. The rods were gripped in a simple tensometer and pulled in tension in liquid helium. The magnetization M was determined from fluxmeter deflections on moving a pair of oppositely wound co-axial coils from one position around the middle of the specimen to another remote from the specimen; in both positions there was zero mutual inductance between the empty coil pair and the field coil.

Evidence for the γ phase is shown in the magnetization curves of figs. 1(a) and (b), which were obtained in increasing field from, respectively, a