

TABLE V. Calculated variables.

Pressure P (kbar)	Isothermal compress- ibility β_T (bar ⁻¹)	Thermal- expansion coefficient α (°C ⁻¹)	Density ρ (g/cm ³)	Volume V ($V=1.0$ at 0°C)	Adiabatic compress- ibility β_{ad} (bar ⁻¹)
$T=21.9^\circ\text{C}$					
1	3.881×10^{-6}	1.766×10^{-4}	13.5948	1.00000	3.395×10^{-6}
2	3.751	1.724	13.6468	0.99621	3.289
3	3.632	1.685	13.6973	0.99254	3.192
4	3.522	1.648	13.7463	0.98900	3.102
5	3.419	1.614	13.7941	0.98557	3.018
6	3.324	1.581	13.8407	0.98225	2.941
7	3.235	1.551	13.8862	0.97904	2.868
8	3.15	1.52	13.931	0.9759	2.799
9	3.07	1.50	13.974	0.9729	2.735
10	3.00	1.47	14.017	0.9699	2.674
11	2.93	1.45	14.058	0.9671	2.616
12	2.87	1.42	14.099	0.9643	2.562
13	2.80	1.40	14.139	0.9615	2.510
$T=40.5^\circ\text{C}$					
1	3.963×10^{-6}	1.762×10^{-4}	13.5503	1.00330	3.444×10^{-6}
2	3.827	1.719	13.6032	0.99941	3.334
3	3.702	1.680	13.6545	0.99565	3.234
4	3.587	1.643	13.7043	0.99203	3.141
5	3.481	1.608	13.7528	0.98853	3.055
6	3.383	1.576	13.8001	0.98514	2.975
7	3.290	1.545	13.8462	0.98186	2.900
8	3.20	1.52	13.891	0.9787	2.829
9	3.12	1.49	13.935	0.9756	2.763
10	3.05	1.46	13.978	0.9726	2.701
11	2.98	1.44	14.020	0.9697	2.641
12	2.91	1.41	14.062	0.9668	2.585
13	2.84	1.39	14.102	0.9640	2.532
$T=52.9^\circ\text{C}$					
1	4.018×10^{-6}	1.760×10^{-4}	13.5207	1.00550	3.477×10^{-6}
2	3.878	1.717	13.5742	1.00154	3.365
3	3.749	1.677	13.6261	0.99773	3.262
4	3.632	1.640	13.6764	0.99405	3.167
5	3.523	1.605	13.7254	0.99050	3.080
6	3.422	1.572	13.7732	0.98707	2.998
7	3.327	1.542	13.8197	0.98375	2.921
8	3.24	1.51	13.865	0.9805	2.850
9	3.16	1.48	13.910	0.9774	2.782
10	3.08	1.46	13.953	0.9743	2.719
11	3.01	1.43	13.995	0.9714	2.659
12	2.94	1.41	14.037	0.9685	2.602
13	2.87	1.39	14.078	0.9657	2.548

$P=13,5874$
at 25°C

pressure, for three temperatures, has been established while the change of velocity with temperature at 1 atm is given by Hubbard and Loomis.²⁷ The values for C_P at 1 atm and various temperatures are given by Douglas *et al.*³⁴ to an accuracy of 0.3%. Values for α at atmospheric pressure and T have been taken from the work of Beattie *et al.*,³⁵ which establishes α within about 1 part in 10^5 . The density ρ is given by Bigg,³⁶ who used the most recent determination of the density of Hg at

20°C, in conjunction with Beattie's expansion formula, to determine ρ as a function of temperature to within about 4 ppm. Using the data for ρ and the sonic-velocity data of Hubbard and Loomis, the adiabatic compressibility of liquid Hg may be calculated according to Eq. (3). Using β_{ad} , and α and C_P from the above sources, β_T may be calculated according to Eq. (4). All the data are thus established for the initiation of the calculation at $P_1=1$ atm. The numerical values of the input data are shown in Table IV.

The results of the calculation for α , β_T , β_{ad} , ρ , and V as a function of P at 21.9°, 40.5°, and 52.9°C are shown in Table V. Figures 5-7 show the variation of α , β_T , and V with pressure. No variation of C_P with P

³⁴ T. B. Douglas, A. F. Ball, and D. C. Ginnings, *J. Res. Natl. Bur. Std.* **46**, 334 (1951).

³⁵ J. A. Beattie, B. E. Blaisdell, J. Kaye, H. T. Gerry, and C. A. Johnson, *Proc. Am. Acad. Arts Sci.* **74**, 371 (1941).

³⁶ P. H. Bigg, *Brit. J. Appl. Phys.* **15**, 1111 (1964).