

LIST OF TABLES

<u>Table No.</u>		<u>After Page</u>
1-1	Properties of the Alkali Metals	8
2-1	The Ettingshausen, Nernst, and Righi-Leduc Effects	26
3-1	Hall Voltages of Four Alkali Metals at Room and Liquid Nitrogen Temperatures	40
3-2	Hall Constants for Lithium, Sodium, and Potassium	40
4-1	Warping Parameters for the Alkali Metals Computed from Data of F. Ham	46
4-2	Warping Parameters of Alkali Metals at Two Pressures, computed from Data of F. Ham	46
4-3	Velocity of Sound in Potassium	56
4-4	Scattering Functions for K and Li using Bailyn's values of u^3 (JS) ²	58
4-5	Scattering functions for k in 110 direction	60
4-6	Scattering functions for k in 100 direction	
4-7	Scattering functions for k in 111 direction	60
4-8	I(k) for Various Conditions	60

Abstract

Recent band structure calculations by Ham indicate how the Fermi surface of the alkali metals, which is expected to be nearly spherical under normal conditions, may change when the lattice constant is decreased through hydrostatic pressure. Since direct measurement of the distortion of the Fermi surface is difficult, we have tried to study its magnitude by measuring the Hall voltage in the alkalis as a function of hydrostatic pressure up to $15,000 \text{ kg/cm}^2$. In each case the Hall voltage decreases with increasing pressure, the size of the decrease ranging from 2 percent in $15,000 \text{ kg/cm}^2$ for lithium to 37 percent in $15,000 \text{ kg/cm}^2$ for cesium before compressibility corrections are applied.

The Hall constant, R , can be written as $1/Necn^*$ where n^* is a factor of the order of unity which expresses the deviation from the free electron value of the Hall constant. The data, with all explicit volume dependence removed, are expressed in the form of curves of n^* vs. pressure. In all of the alkalis except cesium, n^* decreases monotonically with increasing pressure; the decreases range from 5 percent in $15,000 \text{ kg/cm}^2$ for lithium to 8 percent in $15,000 \text{ kg/cm}^2$ for rubidium. In the case of cesium n^* passes through a minimum at 5000 kg/cm^2 and rises to a value of 1.2 at $15,000 \text{ kg/cm}^2$.

The change of n^* between room and liquid nitrogen temperatures was also measured. In all of the alkalis except lithium the change is less than 3 percent. In lithium n^* decreases by about 25 percent between room and liquid nitrogen temperature.

The warping of a nearly spherical Fermi surface is described by Kubie harmonics and the effect of the warping on n^* considered. Increases in the warping parameters increase n^* ; since the band structure calculations indicate that increasing pressure increases the warping parameters, the data cannot be explained on the basis of anisotropic Fermi surfaces alone. If anisotropic scattering times as well as warped Fermi surfaces are considered, then increases of the warping parameters can cause decreases in n^* .