

45. Reference 42.
46. H. Brooks, private communication.
47. Reference 5, p. 185.
48. D. H. Tombouliau, Handbuch der Physik, Springer Verlag, Berlin 30, 272, (1957)
49. J. Hatton, Phys. Rev. 100, 681 (1955).
50. P. Kapitza, Proc. Roy. Soc. A123, 292 (1929).
51. A. H. Wilson, The Theory of Metals, Cambridge Univ. Press, p. 226, (1953).

II. Experimental Techniques

A. Electrical

1. The measurement problem.

The voltage produced by a Hall effect sample is

$$V_H = RHI/t \quad (II-1)$$

where

- V_H - Hall voltage
- H - magnetic field in gauss
- I - current in amps
- t - thickness in cm
- R - Hall constant in volt-cm/amp - gauss

We can estimate the Hall voltage produced by a typical alkali, sodium. Using $R = 21 \times 10^{-13}$ volt-cm/amp - gauss, $H = 6000$ gauss, $I = 3$ amps, and $t = .05$ cm, we obtain $V_H = .75$ microvolts. As we measure the voltage produced when the magnetic field is reversed we actually measure $2V_H$ or 1.5 microvolts.

If we estimate a change of about 10 percent in the Hall voltage in $15,000 \text{ kg/cm}^2$ and wish to measure this change to at least 10 percent, we must resolve changes of 1 percent in V_H . This means we need a measuring system that can resolve 10^{-8} volts.

2. The choice of an ac or dc method.

Hall voltage measurements may be performed using either an ac or dc system. In an ac system a dc magnetic field and an ac sample current can be used. The Hall voltage is then an ac voltage having the same frequency as the sample current. Such a system is described in detail by Lavine [1, 2]. Its advantages include the elimination of contact, thermoelectric, and thermomagnetic potentials. Furthermore, ac amplifiers provide sensitive detectors. Lavine also pointed out a serious defect of the ac method. The high currents, of the order of an ampere, flowing through the sample cause it to vibrate in the