

HP6

Metal	a atomic units	$\frac{ak_{100}}{2\pi}$	$\frac{ak_{110}}{2\pi}$	$\frac{ak_{111}}{2\pi}$	A	A ₁
Li	8.11	.613	.623	.613	-.002	-.005
	6.65	.607	.634	.613	-.011	-.011
	5.34	.575	.665	.590	-.031	-.037
Na	10.04)	No anisotropy				
	8.11)					
	6.65)					
K	11.46	.625	.640	.625	-.003	-.007
	10.05	.620	.620	.620	0	0
	8.11	.585	.675	.575	-.013	-.049
Rb	12.57	.611	.629	.611	-.004	-.009
	10.74	.605	.627	.605	-.005	-.011
	9.05	.560	.680	.560	-.028	-.061
Cs	13.35	.600	.655	.600	-.013	-.027
	11.46	.580	.670	.580	-.021	-.045
	10.04	.495	.655	.495	-.041	-.088

Table 4-1

Warping Parameters for Alkali Metals Computed
from Data of F. Ham