

TABLE 4. THE EFFECT OF PRESSURE ON THE IDEAL RESISTIVITY OF POTASSIUM

T ($^{\circ}\text{K}$)	$-\partial \ln \rho_i / \partial p$ (10^{-5} atm^{-1})	$-A$ (10^{-5} atm^{-1})	B (10^{-9} atm^{-2})	$-C$ ($10^{-13} \text{ atm}^{-3}$)	$\partial \ln \rho_i' / \partial \ln V$
Specimen K (2)					
15.4 ₀	24.1 \pm 0.4	23.2 \pm 0.3	37 \pm 5	60 \pm 100	8.5 ₅ \pm 0.15
20.3 ₅	22.8 \pm 0.3	21.9 \pm 0.2	29 \pm 5	12 \pm 100	8.1 ₅ \pm 0.1
29.8	20.6 \pm 0.2	19.6 ₅ \pm 0.2	23 \pm 2	11 \pm 38	7.3 ₂ \pm 0.1
61.1	17.0 \pm 0.2	16.0 \pm 0.2	17 \pm 1	12 \pm 29	6.0 ₂ \pm 0.1
78.0	16.7 \pm 0.2	15.7 \pm 0.2	19 \pm 2	15 \pm 20	5.7 ₄ \pm 0.1
116.7	16.9 ₅ \pm 0.2	15.9 ₅ \pm 0.2	17 \pm 1	5 \pm 18	5.7 ₀ \pm 0.1
196.6	18.1 \pm 0.1	17.0 \pm 0.1	23 \pm 2	17 \pm 38	5.6 ₄ \pm 0.1
273.7	19.0 \pm 0.1	17.9 \pm 0.1	22 \pm 1	11 \pm 41	5.7 ₅ \pm 0.15
308.8	20.1 \pm 0.2	18.9 \pm 0.2	27 \pm 1	18 \pm 20	5.6 ₀ \pm 0.15
308.8*	—	—	—	—	5.7 ₂ * \pm 0.05
Specimen K (5)					
4.2 ₀ †	30 \pm 3	—	—	—	10.7 \pm 1
20.4 ₀	22.8 ₅ \pm 0.2	21.9 \pm 0.2	28 \pm 5	-9 \pm 100	8.1 ₀ \pm 0.1
36.5	19.7 \pm 0.2	18.8 \pm 0.2	25 \pm 2	23 \pm 40	7.0 ₃ \pm 0.1
79.2	16.8 \pm 0.2	15.8 \pm 0.2	19 \pm 2	13 \pm 50	5.8 ₀ \pm 0.1
273.1 ₅	19.2 \pm 0.1	18.1 \pm 0.1	26 \pm 1	21 \pm 41	5.5 ₀ \pm 0.15
Bridgman (1921, 1925)					
273.1 ₅	20.4 \pm 0.5‡	—	—	—	—
298.0	19.6 \pm 0.5	—	—	—	—
333.0	21.1 \pm 0.5	—	—	—	—

* This point corresponds to the density at 308.8 $^{\circ}\text{K}$.

† A large correction was necessary for the effect of pressure on residual resistivity.

‡ Estimated error.

TABLE 5. DETAILS OF THE SODIUM SPECIMENS

specimen	$R_{4.2 \text{ } ^{\circ}\text{K}} / R_{273 \text{ } ^{\circ}\text{K}}$	comments	source of material
Na (1)	6.9×10^{-4}	—	laboratory stock
Na (2)	7.1×10^{-4}	—	
Na (3)	4.0×10^{-4}	specimen in glass capillary*	N. V. Phillips, Eindhoven
Na (4)	2.0×10^{-4}		
Na (5)	2.9×10^{-4}		
Na (6)†	3.0×10^{-4}	—	Messrs A. D. Mackay & Co., New York
Na (7)	3.8×10^{-4}	—	
Na (9)	7.3×10^{-4}	—	laboratory stock

* We are grateful to Dr S. B. Woods for the loan of this specimen.

† The absolute resistivity of a specimen from this stock was $4.7_5 \times 10^{-6} \Omega \text{ cm}$ at 22.0 $^{\circ}\text{C}$ (corrected for residual resistivity). The precision of this result is about 1%. Previous values at this temperature are $4.7_0 \times 10^{-6} \Omega \text{ cm}$ (Hackspill 1910) and $4.8_4 \pm 0.1 \times 10^{-6} \Omega \text{ cm}$ (Bradshaw & Pearson 1956).