

as discussed by Wilson and Pitt.<sup>2)</sup>

The compressibilities of  $\text{NiS}_2$  at room temperature were obtained from the results of the present study;  $(9.2 \pm 0.5) \times 10^{-4} \text{ kbar}^{-1}$  for insulating phase and  $(7.1 \pm 0.5) \times 10^{-4} \text{ kbar}^{-1}$  for metallic phase.

The authors wish to thank M. Hatakeyama and M. Yasukawa for their help in the experimental work.

#### References

- (1) J. A. Wilson, *Advance in Phys.* 21(1972) 143.
- (2) J. A. Wilson and G. D. Pitt, *Phil. Mag.* 23 (1971) 1297.
- (3) S. Endo, T. Mitsui, K. Yamakawa and T. Yagi, *Japan J. Appl. Phys.* 4 (1971) 534.
- (4) D. L. Decker, *J. Appl. Phys.* 42 (1971) 3239.