

after four months exposure to the atmosphere for high pressure orthorhombic type  $\text{HoSb}_2$ . A sample of  $\text{LaSb}_2$  type  $\text{TbSb}_2$  was exposed to the atmosphere initially and then sealed in an X ray capillary tube and showed no decomposition which could be detected by X ray diffraction analysis after four months.