

Preprint

This is a preprint of a paper intended for publication in a journal or proceedings. Since changes may be made before publication, this preprint is made available with the understanding that it will not be cited or reproduced without permission of the author.

Physical Review B

EFFECT OF PRESSURE ON THE FERROMAGNETIC  
TRANSITION OF  $\text{MnAs}_x\text{Sb}_{1-x}$  SOLID SOLUTIONS\*

EDWA-LR-72-0041

L. R. Edwards and L. C. Bartel

Sandia Laboratories, Albuquerque, New Mexico 87115

ABSTRACT

The ferromagnetic transition temperature of  $\text{MnAs}_x\text{Sb}_{1-x}$  solid solutions for  $0 \leq x \leq 1$  have been measured as a function of pressure up to 4.5 kbar. Previous work has shown that for the solid solutions in the concentration range  $0.9 \lesssim x \leq 1$  the magnetic transition is first-order and is accompanied by a hexagonal to orthorhombic structure transformation, while for  $0 \leq x \lesssim 0.9$  the magnetic transition is second-order with no structural change. We have found that the initial pressure derivative of the transition temperature,  $\partial T_c / \partial P$ , changes discontinuously in the narrow concentration range  $0.87 \lesssim x \leq 0.90$ , further demarcating the first and second-order regions. We show that an itinerant electron ferromagnet model can be applied to the solid solutions which exhibit second-order behavior. From the experimental values of  $\partial T_c / \partial P$  a minimum value of the Stoner enhancement factor,  $(\bar{I} - 1)^{-1}$ , is estimated for the second-order solid solutions. We also find that substituting Sb for As in the first-order region increases the critical pressure,  $P_c$ , which stabilizes the orthorhombic phase to lowest temperature. This further supports Goodenough's observation of a critical molar volume range in which the first-order transformation occurs.

AUG 20 1971

## I. INTRODUCTION

The isomorphous metallic compounds MnAs and MnSb have different magnetic properties which are believed to be due to differences in the Mn-Mn separation distance. For increasing temperature, MnAs exhibits a first-order ferromagnetic (FM) to paramagnetic (PM) transition at 313°K which is accompanied by a change in crystal symmetry from the hexagonal NiAs structure ( $B 8_1$ ) to the orthorhombic MnP structure ( $B 31$ ). (Hereinafter we use FM to denote ferromagnetic, ferromagnet, or ferromagnetism, and similarly for PM.) On further heating, a second-order transition involving a change from a low-spin PM to a high-spin PM phase and a change in crystal symmetry from the orthorhombic ( $B 31$ ) to hexagonal structure ( $B 8_1$ )<sup>1</sup> is observed at 398°K. On the other hand, MnSb has a second-order FM to PM transition at 572°K with the crystal structure remaining hexagonal ( $B 8_1$ ) through the transition.<sup>2</sup> A complete series of solid solutions is formed by MnAs and MnSb in which the hexagonal lattice parameters decrease monotonically from MnSb to MnAs.<sup>3</sup>

The various magnetic transition temperatures and crystal structures of the solid solutions  $MnAs_xSb_{1-x}$  as reported by Sirota and Vasilev<sup>4</sup> and Goodenough et al.<sup>5</sup> are summarized in Fig. 1. Here, for increasing temperature,  $T_c$  denotes the FM to PM transition temperature,  $T'$  denotes the PM to PM transition temperature at which the effective moment decreases, and  $T_t$  is a PM to PM transition temperature at which the effective moment increases and the crystal structure changes from orthorhombic to hexagonal. For the solid solutions in the concentration range  $0.9 \leq x \leq 1.0$  the transition from the FM hexagonal phase to the PM orthorhombic phase is first-order. All other transitions are second-order.

From Fig. 1 we see that over the concentration range  $0 \leq x \leq 0.80$  the FM to PM transition temperature,  $T_c$ , decreases with increasing As concentration. In addition, the effect of substituting As for Sb is to decrease the lattice