

The magnetostriction of $\text{Pd}_{97}\text{Fe}_{03}$ is linear in H above $H \sim 5$ kOe, in accordance with Eq. (3), when μ is assumed independent of H . The slope of this linear variation, together with the measured saturation magnetization, gives $\partial \ln \mu / \partial \ln V = -0.06 \pm 0.01$. The non-linear magnetostriction below $H \sim 5$ kOe is characteristic of these alloys in the field and temperature range where their magnetization is also appreciably field-dependent.⁶ In sample $\text{Pd}_{99.7}\text{Fe}_{00.3}$ this non-linear field-dependence persists up to the highest fields at 4.2°K, since this is close to the Curie temperature of the alloy. However at 1.7°K a satisfactory linear variation over a wide field range is obtained as shown in Fig. 1.

The resultant values of $\partial \ln \mu / \partial \ln V$ for these alloys and also for $\text{Pd}_{99}\text{Fe}_{01}$, whose magnetostriction is not shown in Fig. 1, are listed in Table 1. The values of $JX/(1+JX)$ for substitution in Eq. (2) were obtained from the measured saturation magnetization for each alloy by taking $\mu_0 = 3.3 \mu_B$ for the local moment on an Fe site measured by large-angle neutron scattering.⁷

The resistivity of the most dilute PdFe alloy has a discontinuity in the temperature dependence near the Curie temperature T_c , as shown in Fig. 2. Curves obtained at atmospheric pressure and at high pressure in different apparatus⁸ show that the discontinuity associated with T_c decreases at a rate $dT_c/dP = -4 \pm 4 \times 10^{-6} \text{ }^\circ\text{K bar}^{-1}$. The corresponding value of $d \ln T_c / d \ln V$ is given in Table 1, and $d \ln J / d \ln V$ is evaluated by use of Eq. (5).