




FIG. 3. Pressure effect on T_α as determined from basic C_{33} vs. temperature data. ($C_{33} = \rho V_{[001]}^2$)




FIG. 4. Variations with hydrostatic pressure of T_α and the temperatures delineating the high acoustic attenuation for C_{11} mode in uranium. The T_c vs. pressure curve obtained from Reference 9 to 8 kbar and reference 7 at $p > 8$ kbar.

integral number of specimen waves, V = wave velocity, t = crystal thickness and the subscripted terms represent the basis data at 77.8°K. T_α is defined as the temperature at which there occurs

an abrupt change in slope of the $f/f_{77.8}$ vs. T curves. For the [100] data, Fig. 1, T_α cannot be directly observed because of the very large acoustic attenuation that is associated with the

softness of this mode near the phase transition. The decrease with pressure in T_α and the temperature of high attenuation is, however, clearly indicated, as is the reduction of the hysteresis effects² at $T < T_\alpha$. The data for the [010] direction, Fig. 2, clearly show T_α at two different hydrostatic pressures as well as at 1 bar or 0 psi. The [001] data, Fig. 3, show that unambiguous shift in T_α between 1 bar and 0.35 kbar (5,000 psi). At 4.07 kbar, however, there is a clear change in the character of the data for [001] so that T_α is less well defined.

The data for dT_α/dP are summarized in Fig. 4, where the indicated T_α marked a, b and c refer to [100], [010] and [001], respectively. The points (a) were obtained by interpolation of the [100] data. The decrease in T_α with increasing pressure is very near linear, with $dT_\alpha/dP = -3.4^\circ\text{K/kbar}$. The lines marked T_{MX} and T_{MN} delineate the temperature range at a given pressure over which the longitudinal [100] mode signal is lost to attenuation and the pressure range at a given T that this mode velocity decreases with increasing pressure. Finally, the reported superconducting T_c vs. pressure data are reproduced

from reference 9 and 7. We arrive at the conclusion that the maximum T_c occurs at or near the pressure at which $T_c = T_\alpha$. This is a rather different conclusion than is reached from a direct volume to valence relation. It is consistent, however, with the concept that $T_{c,\text{max}}$ occurs when the electronic effects produced by cooling from T_α are completely reversed by ~ 10 kbar pressure or, similarly, ~ 10 kbar pressure is sufficient to retain the bulk superconducting α phase during cooling. It is not, however, necessarily inconsistent with an electron-phonon coupling model. The indications are that $T_{c,\text{max}}$ occurs where $\omega_{[100]}$, the frequency for [100] longitudinal phonons, reaches a minimum value under hydrostatic pressure. In subsequent experiments we will attempt to measure the pressure dependence of the transverse mode velocities at 4°K and thereby estimate the changes in the whole phonon spectrum with pressure at superconducting temperatures.

Acknowledgements — We are indebted to J.L. Mundy for the use of his high pressure intensifying and measuring system, to D. Gerlich and B. Porte for technical assistance in design and operation of the pressure cell and to J.W. Garland and H. Montgomery for discussions.

REFERENCES

1. FISHER E.S., and McSKIMIN H.J., *Phys. Rev.* **124**, 57 (1961).
2. FISHER E.S. and DEVER D., *Phys. Rev.* **170**, 607 (1968).
3. BRODSKY M.D., GRIFFIN N.J. and ODIE M.D., *J. appl. Phys.* **40**, 895 (1969).
4. JCUSSET J.C., *Acta Met.* **14**, 193 (1966).
5. LANDER G.H., and MUELLER M.H., *Acta Crystallogr.* (to be published).
6. GEBALLE T.H., MATTHIAS B.T., ANDRES K., FISHER E.S., SMITH T.F., and ZACHARIESEN W.H., *Science* **152**, 755 (1966).
7. GARDNER W.E. and SMITH T.F., *Phys. Rev.* **154**, 309 (1967).
8. HO J.C., PHILLIPS N.E. and SMITH T.F., *Phys. Rev. Lett.* **17**, 694 (1966).
9. PALMY C. and FISHER E.S., *Solid State Commun.* **8**, (1970).
10. GARLAND J.W., 1969 *Spring Superconducting Symposia*, NRL Report 6962, Naval Research Laboratory, Washington D.C. (March 28, 1969).