

c/a ratio <1.60 , the changes in the shear moduli, C_{44} and C_{66} , with pressure are strongly influenced by the change in c/a ratio.

(2) The Grüneisen γ computed from an averaging of the mode γ 's, as derived from the hydrostatic pressure derivatives of the elastic moduli, can be widely different than the γ computed from thermal expansion data when the dC_{ij}/dP contain significant contributions from the changes in axial ratio and when the volume dependence of the axial ratio, or ratios, during hydrostatic compression differs from that during thermal expansion. This indicates that the high frequency thermal vibrations are also sensitive to changes in axial ratio with thermal expansion.

(3) A correlation of the quantitative effect of (c/a) on C_{44} and C_{66} for Ti and Zr with theoretical calculations for the strain energy contributions to h.c.p. crystals[28] indicates that $dC_{44}/d(c/a)$ is derived primarily from electrostatic forces whereas $dC_{66}/d(c/a)$ probably arises for electron transfer during Fermi surface distortion.

(4) The equations of state at very high pressures, predicted from the pressure derivatives of the bulk moduli of Ti and Zr at lower pressure, do not agree with the equations of state derived from shock-wave experiments for these two metals.

Acknowledgements—The authors are indebted to Mr. D. Dever for assistance in crystal preparation and to Dr. D. Gerlich for the 'Gammacal' computer program. Part of this work was carried out under auspices of the U.S. Atomic Energy Commission.

REFERENCES

1. FISHER E. S., MANGHNANI M. H. and SOKOLOWSKI T. J., *J. appl. Phys.* **41**, 2991 (1970).
2. GERLICH D., *J. Phys. Chem. Solids* **30**, 1638 (1969).
3. FISHER E. S. and RENKEN C. J., *Phys. Rev.* **135**, A482 (1964).
4. McSKIMIN H. J., *J. Acoust. Soc. Am.* **33**, 12 (1961).
5. GOLDAK J. and LLOYD L. T., unpublished measurements of thermal expansion in Ti single crystals, private communication from L. T. Lloyd, Argonne National Lab. (Argonne, Ill.)
6. HILL R., *Proc. Phys. Soc. Lond.* **A65**, 349 (1952).
7. ANDERSON O. L., *J. Phys. Chem. Solids* **27**, 547 (1966).
8. MURNAGHAN F. D., "Finite Deformation of an Elastic Solid," p. 68 John Wiley, New York (1951).
9. OVERTON W. C., Jr., *J. Chem. Phys.* **37**, 116 (1962).
10. BRIDGMAN P. W., *Proc. Am. Acad. Arts Sci.* **76**, 55 (1958).
11. WALSH J. M., RICE M. H., McQUEEN R. G. and YARGER F. L., *Phys. Rev.* **108**, 196 (1957).
12. JAMESON J. C. *Science* **140**, 72 (1963).
13. FISHER E. S., MANGHNANI M. H., BENZING W. M. and GOODMAN G., *Proc. Int. Colloquium on Phys. Properties of Solids at High Pressures*, Grenoble (Sept. 8, 1969), C.N.R.S., Paris. (1970).
14. SCHMUNK R. E. and SMITH C. S., *J. Phys. Chem. Solids* **9**, 100 (1959).
15. CORLL J. A., *ONR Tech. Rep.* # 6 (1962).
16. DANIELS W. B. and SMITH C. S., *Phys. Rev.* **111**, 713 (1958).
17. SCHUELE D. E. and SMITH C. S., *J. Phys. Chem. Solids* **25**, 80 (1964).
18. McCAMMON R. D. and WHITE G. K., *Phil. Mag.* **11**, 1125 (1965).
19. COWAN J. A., PAWLOWICZ A. T. and WHITE G. K., *Cryogenics* **8**, 155 (1968).
20. GOLDAK J., LLOYD L. T. and BARRETT C. S., *Phys. Rev.* **144**, 478 (1966).
21. SLUTSKY L. J. and GARLAND C. W., *Phys. Rev.* **107**, 972 (1957).
22. CHANG Y. A. and HIMMEL L., *J. appl. Phys.* **37**, 3787 (1966).
23. RUSSELL R. B., *Trans. AIME* **200**, 1045 (1954).
24. WILLENS R. H., *Rev. Scient Instrum.* **33**, 1069 (1962).
25. LEIGH R. S., *Phil. Mag.* [7] **42**, 139 (1951).
26. REITZ J. R. and SMITH C. S., *Phys. Rev.* **104**, 1253 (1956).
27. HUNTINGTON H. B., *Phys. Rev.* **57**, 60 (1940).
28. COUSINS C. S. G., *J. Phys. C. (Proc. Phys. Soc.)* **1**, 478 (1968).
29. FISCHER O., PETER M. and STEINEMANN S., *Helv. Phys. Acta* **42**, 459 (1969).