Structural Transformations of Some Clay Minerals Under Pressure in Hydrothermal Conditions

by V. A. Frank-Kamenetzky, N. V. Kotov, E. A. Goilo and G. N. Klotchkova

With complined

Mineral, Soc. Japan. Spec. Pap. 1, 88~97 (1971) [Proc. IMA-IAGOD Meetings '70, IMA Vol.

Department of Crystallography and Lab. of High Pressure. The Leningrad State University, Leningrad B-164, USSR

Abstract

Systematical investigations of the alteration of clay minerals under hydrothermal conditions and the discovery of phases and structural relations of minerals of kaolinite group, monitorillonoids, mixed-layered silicates etc., are of great interest.

In the presence of K. Na chlorides (P=900 kg/cm², T to 500 C, 22+75 hr) kaolinite, dickite and metahalloysite are decomposed to form dioctahedral hydromicas, which are formed through the intermediate disordered micd-montmorillonite mixed-layered formations.

Polytypic modifications of newly formed micas depend upon the structure of the initial materials from kaolinite, mica IM prevails; from dickite-mica 2M₃; as from metahallovsite disordered mica.

Under the same conditions, in the presence of Ca chlorides, knotning group transforms through the intermediate phases to rectorite and mono-layered hexagonal analog of anortite, and with Mg to tosudite.

The transformations of the dioctahedral monimorillonies depend upon the concentration of the charges in octahedral and tetrahedral positions. From beidellite in the presence of K. Na. Ca. Mg chiorides the same phases as from kaoliniae are formed, but under considerably lower temperatures. In the presence of K.Cl. dioctahedral montmovillonite transforms through a whole spectra of disordered mice-montmorillonite phases to hydromica and sandine, and with Na and Ca chlorides to trioctahedral montmorillonite and plagioclase. In the presence of MgCl. trioctahedral montmorillonite, are formed after dioctahedral, and if the duration of treatment is longer. It transforms into tale-montmorillonite mixed-layered phase.

Sepiolite is decomposed (P=800-2000 kg/cm², T=325°, 22-140 hr) and substituted by Mg-mont-morillonite; palygorskite under the same conditions is substituted by monthrorillonite, then (~500°) by mixed-layered montmorillonite-chlorite, and then by chlorite (<600°) and cordierite+talc (>600°).

In the presence of Ca Mg chlorides (P=1000 kg/cm², 22 hr.) the lowest temperatures of decom-

Regime of X-ray investigation, CuKo: Ni-filtr 35 kv, 24 mA; 12, 1200; RC = 1-2 sec.

position of sepiolite and palygorskite—are marked (~250~100°). From sepiolite in the presence of Cachorides Mg montmorillonite—tale+Ca-amphibole are formed; with MgCl₂-Mg montmorillonite—tale+pyroxene. From palygorskite with CaCl₂ di- and triocchedical montmorillonite are formed and then tale+anortite (T>450°C).

In the presence of mixture of Na, Ca Mg chlorides (P=1000 kg/cm², 22 hr) sepiolite transforms to Mg monimorillonite and/paygor(kite (~250°)) and to di- and trioctahedral monimorillonite (~300°); Purther, under T=400-450° tale is formed after sepiolite and plagioclase, chlorite+tale after paygorskite.

The character of the newly-tormed phases in the majority of experiments depends on the contents of the original material and upon the type of the mineralizer added, but their structure is defined to the great extent by the structural peculiarities of the initial materials, which are inactited in the process of solid state transformational reactions with the participation of the vapour phase.

Introduction

In the pre-ent article are compared the essential features of structural succession that are typical for structural-typomosphous? alteration under hydrother-mal conditions of kaolitine group (kandites, montmorial-tonoids, smektites) and layer-ribbon silicates—sepiolites and palygorskites.

As initial materials, the followings were used: kaolinite from Prosjanovsk deposit, USSR, metahalloysite from Micalovec deposit, CzSSR, dickite from Turomginsk deposit, USSR, sepiolite from Karamasar, USSR and palygorskite from Pamir, USSR, The samples were held under constant P41,0=1-2 kb. T=200-650 C conditions in a reactor with a cold lick (Tuttle apparatus type") in the presence of pure water or in mixture with chlorides of K. Na. Ca. Mg in ratio 2:1 in sealed ampoules; then they were tempered. Some experiments were carried out under stress by means of an anvil, designed by Bridgman.3 . and under quasihydrothermal pressure in a cylinderpiston type apparatus. The structural characteristics of newly formed materials were determined mainly by means of X-ray diffractometry.

OCT 25 1973

The Inheritance of the Structural Motive

The transformations of kaolinite under hydrothermal conditions in the presence of K. Na. Ca. Mg chlorides (Fig. 1) show that the intermediate and final new phases are in general layered silicates and aluminosilicates with similar basis of structure. Even if the samples are treated for 72 hrs at temperatures 200-500 C non-layered phases (zeolites, feldspars, etc.) that are formed under similar conditions from glasses and gels. Were not formed. Only under higher temperature stability region than that of kaolinite (T > 475° C. 3-22 hrs), an admixture of andalusite-like phase was formed.

The specification of synthesized phases is as follows, in different combinations of tetrahedral and octahedral nets with a formation of 2,3,4, and manylayered structures. On the diffractogramms of all layered phase which take a part in reactions, this can be seen in the conservation of the position of reflections hkO (h, k-0; f, 2, 3.1. ; h, k, h+k-even) and in essential alteration of the position of reflections 001 and hkl (for example-the experiments with KCl and CaCL—(Figs. 2, 3). Small variations of parameter h (Ab±0.06 Å), that is fixed by changing of maximum 060, show that the movement of structure in the basal plane is insignificantly small. It is interesting to compare the sequenses of formation of new phases, between the system in which kaolinite minerals were treated under hydrothermal conditions with addition of CaCl, and the system in which glasses and gels of analogous composition were used as initial materials. In the first system two main phases are formed: a swelling one-14 A and non-swelling-7A (Fig. 3). The swelling phase, that was examined by X-ray with different treatments, appeared to be montmorillonite (possibly with tetrahedral Al). As the duration of treatment increases and as temperature of synthesis increases up to 400-500 C, this phase is transformed (Fig. 3) into ordered mixed-layered phase, like micamontmorillonite. The 7A phase was examined by electronomicrography and identified to be mono-layered hexagonal analog of anorthe: it appears at T=300-500 C in 22 hrs. (Fig. 3) and after the treatment for

Fig. 1: a Phases formed from knownie (A), palygorskie (B) and sepiolite (C) under hydrothermal conditions with additions of chlorides (P_{H2}O=1 khur, 200-500 C, 22-44) hours.

Symbols: f) ordered kaolinite (Kt. 2) disordered kaolinite; 3) diociahedral monthorillonite (Mt), 4) triociahedral montmorillonite (Mt), 6) Noi-hedral montmorillonite. 5) K-hedronica (HM), 6) Noi-hedronica (HM), 7) rectoric (Rt. 8) toxialite (Lt. 9) hexagonal analogue of anothic (At. 10) random interstratification of eldorite and montmorillonite: 11) random interstratification of eldorite and montmorillonite (LT) take (LT) tremolite: 14) Slogi (LT) admixtures (X-andalustie in experiments with kaolinite: quartz+biofite+ka-feldspar/with Kl. nepheline+ablite/with Nat. quartz+anottie+cordicrite/with (Lt.), take-quartz, with Mg.—in experiments with palygorskite). Borders, and fields of phase distribilitions on X-ray dista.

70 hours at T 500°C is transformed into two-layered anortite phase. The formation of two-layered phase of anortite composition was reported under similar conditions¹¹ from glasses and gels at T 350°C; at higher temperature crystalline anortite is formed and swelling phases did not appear. Therefore, in the transformations of kaolinite, the metastable layered phases of anortite composition occur at 400-500°C; under the same conditions the stable anortite is formed from gels and glasses of similar composition.¹²

In spite of the similarity of chemical composition

