

- 3 -

transus and is classified as a beta stabilizer in that system.

Magnesium is soluble in solid titanium to the extent of at least 1.5% in both the alpha and beta phases. No intermetallic compounds or magnesium rich phases were observed either by light microscopy or x-ray diffraction. However, this does not negate the possibility that such phases exist at higher alloy concentrations.

JWF/bfc