

(v) The γ_i 's calculated from dv_i/dP are higher than those for α -quartz and high-silica glasses, reflecting the increase in ionic character of the glasses as the Na_2O content increases.

(vi) As the Na_2O content is increased in the sodium glasses, the value of γ_{HT} increases significantly, correlating with an absence of negative thermal expansion in these glasses.

ACKNOWLEDGMENT

The authors are grateful to G.W. Cleek, National Bureau of Standards and J.R. Sweet, The Pennsylvania State University, for providing the glass specimens. They thank E.S. Fisher, Argonne National Laboratory, for the critical reading of the manuscript and for his many helpful suggestions. One of the authors (M. H. M.) gratefully acknowledges the support for this work by the Office of Naval Research (Contract N00014-67-A-0387-0012, NR 032-527). Hawaii Institute of Geophysics Contribution No. 465.

*Based on work performed under the auspices of the U. S. Atomic Energy Commission.

¹R. J. Charles, *Progress in Ceramic Science* (Pergamon, New York, 1961), Vol. I.

²M. H. Manghnani (unpublished).

³R. Hanna, *J. Phys. Chem.* **69**, 3846 (1965).

⁴R. Hanna and G.-J. Su, *J. Amer. Ceram. Soc.* **47**, 597 (1964).

⁵D. Crozier and R. W. Douglas, *Phys. Chem. Glasses* **6**, 240 (1965).

⁶J. R. Sweet and W. B. White, *Phys. Chem. Glasses* **10**, 246 (1969).

⁷P. E. Jellyman and J. P. Proctor, *J. Soc. Glass Technol.* **39**, 173 (1955).

⁸V. A. Florinskaya, *The Structure of Glass* (Consultants Bureau, New York, 1960), p. 154.

⁹I. Simon and H. O. McMahon, *J. Amer. Ceram. Soc.* **36**, 160 (1953).

¹⁰J. R. Ferraro and M. H. Manghnani, *J. Phys. Chem. Glasses* (to be published).

¹¹J. R. Ferraro, S. S. Mitra, and C. Postmus, *Inorg. Nucl. Chem. Lett.* **2**, 269 (1966).

¹²C. Postmus, S. S. Mitra, and J. R. Ferraro, *Inorg. Nucl. Chem. Lett.* **4**, 55 (1966).

¹³N. F. Borrelli and G.-J. Su, *Mater. Res. Bull.* **3**, 181 (1968).

¹⁴E. R. Lippincott, R. Van Valkenburg, A. Wier, and C. E. Bunting, *J. Res. Nat. Bur. Stand.* **61**, 61 (1958).

¹⁵R. J. Bell, M. E. Bird, and P. Dean, *Proc. Phys. Soc. Lond.* **1**, 299 (1968).

¹⁶P. H. Gaskell, *Phys. Chem. Glasses* **8**, 69 (1967).

¹⁷J. Bock and G.-J. Su, *J. Amer. Ceram. Soc.* **53**, 69 (1970).

¹⁸M. Blackman, *Proc. Phys. Soc. Lond.* **70**, 827 (1957).

¹⁹A. Bienenstock and G. Burley, *J. Phys. Chem. Solids* **24**, 1271 (1963).

²⁰H. T. Smyth, *J. Amer. Ceram. Soc.* **42**, 276 (1959).

²¹J. Zarzycki, *Chemical and Mechanical Behavior of Inorganic Materials* edited by A. W. Searcy, D. V. Ragone, and V. Columbo (Interscience, New York, 1970), pp. 443-474.

²²B. E. Warren, *J. Appl. Phys.* **8**, 645 (1937).

²³O. L. Anderson and G. J. Dienes, *Noncrystalline Solids* (Wiley, New York, 1960), p. 449.

²⁴G. K. White, *Cryogenics* **4**, 2 (1964).

²⁵T. H. K. Barron, *Phil. Mag.* **46**, 720 (1955).

²⁶D. E. Schuele and C. S. Smith, *J. Phys. Chem. Solids* **25**, 801 (1964).