



Fig. 1. Axonometric projections of crystalline phases synthesized in  $\text{BaO}-\text{SiO}_2-\text{H}_2\text{O}$  system. a)  $5\text{BaO} \cdot 4\text{SiO}_2 \cdot 1.2\text{H}_2\text{O}$  (phase A); b) phase B; c)  $\text{BaSi}_2\text{O}_5$ ; d)  $\text{Ba}_2\text{Si}_3\text{O}_8$ ;  $\text{P}2_1/\text{b}$  orientation.

**Phase C.** Composition unknown; thin, transparent acicular crystals.

$\text{BaSi}_2\text{O}_5$ . Occurs in nature as the mineral sambornite; colorless, transparent tabular crystals. Figure 1b shows the axonometric projection of a  $\text{BaSi}_2\text{O}_5$  crystal using the same orientation as Douglass [9]. Faces defined by well-developed  $\{001\}$  pinacoid, which must be considered to result from a laminar structure with  $[\text{Si}_4\text{O}_{10}]_{\infty}$  networks parallel to the  $(001)$  face [9]. A subordinate role is played by  $\{012\}$ ,  $\{110\}$ ,  $\{103\}$ , and  $\{105\}$  rhombic prisms and a second pinacoid.

$\text{Ba}_2\text{Si}_3\text{O}_8$ . Composition established from data in literature [13, 14]. Monoclinic system. Lattice constants:  $a = 12.476 \pm 0.004$ ,  $c = 13.962 \pm 0.005$ ,  $b = 4.688 \pm 0.003 \text{ \AA}$ ,  $\beta = 93^\circ 37' \pm 3'$ ;  $Z = 4$ . Fedorov group  $C_{2h}^5 = \text{P}2_1/c$ . Flat rhomboid crystals. External faceting defined by combinations of many rhombic prisms ( $\{122\}$ ,  $\{\bar{1}\bar{2}2\}$ ,  $\{011\}$ ,  $\{021\}$ ,  $\{012\}$ ,  $\{031\}$ ,  $\{051\}$ ,  $\{056\}$ , and  $\{456\}$ );  $\{010\}$  pinacoid not observed in all crystals (Fig. 1d).

The authors wish to take this opportunity to thank T. I. Ivanova for making the optical measurements and determining the density of phase A.

#### LITERATURE CITED

1. N. A. Moshchanskii, Author's Abstract of Doctoral Dissertation [in Russian], TsNIPS, Moscow (1953).
2. H. F. Taylor, 4th International Congress on Cement Chemistry [in Russian], Stroizdat, Moscow (1964), pp. 159-200.
3. H. Funk, Z. Anorgan. Allgem. Chem., 296, 46 (1958).
4. E. M. Levin and G. M. Ugrinc, J. Res. Nat. Bur. Standards, 51, 37-56 (1953).
5. W. Wahl, Z. Kristallogr., Mineralog., Petrogr., 36, 156 (1902).
6. G. W. Krueger and W. Wieker, Z. Anorgan. Allgem. Chem., 340, No. 5-6, 277 (1965).
7. B. N. Litvin, Dissertation [in Russian], Inst. Kristallogr., Akad. Nauk SSSR, Moscow (1964).
8. H. Remy, Treatise on Inorganic Chemistry, American Elsevier, New York.
9. R. M. Douglass, Amer. Mineralogist, 43, 517 (1958).
10. A. N. Lazarev, F. F. Tenisheva, and R. G. Grebenchikov, Dokl. Akad. Nauk SSSR, 140, 811 (1961) [Sov. Phys. — Dokl., 6, 847 (1962)].
11. W. Hilmer, Kristallografiya, 7, 704 (1962) [Sov. Phys. — Crystallogr., 7, 573 (1963)].
12. J. T. Alfors, M. C. Stinson, R. A. Matthews, and A. Pabst, Amer. Mineralogist, 50, 314 (1965).
13. H. Katscher and F. Lieban, Naturwissenschaften, 52, No. 18, 512 (1965).
14. R. S. Roth and E. M. Levin, J. Res. Nat. Bur. Standards, 62, 193 (1959).