

on. For example, it can be shown that the nominal residual hoop stress at the liner bore at Point X in Figure 3 would be 1/2 the value normally achieved entirely under the shrink-ring. (An analysis of this is given in Reference (2)). This is assumed to apply to the type of shrink rings shown in Figure 2 as well. Thus, it is concluded that a side-bore container with such "partial" shrink-rings, compared to a straight-bore container with the same number but "whole" shrink-rings, will have a pressure capability less than that given by Equation (11).

To avoid difficulties associated with shrink-rings on a side-bore liner, an autofrettaged monoblock design of a side-bore container is considered. If the wall ratio could be made sufficiently large, and an autofrettage residual stress of sufficient magnitude could be achieved, then Equation (11) may apply for p = pressure capability of an autofrettaged straight cylinder. For example, pressures, p , up to 290,000 psi have been applied many times to a monoblock autofrettaged cylinder of 285,000 psi ultimate tensile strength as reported by Thomas, Turner, and Wall⁽²⁾. The cylinder had an overall wall ratio of $K = 7.2$.

Before autofrettage can be recommended with confidence for side-bore cylinders, experiments should be conducted to determine if the same benefit is achieved as achieved in straight-bore cylinders. It is well to point out here that autofrettaged cylinders are weaker in fatigue than are shrink-fitted cylinders⁽²⁾ but an autofrettaged monoblock may be easier to replace than a liner of a shrink-fitted container.

Clearly, there are many unknowns in the design of side-bore containers. Even in the design of straight-bore containers much remains to be learned about such factors as fatigue properties of high-strength steel cylinders under cyclic internal pressures and the autofrettaging capabilities of high-strength steels. However, because relatively low fluid pressures of about 150,000 psi will be required for the HYDRAW of titanium tubing, the use of a side-bore container is a distinct possibility and would be eminently desirable from a materials handling standpoint. Consequently, studies are soon to be conducted on geometrically similar plastic models to determine the stress-concentration factor at the critical tee-intersection. This will be done by measuring the strains under pressure indicated by suitably positioned strain gauges. Pressures of only a few hundred psi would be required. The variation of stress-concentration factor with wall ratio will be investigated. The model will be designed with an optimum side-bore to through-bore diameter ratio of one, and with a tee-intersection-radius to bore-radius ratio of one.

REFERENCES

- (1) Fiorentino, R. J., Richardson, B. D., Meyer, G. E., Sabroff, A. M., Boulger, F. W., "Development of the Manufacturing Capabilities of the Hydrostatic Extrusion Process", Technical Report AFML-TR-6, Contract No. AF 33(615)-1390, October 1967.
- (2) Meyer, G. E., Simonen, F. A., Gerdeen, J. C., Fiorentino, R. J., Sabroff, A. M., "Design Study of a Production Press for Ultrahigh-Pressure Hydrostatic Extrusion", Final Report, Contract No. F 33615-67-C-1434, to be issued March 1968.
- (3) Thomas, S. L. S., Turner, H. S., and Wall, W. F., "Piston-Cylinder High Pressure Apparatus for Use up to 25 kb", Paper No. 11, Institution of Mechanical Engineers, High Pressure Engineering Conference, London, September 11-15, 1967.