

a pressure-temperature diagram as shown in Fig.2. When the product was a mixture of the two phases, their relative quantity was estimated from the intensities of powder diffraction peaks. From the figure, the equilibrium phase boundary can be expressed in terms of the equation;  $P(\text{kbar})=26.7+0.026_5T(^{\circ}\text{C})$ .

Considerations: The pressure induced phase transition of ABO<sub>4</sub> compounds has been examined by several researchers(7,8,9, 10). Among them, Nicol and Durana(1) claimed through their high pressure Raman spectra measurements that CaWO<sub>4</sub> and CaMoO<sub>4</sub> transformed reversibly to a high pressure form at about 20kbars which was of similar structure to wolframite. On the other hand, Sleight(2) showed that the quenched specimens of CaWO<sub>4</sub>, CdWO<sub>4</sub>, CaMoO<sub>4</sub> and CdMoO<sub>4</sub> did not reveal any high pressure form. It was therefore considered that these wolframite-like high pressure phases are not quenchable. In comparison with those observations, it is interesting to note that the high pressure forms are obtained in quenched products for PbWO<sub>4</sub>(3) and BaWO<sub>4</sub> where the A-cations are relatively large. As Fig.2 shows, the  $dP/dT$  is positive in the transformation of BaWO<sub>4</sub>-I to BaWO<sub>4</sub>-II. This is similar to the behaviors of the high pressure form of PbWO<sub>4</sub>.

In the BaWO<sub>4</sub>-I → BaWO<sub>4</sub>-II transformation, the volume of the unit cell decreases by 12.1% of the I-form( the cell volume of the II-form is normalized to a four formula unit cell). If the transformation is of a scheelite → wolframite structure, no change in the average coordination number may result in much smaller volume decrease. Shannon and Prewitt(11) discussed an empirical tendency that a larger decrease of cell volume is associated with an increase of coordination number. In fact, the present case, the decrease amounting to 12.1% is associated with an increase in the average coordination number in the high pressure phase.

#### Acknowledgements

We are very grateful to Dr. I.Kawada of this Institute, for X-ray analysis suggestions. We also indebted to Mr. H.Ohashi and Mr. M.Saeki for their helpful comments.

References

1. M. Nicol and J. F. Durana, J. Chem. Phys. 54, 1436, (1971)
2. A. W. Sleight, Acta Cryst. B28, 2899, (1972)
3. L. L. Y. Chang, J. Amer. Ceram. Soc. 54, 357, (1971)
4. O. Fukunaga, K. Takahashi, T. Fujita and J. Yoshimoto, Mat. Res. Bull. 4, 315, (1969)
5. "Proceedings of the Symposium on Accurate Characterization of the High Pressure Environment", N.B.S., Gaithersburg, Oct. (1968)
6. ASTM card No.14-674
7. V. S. Stubician and R. Roy, Z. Krist. 119, 90, (1963)
8. A. W. Sleight and B. L. Chamberland, Inorg. Chem. 8, 1672, (1968)
9. S. Tamura, Solid State Commun. 12, 597, (1973)
10. S. Tamura, K. Hirota and M. Wakakuwa, 15th High Pressure Conference of Japan, Fukuoka, Oct. (1973)
11. R. D. Shannon and C. T. Prewitt, Mat. Res. Bull. 4, 57, (1969)