



FIG. 2. Relative optical density vs. temperature showing NaCl to zincblende phase transformation.

they able to measure the absorption edge beyond the transition. We experienced the same difficulty with our thicker samples, and found that the loss of light was due to the NaCl phase being in a powder form. In some of the 6.0 mil samples, the edge was very broad. The short wavelength end of the edge would remain the same regardless of whether the samples were powdered or single crystal, but the long wavelength end of the edge would shift to longer wavelengths as the crystal progressed from a pure single crystal to a powder. Their edge was measured at an attenuation coefficient of 64 cm^{-1} so the reported edge would be shifted to a longer wavelength and thus the value of E_g would be low. The error of E_g determined at an attenuation coefficient of 64 cm^{-1} would be progressively worse as the absorption edge was broadened.

Samara and Giardini's determination of $E_g = 1.3 \text{ eV}$ is based on the assumption that the crystal is in the intrinsic conductivity range ($550\text{--}800^\circ\text{C}$) and that the mobility is constant. There is a question whether the crystal is really in the intrinsic region at this temperature. If it is not, the

measured value of E_g would be the activation energy of one of the donor levels and would be less than the true E_g . We feel that their value of E_g is not the fundamental band gap but of some deep trapping level.

The annealing temperature of the NaCl to zincblende phase is directly proportional to the amount of strain in the recovered samples, as would be expected. This is also in agreement with CORLL's work⁽³⁾ in which the recovered NaCl structure was heavily strained and annealed at 150° or higher temperatures.

REFERENCES

1. EDWARDS A. L., SLYKHOUSE I. E. and DRICKAMER H. G., *J. Phys. Chem. Solids* 2, 140 (1959).
2. KALBALKINA S. S. and TROITSKAYA Z. V., *Soviet Phys. Dokl.* 8, 800 (1964).
3. CORLL J. A., *J. appl. Phys.* 35, 3032 (1964).
4. SAMARA G. A. and GIARDINI A. A., *Phys. Rev.* 140, A388 (1964).
5. *Modern Very High Pressure Techniques*, pp. 25-29, edited by R. H. WENTORF, JR. Butterworths (1962).

while other areas were
ed light.
re of the NaCl struc-
as measured optically
eter. The sample was
hich had a Rosemont
stance thermometer
as placed in a quartz
armed at a slow rate.
gh the crystal and the
re was recorded. The
ase is a fine powder
nsion associated with
optically dense. The
by the increase in
1.4.0 mil samples are
k sample was trans-
 $0 \pm 5^\circ\text{K}$.

blende to wurtzite
 $\frac{1}{2}$ hour at 375° . At
ansformation takes

studies on the high
when the starting
covered sample was
of 4.0 to 10.0 mil
, and crystal thick-
d large regions of

Measurements (Fig. 1)
was so thin, i.e.
t it was necessary
of the salt pellet.
ints at the high
to the crystal-salt
reported value of
tion edge of the
he corresponding
e crystal gives
is not in agree-
ues of 1.3 eV by
eV by EDWARDS,
Edwards, Slyk-
the shift of the
= 1.7 eV for the
ansformation at
n a loss of most
two runs" were