

TABLE I
X-RAY POWDER DIFFRACTION PATTERN OF TETRAGONAL
SnP ($a = 3.831 \pm 0.001 \text{ \AA}$, $c = 5.963 \pm 0.001 \text{ \AA}$)

$1/\sin^2 \theta$	h	k	l	d (obs.)	d (calc.)
90	1	0	1	3.2189	3.2226
100	0	0	2	2.9784	2.9610
90	1	1	0	2.7105	2.7084
90	1	1	2	2.0030	2.0046
80	2	0	0	1.9151	1.9152
70	1	0	3	1.7625	1.7640
80	2	1	1	1.6458	1.6464
70	2	0	2	1.6103	1.6113
20	0	0	4	1.4921	1.4905
30	2	2	0	1.3545	1.3542
30	1	1	4	1.3068	1.3056
10	3	1	2	1.2972	1.2975
10	3	0	1	1.2473	1.2485
30	2	2	2	1.2332	1.2310
40	3	1	0	1.2111	1.2113
20	2	0	4	1.1756	1.1762
10	1	0	5	1.1361	1.1365
40	3	1	2	1.1224	1.1221
10	3	0	3	1.0744	1.0742
10	3	2	1	1.0462	1.0459
10	2	2	4	1.0018	1.0023
20	2	1	5	.9784	.9786
10	4	0	0	.9577	.9576
10	3	1	4	.9406	.9403
10	3	2	3	.9376	.9376
5	4	1	1	.9186	.9179
10	4	0	2	.9123	.9117
10	3	3	0	.9026	.9026
2	2	0	6	.8816	.8820
5	3	0	5	.8715	.8714
10	3	3	2	.8645	.8643
10	4	2	0	.8509	.8505
10	4	1	3	.8422	.8416
10	1	0	7	.8316	.8314
10	4	2	2	.8231	.8234
5	3	2	5	.7930	.7932

*Head using the David Mann Film Reader.

TABLE II
 I_0 AND I_c FOR TETRAGONAL SnP

h	k	l	I_0	I_c
1	0	1		47.36
-1	0	-1		44.06
			100.00	91.43
0	0	2		20.93
0	0	-2		22.13
			36.95	43.07
1	1	0		74.84
1	1	2		25.67
-1	-1	-2		27.16
			55.41	52.83
2	0	0		25.77
1	0	3		13.19
-1	0	-3		11.95
			21.70	25.14
2	1	1		14.25
-2	-1	-1		13.36
			25.70	27.61
2	0	2		12.41
-2	0	-2		13.16
			27.71	25.57
0	0	4		1.68
0	0	-4		1.86
			3.99	3.54
2	2	0		7.76
1	3	0		10.45
1	2	3		9.32
-1	-2	-3		8.41
1	1	4		4.26
-1	-1	-4		4.72
			25.60	26.71
3	0	1		2.90
-3	0	-1		2.72
			6.50	5.61
2	0	4		3.01
-2	0	-4		3.34
			6.10	6.35

No. IDF4, cut out, and weighed. Fourteen pieces of data were collected.

Least-squares refinement based on the function $\sum w I_0 - I_c^2$ was done using a program written by

TABLE III
FINAL PARAMETERS AND BOND DISTANCES AND ANGLES
FOR TETRAGONAL SnP

Atom	Position (x, y, z)	Temp factor, \AA^2
Sn	0, 0, 0	0.9 ± 0.3
P	0, 0, 0.428 ± 0.010	2.6 ± 1.6

Atoms*	Dist, \AA	Atoms	Angles, deg
Sn(1)-P(2)	2.55 ± 0.06	P(3)-Sn(1)-P(2)	99.0 ± 1.2
Sn(1)-P(3)	2.74 ± 0.01	P(3)-Sn(1)-P(4)	81.0 ± 1.2
Sn(1)-P(4)	3.41 ± 0.06	P(5)-Sn(1)-P(3)	88.6 ± 0.4

* The numbers on the atoms correspond to the numbers of the atoms in Figure 1.

Prewitt¹⁰ which handles the sums of nonequivalent overlapping reflections. Atomic scattering factors¹¹ corrected for the real and imaginary parts of the anomalous dispersion were used. The imaginary component was applied separately to reflections hkl and $\bar{h}kl$. Occupancy factors were held at 2 and the weighting scheme $w = 1/\sigma^2$, with $\sigma = \sqrt{I_0} + 2.0$, was used. The positions 0, 0, z of space group $I4mm$ were used in the refinement with z held at 0.0 for Sn and $z = 0.4$ initially assumed for P.

One scale factor, the single position parameter for P, and two isotropic temperature factors were varied. The R factor defined as $R = \sum I_0 - I_c / \sum I_0$ was reduced to 7.8%. The intensity data and final position parameters are shown in Table II. Bond distances were calculated¹² (Table III). The numbers of the atoms correspond to those in Figure 1.




Figure 1.—Structure of SnP.

The cubic structure was shown to be NaCl type. Intensities were read from a Debye-Scherrer pattern using the David Mann film reader. These were compared to the Debye-Scherrer patterns calculated for SnP having the NaCl-type and ZnS-type structures by a program written by Jeitschko and Parthé.¹³ The results (Table IV) clearly indicate the NaCl-type structure to be correct. The pattern is similar to that reported by Osugi, *et al.*,⁴ to be sphalerite type.

(10) C. T. Prewitt, local unpublished computer program.

(11) "International Tables for X-Ray Crystallography," Vol. III, The Kynoch Press, Birmingham, England, 1962, pp 202 and 213, Tables 3.3.1A and 3.3.2A.

(12) L. W. Finger, "University of Minnesota Program for Computing Bond Angles and Distances with Error and Analysis," UMRADTEA, 1965.

(13) W. K. Jeitschko and E. Parthé, unpublished computer program for calculation of X-ray powder diffraction patterns.