



Fig. 5. Depression of the superconducting transition temperature in LaCe alloys under pressure. Numbers denote cerium concentrations. Samples with 1 and 1.5% Ce (this work) were fcc, those of Maple *et al.*⁷ "as cast"

remarkable agreement with the theoretical value of 6.05 K, obtained from the formula of Müller-Hartmann and Zittartz⁴

$$\Delta T_{c \max} = -\frac{c}{8k_B N(0)}$$

with $N(0) = 2.4 \text{ eV}^{-1}$ ⁽⁸⁾. Also the dependence on concentration c is qualitatively obeyed. We wish to mention here that the results of Fig. 1 and 4, according to which $T_k = 4 \text{ K}$ and $T_{c0} = 7.7 \text{ K}$ at 14 kbar, i.e. $\vartheta \approx 0.5$ for maximum pair breaking are inconsistent with the theoretical predictions of $\vartheta \approx 2$ (Zuckermann³) and $\vartheta \approx 12$ (Müller-Hartmann and Zittartz⁴). It must be recalled, however, that the theoretical results hold for very low concentrations only, whereas at 14 kbar the concentration of 1% Ce is close to the critical concentration at which the order parameter vanishes. Here it is noteworthy that, according to a theory of Coqblin and Schrieffer¹², Ce alloys cannot be described exactly by the Hamiltonian $H = JS \cdot \sigma$ because of the strong spin-orbit interaction of the $4f$ state. Taking this into account, but using the Born approximation only, they obtain for the decrease of T_c nearly the same result as Eq. (3).

¹² Coqblin, B., Schrieffer, J. R.: Phys. Rev. 185, 847 (1969).

To our knowledge the influence of resonance scattering on T_c has not been calculated with this Coqblin-Schrieffer Hamiltonian.

In conclusion, both the maximum in the depression of T_c and the results on the Kondo anomaly under pressure can be reasonably well correlated within existing theories, whereas no details, either experimental or theoretical, are known on the magnetic-nonmagnetic transition of the cerium ion in lanthanum lattices. While the results on the slopes of the R versus $\ln T$ curves may not fully permit an unambiguous decision between both ways of interpretation, there is strong evidence from the continuous increase of the resistance in the pressure regime above 14 kbar that the maximum in pair breaking does not characterize the magnetic transition.

We wish to thank Dr. H. U. Everts, Prof. Dr. P. Fulde and Prof. Dr. W. Götze for many informative discussions.

Dr. Edgar Umlauf
Zentralinstitut für Tieftemperaturforschung
der Bayerischen Akademie der Wissenschaften
BRD-8046 Garching, Hochschulgelände
Deutschland

Univ.-Doz. Dr. Wolfgang Gey
Physikalisches Institut
der Universität Karlsruhe
BRD-7500 Karlsruhe, Engesserstr. 7
Deutschland