

From these data we obtain:

$$\tau \cdot \Delta(1/\tau) = 6 \cdot 10^{-3},$$

$$\text{La}_{0.994}\text{Tb}_{0.006}\text{Al}_2$$

$$T_c = 2.130 \text{ K}; \quad Z = 0.35; \quad \Delta T_c = -0.145 \text{ K};$$

$$\left( T_c/T_{c0} - x \frac{\partial(T_c/T_{c0})}{\partial x} \right) \cdot \Delta T_{c0} = +4 \text{ mK};$$

$$x \frac{\partial T_c}{\partial x} \cdot \tau \Delta(1/\tau) = 7 \text{ mK}.$$

In the table we have listed our theoretical result of  $T_c/T_{c0}$  and  $T_c - T_{c0}$  for  $\text{La}_{0.994}\text{Tb}_{0.006}\text{Al}_2$  for two values of the groundstate separation and different values of the LLW parameter  $X_L$ . The experimentally determined value of 11 mK for the first two terms of the r.h.s. of Eq. (10) has been added. These results have to be compared with the experimental values of  $T_c/T_{c0} = 0.650$  and  $\Delta T_c - \Delta T_{c0} = 29 \text{ mK}$ . It can be noticed that for a large number of level schemes, characterized by the parameter  $X_L$ , both the experimental values of  $T_c/T_{c0}$  and  $\Delta T_c - \Delta T_{c0}$  are in agreement with the assumption of a groundstate separation

Table 1. Calculated values of  $T_c/T_{c0}$  and  $\Delta T_c - \Delta T_{c0}$  at 10 kbar for two values of the ground-state separation  $\delta$ . The uncertainty in the values of  $\Delta T_c - \Delta T_{c0}$  amounts to  $\pm 2 \text{ mK}$

	Ground State	$T_c/T_{c0}$		$\Delta T_c - \Delta T_{c0} [\text{mK}]$ at $p = 10 \text{ kbar}$	
		$\delta/T_{c0} = 1$	$\delta/T_{c0} = 2$	$\delta/T_{c0} = 1$	$\delta/T_{c0} = 2$
$W < 0$					
$X_L = 1$	$\Gamma_3$	0.645	0.664	26	36
0.8	$\Gamma_2$	0.646	0.672	42	74
0.6	$\Gamma_2$	0.647	0.667	26	48
0.4	$\Gamma_2$	0.648	0.666	26	51
0.2	$\Gamma_2$	0.648	0.666	25	40
0	$\Gamma_2$	0.648	0.667	25	40
-0.2	$\Gamma_2$	0.650	0.665	29	36
-0.4	$\Gamma_2$	0.644	0.669	32	57
-0.6	$\Gamma_1$	0.643	0.665	25	38
-0.8	$\Gamma_1$	0.644	0.664	24	36
$W > 0$					
$X_L = 1$	$\Gamma_1$	0.644	0.664	23	36
0.8	$\Gamma_1$	0.641	0.665	23	35
0.6	$\Gamma_1$	0.650	0.654	1	-6
0.4	$\Gamma_5^{(1)}$	0.641	0.649	22	29
0.2	$\Gamma_5^{(1)}$	0.641	0.649	19	25
0	$\Gamma_5^{(1)}$	0.642	0.650	21	28
-0.2	$\Gamma_5^{(1)}$	0.644	0.648	23	30
-0.4	$\Gamma_5^{(1)}$	0.642	0.650	27	32
-0.6	$\Gamma_3$	0.644	0.665	21	26
-0.8	$\Gamma_3$	0.644	0.664	26	37

between 1 and 2  $T_{c0}$ . This is true even in the case when the groundstate of Tb ions is magnetic ( $\Gamma_5^{(1)}$ ). A magnetic groundstate, however, can be ruled out from measurements of the susceptibility [8] and also from measurements of the concentration dependence of  $T_c$  for samples with higher concentrations of Tb ions [2]. Large deviations of the calculated values from the experimental values of  $(\Delta T_c - \Delta T_{c0})$  occur near crossing points of the lowest energy levels, for example at  $X_L = 0.6$  ( $W > 0$ ) and  $X_L = 0.8$  ( $W < 0$ ).

## 5. Conclusions

We have shown that the pressure dependence of the superconducting transition temperature of  $\text{La}_{1-x}\text{Tb}_x\text{Al}_2$  can be described quantitatively by a theory which takes into account the crystal field splitting of magnetic impurities. The results are consistent with earlier experiments on the concentration dependence  $T_c(x)$ . The variation of  $T_c$  under pressure depends essentially on the change of the energy splitting  $\delta$  between ground state and first excited state. The results turned out to be rather insensitive to the details of the level scheme, as in the case of the concentration dependence  $T_c(x)$ . Therefore, the original idea to determine the crystal field parameters from these experiments, could not be realized.

For a quantitative analysis of the experimental results, not only the change in the crystal field splitting is essential but also the following points are important and must be taken into account:

1. As the pairbreaking effect depends on the ratio  $\delta/T_{c0}$ , the large decrease of the superconducting transition temperature  $T_{c0}$  of  $\text{LaAl}_2$  with pressure enhances the effect due to the crystal field splitting.
2. From the experiments with  $\text{LaGdAl}_2$ , where crystal field splitting is absent, it can be concluded, that also the scattering rate of the conduction electrons  $\tau^{-1}$  is changed under pressure. The value of  $\Delta\tau^{-1}/\tau^{-1}$  was used for the analysis of the results on  $\text{LaTbAl}_2$  and can be useful for similar experiments with other crystal field split impurities in  $\text{LaAl}_2$ .

## References

1. Bucher, E., Andres, K., Maita, J. P., Hull, G. W.: *Helv. Phys. Acta* **41**, 723 (1968)
2. Pepperl, G., Umlauf, E., Meyer, A., Keller, J.: *Solid State Comm.* **14**, 161 (1974)
3. Happel, H., Hoenig, H. E.: *Solid State Comm.* **13**, 1641 (1973)
4. Fulde, P., Hirst, L. L., Luther, A.: *Z. Physik* **230**, 155 (1970)

5. Keller, J., Fulde, P.: J. Low Temp. Physics **4**, 289 (1971)
6. Keller, J., Fulde, P.: J. Low Temp. Physics **12**, 63 (1973)
7. Holzer, P., Keller, J., Fulde, P.: J. Low Temp. Physics **14**, 247 (1974)
8. Umlauf, E.: to be published
9. Hoenig, H.E., Happel, H., Njoo, H.K., Seim, H.: to be published
10. Umlauf, E., Pepperl, G., Meyer, A.: Phys. Rev. Letters **30**, 1173 (1973)
11. Maple, M.B.: Phys. Letters **26A**, 513 (1968)
12. Abrikosov, A.A., Gorkov, L.P.: Sov. Phys. JETP **12**, 1243 (1961)
13. Guertin, R.P., Voivin, W., Crow, J.E., Sweedler, A.R., Maple, M.B.: Solid State Comm. **11**, 1889 (1973)
14. Lea, K.R., Leask, M.G.M., Wolf, W.P.: J. Phys. Chem. Solids **23**, 1381 (1972)
15. Maple, M.B., Smith, T.F.: Solid State Comm. **7**, 515 (1969)
16. Dietrich, M.: Thesis (1974) Universität Karlsruhe, Germany
17. Smith, T.F., Chu, C.W., Maple, M.B.: Cryogenics **9**, 53 (1969)

Dr. P. Holzer  
Prof. Dr. J. Keller  
Fachbereich Physik der Universität Regensburg  
D-8400 Regensburg, Postfach  
Federal Republic of Germany

Prof. Dr. W. Gey  
Dipl.-Phys. M. Dietrich  
Dr. R. Meier  
IEKP der Universität und des Kernforschungszentrums Karlsruhe  
D-7500 Karlsruhe 1, Postfach 3640  
Federal Republic of Germany

Dr. E. Umlauf  
Zentralinstitut für Tieftemperaturforschung  
der Bayer. Akademie der Wissenschaften  
D-8046 Garching, Hochschulgelände  
Federal Republic of Germany