

### Section III

where  $\mu_8^*$  and  $\mu_{31}^*$  are the atomic moments in the low-temperature B8<sub>1</sub> and the intermediate temperature B31 phases respectively. Interpretation of the first-order phase change appears to require<sup>13</sup> a  $\beta \sim 10$ .

A  $d\mu/dV > 0$  requires a high-spin  $\rightleftharpoons$  low-spin transition in the critical molar volume interval, and hence

$$\langle d(\epsilon_{\text{ex}} - \epsilon_{\text{cf}})/dV \rangle \Delta V > 0.1 \text{ eV}$$

within this interval  $\Delta V$ . Here  $\epsilon_{\text{ex}}$  and  $\epsilon_{\text{cf}}$  are intra-atomic exchange and crystal-field splittings, respectively, and 0.1 eV is taken as the lower limit of the d-band width for orbitals of e<sub>g</sub> symmetry. Since

$$\Delta(-\epsilon_{\text{cf}}) \approx \frac{1}{3} \epsilon_{\text{cf}} \Delta V/V \approx 0.01 \text{ eV} \quad ,$$

it follows that the sharp transition requires

$$\Delta\epsilon_{\text{ex}} = \langle d\epsilon_{\text{ex}}/dV \rangle \Delta V \geq 0.1 \text{ eV} \quad .$$

Stoner<sup>14</sup> has pointed out that there is a maximum bandwidth, and hence a maximum overlap integral  $\Delta_c^f$  for orbitals on neighboring cations, that will support spontaneous band ferromagnetism. Further, the bandwidth for bonding orbitals is greater than that for antibonding orbitals, so that  $\Delta_{\text{ab}} < \Delta_b$ , where the subscripts refer to antibonding and bonding orbitals, respectively. Thus the two conditions for spontaneous band ferromagnetism are

$$\Delta_b < \Delta_c^f \quad \text{and} \quad \Delta_{\text{ab}} < \Delta_c^f < \Delta_b \quad ,$$

where high-spin manganese requires the first and low-spin manganese implies the second. It is concluded that the unusual occurrence of a  $d\mu/dV > 0$  over a small volume interval  $\Delta V$  manifests the transition

$$\Delta_b < \Delta_c^f \rightarrow \Delta_{\text{ab}} < \Delta_c^f < \Delta_b$$

and demonstrates that  $\Delta_c^f$  is quite sharply defined.