

particularly valuable feature. For these experiments the most complete data were available from the quartz gauge at the rear of the specimen and the impact surface data were used to verify the rear surface data.

The stress-volume relation obtained is shown in Fig. 12. As is anticipated for a second-order phase transition, a well-defined change in compressibility is observed at 25 kbar. The cusp at 4 kbar is the Hugoniot elastic limit. In order to accurately determine the critical stress at the transition it was again essential to have the capability of achieving preselected impact velocities in the immediate vicinity of the transition.

The results and their interpretation have been fully reported elsewhere [36]. In summary, however, it was possible to identify the sharp change in compressibility as a pressure induced ferromagnetic to paramagnetic transition with values in agreement with the extrapolation of previous lower pressure results. From the Ehrenfest relation, it was also possible to calculate the change of specific heat and thermal expansion at the transition from the measured change in compressibility and the pressure coefficient of Curie temperature.

Summary

The measurements described here were accomplished with various experimental arrangements chosen to obtain maximum utility from the capabilities, of the impact experiment. These capabilities taken individually are valuable and, more significantly, when combined, provide new experimental capability which is especially well suited for the study of the physical properties of solids under shock-wave loading. From a consideration of these measurements utilizing impact techniques and a comparison with measurements which seem possible with explosive loading experiments, the new experimental conditions which characterize impact experiments can be summarized as follows:

- 1 The impact experiment is a conceptually simple, easily repeated experiment which imparts well-defined input conditions to a specimen.
- 2 The impact experiment provides virtually continuous values of stress for application to a specimen.
- 3 By utilizing the symmetrical impact condition, experimental arrangements are possible which provide intimate connection between the measurement of the applied stress and the measurement of the stress induced physical property change.
- 4 The symmetrical impact condition and the velocity control permit more flexibility in choosing experimental arrangements which avoid the serious wave interaction problems inherent in free surface velocity experiments.
- 5 The lower limit of the stress range available for investigation is lowered to a few kilobars.

For the measurements performed to date the most useful and definitive data were obtained in the elastic range, which for brittle anisotropic materials extends to high stresses. Within the elastic range the one-dimensional strain configuration imposed by shock-wave compression allows determination of physical property changes resulting from large deformation along specific crystallographic directions. Unfortunately, except for compressibility determination, the experiments conducted for stresses in excess of the elastic limit have not yielded precise well-defined data. The desirable experimental conditions described above are also supplemented by practical considerations of safety and low electrical noise levels.

With these experimental conditions, it has been possible to measure physical properties under large compressions which complement measurements made under static high pressures. The measurements reported are extensive and diverse, and the techniques are well enough developed, such that it seems likely that impact techniques will play an increasingly important role in the study of the properties of solids under large compression.

Acknowledgment

The author is indebted to G. E. Ingram for technical assistance in developing the various experimental arrangements and to numerous Sandia Laboratory colleagues for suggestions and discussions.

References

- 1 Rice, M. H., McQueen, R. G., and Walsh, J. M., "Compression of Solids by Strong Shock Waves," *Solid State Physics*, Vol. VI, Seitz and Turnbull, eds., Academic Press, New York, 1958.
- 2 Duvall, G. E., "Some Properties and Applications of Shock Waves," *Response of Metals to High Velocity Deformation*, Shewmon and Zackay, eds., Interscience, New York, 1961.
- 3 Duvall, G. E., and Fowles, G. R., "Shock Waves," *High Pressure Physics and Chemistry*, Vol. II, Bradley, R. S., ed., Academic Press, New York, 1963.
- 4 Alder, B. J., "Physics Experiments with Strong Pressure Pulses" *Solids Under Pressure*, Paul and Warschauer, eds., McGraw Hill, New York, 1963.
- 5 McQueen, R. G., "Laboratory Techniques for Very High Pressures and the Behavior of Metals Under Dynamic Loading," *Metalurgy at High Pressures and High Temperature*, Gschneidner, Hepworth, and Parlee, eds., Gordon and Breach, New York, 1964.
- 6 Al'tshuler, L. V., "Use of Shock Waves in High-Pressure Physics" *Soviet Physics, Uspekhi*, Vol. 8, 1965, pp. 52-91.
- 7 Deal, W. E., Jr., "Dynamic High-Pressure Techniques," *Modern Very High Pressure Techniques*, Wentorf, R. H., Jr., ed., Butterworths, Washington, 1962.
- 8 Doran, D. G., "Measurement of Shock Pressures in Solids," *High Pressure Measurement*, Giardini and Lloyd, eds., Butterworths, Washington, 1963.
- 9 Hughes, D. S., Gourley, L. E., and Gourley, M. F., "Shock Wave Compression of Iron and Bismuth," *Journal of Applied Physics*, Vol. 32, 1961, p. 624.
- 10 Lundergan, C. D., and Herrmann, W., "Equation of State of 6061-T6 Aluminum at Low Pressures," *Journal of Applied Physics*, Vol. 34, 1963, p. 2046.
- 11 Thurnborg, S., Ingram, G. E., and Graham, R. A., "Compressed Gas Gun for Controlled Planar Impacts Over a Wide Velocity Range," *Review of Scientific Instruments*, Vol. 35, 1964, p. 11.
- 12 Halpin, W. J., Jones, O. E., and Graham, R. A., "A Submicrosecond Technique for Simultaneous Observation of Input and Propagated Impact Stresses" *Dynamic Behavior of Materials*, ASTM Special Technical Publication No. 336, ASTM, Philadelphia, 1963.
- 13 Linde, R. K., and Schmidt, D. N., "Measuring the Submicrosecond Response of Shock Loaded Materials," *Review of Scientific Instruments*, Vol. 37, 1966, p. 1.
- 14 Taylor, J. W., and Rice, M. H., "Elastic-Plastic Properties of Iron," *Journal of Applied Physics*, Vol. 34, 1963, p. 364.
- 15 Graham, R. A., Ingram, G. E., and Ingram, W. D., "Performance of a High-Velocity Propellant Gun for Controlled Impacts," Sandia Corporation Research Report, SC-4652 (RR), Nov. 1961.
- 16 Wasley, R. J., and O'Brien, J. F., "Low Pressure Hugoniot of Solid Explosives," Fourth Symposium on Detonation held at the U. S. Naval Ordnance Test Station, Oct. 1965.
- 17 Ingram, G. E., "Application of Charged Coaxial Cables to the Measurement of Projectile Velocity and Impact Time in a Compressed Gas Gun," *Review of Scientific Instruments*, Vol. 36, 1965, p. 458.
- 18 Barker, L. M., and Hollenbach, R. E., "System for Measuring the Dynamic Properties of Materials," *Review of Scientific Instruments*, Vol. 35, 1964, p. 742.
- 19 Graham, R. A., "Piezoelectric Behavior of Impacted Quartz," Abstract, in *Bulletin of the American Physical Society*, Vol. 5, 1960, p. 511.
- 20 Graham, R. A., "Piezoelectric Behavior of Impacted Quartz," *Journal of Applied Physics*, Vol. 32, 1961, p. 555.
- 21 Graham, R. A., "A Technique for Studying Piezoelectricity Under Transient High Stress Conditions," *Review of Scientific Instruments*, Vol. 32, 1961, p. 1308.
- 22 Graham, R. A., "Dielectric Anomaly in Quartz for High Transient Stress and Field," *Journal of Applied Physics*, Vol. 33, 1962, p. 1755.
- 23 Graham, R. A., Neilson, F. W., and Benedick, W. B., "Piezoelectric Current from Shock-Loaded Quartz—A Submicrosecond Stress Gauge," *Journal of Applied Physics*, Vol. 36, 1965, p. 1775.
- 24 Karcher, J. C., "A Piezoelectric Method for the Instantaneous Measurement of High Pressures," *Scientific Papers of the Bureau of Standards*, No. 445, 1922.
- 25 Wackerle, J., "Shock-Wave Compression of Quartz," *Journal of Applied Physics*, Vol. 33, 1962, p. 922.
- 26 Fowles, G. R., "Shock-Wave Compression of Quartz," Doctoral Thesis, Department of Geophysics, Stanford University, 1962.

27 Koga, U., Aruga, M., and Yoshinaka, Y., "Theory of Plane Elastic Waves in a Piezoelectric Crystalline Medium and Determination of Elastic and Piezoelectric Constants of Quartz," *Physical Review*, Vol. 109, 1958, p. 1467.

28 Bechmann, R., "Elastic and Piezoelectric Constants of Alpha-Quartz," *Physical Review*, Vol. 110, 1958, p. 1060.

29 Jones, O. E., "Piezoelectric Behavior of Quartz Shock-Loaded at 79 K," Abstract in *Bulletin of the American Physical Society*, Vol. 11, 1966, p. 414.

30 Halpin, W. J., "Current from a Shock-Loaded Short Circuited Ferroelectric Ceramic Disk," *Journal of Applied Physics*, Vol. 37, 1966, p. 153.

31 Graham, R. A., and Ingram, G. E., "Capacitance Change of Sapphire Under Shock-Wave Compression—A Shock-Wave Stress Gauge," Abstract in *Bulletin of the American Physical Society*, Vol. 11, 1966, p. 414.

32 Brooks, W. P., and Graham, R. A., "Shock-Wave Compression of Sapphire," Abstract in *Bulletin of the American Physical Society*, Vol. 11, 1966, pp. 414.

33 Graham, R. A., Jones, O. E., and Holland, J. R., "Shock-Wave Compression of Germanium From 20 to 140 Kbar," *Journal of Applied Physics*, Vol. 36, 1965, p. 3955.

34 Graham, R. A., Jones, O. E., and Holland, J. R., "Physical Behavior of Germanium Under Shock-Wave Compression," *Journal of the Physics and Chemistry of Solids*, Vol. 27, 1966, p. 1519.

35 Duff, R. E., and Minshall, S. F., "Investigation of a Shock-Induced Transition in Bismuth," *Physical Review*, Vol. 108, 1957, p. 1207.

36 Graham, R. A., Anderson, D. H., and Holland, J. R., "Shock-Wave Compression of 30 Ni-70 Percent Fe Alloys—The Pressure Induced Magnetic Transition," *Journal of Applied Physics*, Vol. 38, 1967, p. 223.

Supplementary References on Mechanical Properties Determined by Impact Techniques.

37 Barker, L. M., Lundergan, C. D., and Herrmann, W., "Dynamic Response of Aluminum," *Journal of Applied Physics*, Vol. 35, 1964, p. 1203.

38 Butcher, B. M., and Canon, J. R., "Influence of Work-Hardening on the Dynamic Stress-Strain Curves of 4340 Steel," *American Institute of Aeronautics and Astronautics Journal*, Vol. 2, 1964, p. 2174.

39 Hartman, W. F., "Determination of Unloading Behavior of Uniaxially Strained 6061-T6 Aluminum from Residual Strain Measurements," *Journal of Applied Physics*, Vol. 35, 1964, p. 2090.

40 Barker, L. M., and Hollenbach, R. E., "Interferometer Technique for Measuring the Dynamic Mechanical Properties of Materials," *Review of Scientific Instruments*, Vol. 36, 1965, p. 1617.

41 Halpin, W. J., and Graham, R. A., "Shock-Wave Compression of Plexiglas from 3 to 20 Kbar," Fourth Symposium on Detonation held at U. S. Naval Ordnance Laboratory, Oct. 1965.

42 Butcher, B. M., and Karnes, C. H., "Strain-Rate Effects in Metals," *Journal of Applied Physics*, Vol. 37, 1966, p. 402.

43 Barker, L. M., Butcher, B. M., and Karnes, C. H., "Yield Point Phenomenon in Impact-Loaded 1060 Aluminum," *Journal of Applied Physics*, Vol. 37, 1966, p. 1989.

Reprinted from the December 1967
Journal of Basic Engineering