

REFERENCES

1. M. H. Rice, R. G. McQueen and J. M. Walsh in Solid State Physics, Vol. VI, edited by F. Seitz and D. Turnbull, Academic Press, New York, 1958.
2. G. E. Duvall in Response of Metals to High Velocity Deformation, edited by P. G. Shewmon and V. F. Zackay, Interscience, New York, 1961.
3. W. E. Deal, Jr., in Modern Very High Pressure Techniques, edited by R. H. Wentorf, Jr., Butterworths, London, 1962.
4. D. G. Doran in High Pressure Measurements, edited by A. A. Giardini and E. C. Lloyd, Butterworths, London, 1963.
5. G. E. Duvall and G. R. Fowles in High Pressure Physics and Chemistry, Vol. 2, edited by R. S. Bradley, Academic Press, New York, 1963.
6. I. C. Skidmore, Appl. Mat. Research 4, 131 (1965).
7. D. G. Doran and R. K. Linde in Solid State Physics, Vol. 19, edited by F. Seitz and D. Turnbull, Academic Press, New York, 1966.
8. R. A. Graham, J. Basic Engr. 89, 911 (1967).
9. D. C. Pack, W. M. Evans, and H. J. James, Proc. Phys. Soc. (London) 60, 1 (1948).
10. S. Minshall, J. Appl. Phys. 26, 463 (1955).
11. M. Van Thiel, A. S. Kusubov and A. C. Mitchell, Compendium of Shock-Wave Data, Lawrence Radiation Laboratory, University of California, UCRL 50108.

SUMMARY OF HUGONIOT ELASTIC LIMIT MEASUREMENTS

Material	Condition (a)	σ_{HEL} (kbar) (b)	Remarks (c)	Technique (d)	Reference
<u>METALS</u>					
Iron Alloys					
iron	annealed	7	25 mm	E-1	Bancroft, et al. (1955)
iron	AR, annealed	15-7	25-133 mm	E-1, 14	Minshall (1961)
iron	normalized	8-7	20-51 mm ⁺ *	E-5	Jones, et al. (1962)
iron	annealed	11-7	6-51 mm ⁺ *	E-6	Taylor, et al. (1963)
iron	-	10	25-60 mm ⁺ *	E-7	Ivanov, et al. (1963)
iron	annealed	12-6	6-40 mm ⁺ *	E-12	McQueen (1964)
iron	-	11-8	4-18 mm ⁺	E-12	Peyre, et al. (1965)
rac E iron	varied	12-6	12 mm [*]	E-5	Holland (1967)
rac E iron	annealed	10	13 mm, temp 76- 573°K	E-5	Rohde (1968a)
018	normalized	13-10	20-51 mm ⁺ *	E-5	Jones, et al. (1962)
018	annealed - cold rolled	16-9	19 mm	E-5	Jones, et al. (1964)
018	varied	12	19 mm [*]	E-5	Jones, et al. (1968)
020	-	10-12	127 mm	E-1	Minshall (1955)
020	AR, annealed	15-11	50-127 mm	E-1	Minshall (1961)
020	AR	10	51-76 mm	E-1	Costello (1957)
040	-	11	127 mm	E-1	Minshall (1955)
040	AR, annealed	6-14	127 mm	E-1	Minshall (1961)
055	AR, annealed	13-15	125-127 mm	E-1, 14	Minshall (1961)
055	varied	8-15	25 mm	E-14	Loree, et al. (1966)