

TABLE 2

The Elastic Constants of the Constituent Alloys  
of Dental Amalgam at Atmospheric Pressure  
(All Moduli in  $10^{12}$  dynes/cm<sup>2</sup>)

Alloy	Bulk Modulus	Shear Modulus	Young's Modulus	Poisson's Ratio
$\gamma$ -Ag <sub>3</sub> Sn	1.01	0.307	0.836	.36
$\gamma_1$ -Ag <sub>2</sub> Hg <sub>3</sub>	0.871	0.269	0.731	.36
$\gamma_2$ -HgSn <sub>7-8</sub>	0.567	0.181	0.491	.35