

face tensions. Another relationship, proposed by Strauss (37), is very similar to that shown in Fig. 10.

The value of all such relationships depends on the reliability of the experimental data on which they are based. A critical review of all pertinent data from the literature will be published elsewhere.

The straight line of Fig. 10 for cubic or tetragonal metals is given by the equation

$$\sigma_{mp} = 0.274 \left( \frac{\Delta H_{vap}}{V_{at}} \right)^{0.931}$$

or

$$\log \sigma_{mp} = 0.9309 \log \left( \frac{\Delta H_{vap}}{V_{at}} \right) - 0.5623$$

(the logarithms here and in the equations that follow are to the base 10). The relationship for hexagonal and rhombohedral metals is

$$\sigma_{mp} = 5.740 \left( \frac{\Delta H_{vap}}{V_{at}} \right)^{0.620}$$

or

$$\log \sigma_{mp} = 0.6204 \times \log \left( \frac{\Delta H_{vap}}{V_{at}} \right) + 0.7587$$

( $\sigma_{mp}$  is in dynes per centimeter,  $\Delta H_{vap}$  is in calories per gram atom, and  $V_{at}$  is in cubic centimeters per gram atom, all for the liquid at the melting point.)

At the critical temperature  $T_c$ , the surface tension of any substance is zero. It has been shown (38) that, at least in first approximation,  $\sigma$  should be a linear function of temperature. If we know  $T_c$  (see Table 3) we can readily calculate the temperature coefficient over the whole liquid range:

$$d\sigma/dT = -\sigma_0/T_c = -\sigma_{mp}/(T_c - T_{mp})$$

or

$$d\sigma/dT = -\sigma_T/(T_c - T)$$

where  $\sigma_0$  is the extrapolated surface tension at 0°K and  $\sigma_T$  is the surface tension at any temperature  $T$  (see 38 for a table giving  $d\sigma/dT$  for 20 metals and for discussion of this relationship).

### Nuclear Rocket Reactor

The obvious way to produce rocket thrust with a high specific impulse is to use atomic energy and operate a nuclear reactor containing the critical mass of fissionable material in the form of a "liquid pipe," as illustrated in Figs. 5 and 6; then to bubble or blow hydrogen gas radially through the liquid metal to heat the gas to as high a temperature as possible and then allow the atomic hydrogen to expand through the rocket nozzle. The thickness, diameter, and length of the "liquid pipe" can be varied to suit the design requirements.

The first step toward realization of this goal should be the study of the chemistry (at as high a temperature as is now experimentally possible) of appropriate metals with various refractory oxides, carbides, nitrides, sulfides, and other substances useful for such a nuclear program (39).

### References and Notes

- H. D. Babcock, *Astrophys. J.* **102**, 154 (1945).
- A. V. Grosse and J. Conway, *Ind. Eng. Chem.* **50**, 669 (1958).
- W. Doyle, J. Conway, A. V. Grosse, *J. Inorg. Nucl. Chem.* **6**, 138 (1958).
- A. V. Grosse, in *Proceedings of the High Temperature Symposium at Berkeley, Calif., June 1956* (1957), pp. 59-68.
- Chem. Eng. News* **28**, 1564 (1950).
- R. H. Wilson, J. B. Conway, A. Engelbrecht, A. V. Grosse, *J. Am. Chem. Soc.* **73**, 5514 (1951).
- Natl. Bur. Std. (U.S.) Circ. No. 523* (1954), p. 111.
- J. B. Conway, R. H. Wilson, Jr., A. V. Grosse, *J. Am. Chem. Soc.* **75**, 499 (1953).
- J. B. Conway, W. Smith, W. Liddell, A. V. Grosse, *ibid.* **77**, 2026 (1955); J. B. Conway and A. V. Grosse, *ibid.* **80**, 2972 (1958).
- A. D. Kirshenbaum and A. V. Grosse, *ibid.* **78**, 2020 (1956).
- A. G. Streng and A. V. Grosse, *ibid.* **79**, 1517 (1957).
- , *ibid.*, p. 3296.
- , *ibid.*, p. 5583.
- C. S. Stokes, W. W. Knipe, L. A. Streng, *J. Electrochem. Soc.* **107**, 35 (1960).
- H. W. Leutner and C. S. Stokes, *Ind. Eng. Chem.* **53**, 341 (1961).
- The physics of plasmas and electric arcs (including the early history) is well described by W. Finkelnburg and H. Maecker in *Handbuch der Physik*, S. Flügge, Ed. (Springer, Berlin, 1956), vol. 22, pp. 254-444.
- See past literature in A. V. Grosse, *Inorg. Chem.* **1**, 436 (1962).
- F. Birch, *Phys. Rev.* **41**, 641 (1932).
- A. V. Grosse and A. D. Kirshenbaum, *J. Inorg. Nucl. Chem.* **24**, 739 (1962).
- See, for example, E. A. Guggenheim, *J. Chem. Phys.* **13**, 253 (1945).
- C. T. Ewing, J. P. Stone, R. R. Miller, *Naval Res. Lab. Rept. No. NRL 1069* (1960); M. Makansi, W. A. Selke, C. F. Bonilla, *J. Chem. Eng. Data* **5**, 441 (1960).
- The only exceptions found so far are iron, cobalt, and nickel. See A. V. Grosse and A. D. Kirshenbaum, *J. Inorg. Nucl. Chem.*, **25**, 331 (1963).
- A. V. Grosse and J. B. Conway, *Ind. Eng. Chem.* **50**, 663 (1958).
- R. E. White and T. W. Higgins, *Tappi* **41**, 71 (1958).
- A. D. Kirshenbaum and J. A. Cahill, *J. Inorg. Nucl. Chem.* **14**, 285 (1960).
- P. J. McGonigal, A. D. Kirshenbaum, A. V. Grosse, *J. Phys. Chem.* **66**, 737 (1962).
- A. V. Grosse, H. W. Leutner, W. J. Murphy, C. S. Stokes, *J. Am. Chem. Soc.* **84**, 3209 (1962).
- C. S. Stokes, W. W. Knipe, L. A. Streng, *J. Electrochem.* **107**, 35 (1960); C. S. Stokes and W. W. Knipe, *Ind. Eng. Chem.* **52**, 287 (1960).
- C. Hering, *Trans. Am. Electrochem. Soc.* **11**, 329 (1907).
- , *ibid.* **15**, 255 (1909); *ibid.* **39**, 313 (1921).
- E. F. Northrup, *Phys. Rev.* **24**, 474 (1907).
- E. N. C. Andrade, *Phil. Mag.* **17**, 698 (1934).
- A. V. Grosse, *J. Inorg. Nucl. Chem.* **23**, 333 (1961); *ibid.* **25**, 317 (1963).
- E. N. C. Andrade, *Phil. Mag.* **17**, 497 (1934).
- A. Skapski, *J. Chem. Phys.* **16**, 386 (1948); *ibid.*, p. 389.
- J. W. Taylor, *Metallurgia* **50**, 161 (1954).
- S. W. Strauss, *Nucl. Sci. Eng.* **8**, 362 (1960).
- A. V. Grosse, *J. Inorg. Nucl. Chem.* **24**, 147 (1962).

39. I am indebted to the several government agencies that have supported the high-temperature work at the Research Institute of Temple University for over 15 years—specifically, the National Science Foundation, the U.S. Atomic Energy Commission, the offices of Naval Air Force, and Army Research, and the Army Ballistic Missile Agency. I am also indebted to my co-workers at the institute, particularly to J. A. Cahill, J. B. Conway, J. J. Correa, W. L. Doyle, Alfred Engelbrecht, T. R. Flint, J. G. Floss, Neil Goodis, A. D. Kirshenbaum, Theron Lee, Jr., H. W. Leutner, W. E. Marceau, P. J. McGonigal, R. A. Miller, W. J. Murphy, E. W. Smith, C. S. Stokes, A. G. Streng, L. V. Streng, and R. P. M. Werner. I also thank Prof. Dr. Ulrich Hofmann of the University of Heidelberg for arranging the lecture tour in the course of which I delivered the address on which this article is based.