

imum varies linearly with the cube of the Ag ion separation. The independence of the energy of the  $\Gamma_1$  state with respect to the halide ion indicates that the conduction states are centered on the Ag ions, in agreement with the calculations of Scop,<sup>12</sup> who found that the conduction band was formed principally from  $\text{Ag}^+ 5s$  states.

The correlation shown in Fig. 16 may be used to predict the energy of the  $\Gamma_1$  state for other silver halide crystals which have the NaCl structure. If the absorption edge of the crystal is known, then the photoelectric threshold may be predicted also. By using a lattice constant of 4.92 Å, the conduction-band minimum of AgF is estimated to be at  $-2.5$  eV. This value must be viewed in the light of the anomalous behavior often observed for fluorides. Since AgCl and AgBr form solid solutions in all proportions, the conduction-band minimum and the photoelectric threshold of mixed crystals may be estimated by using the published data for the lattice parameter<sup>29</sup> and for the absorption edge.<sup>8,30</sup> For a mixed crystal with 42% AgBr the absorption edge and lattice constant at room temperature are 2.64 eV and 5.68 Å. From Fig. 16 the energy of the  $\Gamma_1$  state and the photoelectric threshold are estimated to be  $-3.45$  and 6.1 eV, respectively. Similar estimates may be made for iodobromide and iodochloride mixed crystals and for the high-pressure phase of AgI, which has the NaCl structure.<sup>31-33</sup> It would be of interest to see if the photoelectric threshold of the mixed crystals containing AgI is correlated by Fig. 16, since the absorption edge of these crystals is highly sensitive to small amounts of iodide ion.<sup>8</sup>

For both AgCl and AgBr Balchan and Drickamer<sup>16</sup> observed a blue shift of the absorption edge at temperatures above 250°C. Their observation may be explained in terms of the band-structure changes in the intermediate region (region 3, Fig. 1). For all temperatures, their shifts were calculated from the same

<sup>29</sup> H. Raynaud, M. Duranté, B. Hervier, and J. Pouradier, *Sci. Ind. Phot.* 26, 425 (1955).

<sup>30</sup> K. Meinig, J. Metz, and J. Teltow, *Phys. Status Solidi* 2, 1556 (1962).

<sup>31</sup> R. B. Jacobs, *Phys. Rev.* 54, 325 (1938).

<sup>32</sup> G. J. Piermarini and C. E. Weir, *J. Res. Natl. Bur. Std.* A66, 325 (1962).

<sup>33</sup> W. A. Bassett and T. Takahashi, *Am. Mineralogist* 50, 1576 (1965).

$\nu_0$  value—25 200  $\text{cm}^{-1}$  for AgCl and 22 000  $\text{cm}^{-1}$  for AgBr. At higher temperatures, it is known<sup>1,30</sup> that the edge shifts to the red; at 250°C, a shift of 0.2 eV (1600  $\text{cm}^{-1}$ ) was observed. Thus, the data obtained at high temperature did not correspond to the observed room-temperature transitions but to transitions involving valence states possibly 0.2 eV farther away from the valence-band maximum at  $L_3'$ . Since the  $p-d$  coupling term and pressure-induced energy increase of the valence state with respect to  $\Gamma_{15}$  decrease for values of  $k$  away from  $L_3'$ , a pressure-induced blue shift at high temperatures is possible (i.e., the shift to higher energies of the valence band is less than the shift of the conduction band).

No explanation was found for the discrepancy between the present work and that of Slykhouse and Drickamer<sup>15</sup> concerning the AgBr absorption edge (see Fig. 13). One pertinent observation is that at the  $\nu_0$  value used by them, AgBr has a large absorption coefficient (150  $\text{cm}^{-1}$ ) which, at room temperature and atmospheric pressure, corresponds to the shoulder region of the AgBr spectrum [region 3, Fig. 1(b)]. It was in this shoulder region that the isostatic point was found both for AgBr and for AgCl.

The phonon spectrum in the silver halides should be affected by an increase in pressure, with a resulting effect on the indirect transitions in the absorption edge. However, at room temperature these effects should be overshadowed by the changes in the band structure.

At present no adequate explanation for the effect of the substrate upon the exciton peak location in AgCl is available. The peak locations for the Aclar and NaCl substrates differed by 360  $\text{cm}^{-1}$ ; however, no measurable difference was observed for the AgBr layers. It is difficult to attribute the difference to impurities, since the absorption coefficient of the AgCl is so large in this spectral region ( $>10^5 \text{ cm}^{-1}$ ).

#### ACKNOWLEDGMENTS

The author is grateful to Dr. G. W. Luckey, Dr. R. S. Van Heyningen, and Dr. R. K. Ahrenkiel for several helpful discussions concerning this study. In addition, he thanks R. M. Gluck, A. A. Rasch, and W. C. Hodges for preparing some of the silver halide samples.

IT is w  
are s  
perature  
the  $F$  op  
light ble  
and the t  
of recom  
the  $F$ -to-

where  $h$   
of  $F$  lig  
photo-ion  
vacancy)  
and enco  
( $M^+$  or  
tures an

There  
literature  
grate an  
defects a  
cerned p  
center fo  
tron by  
also be s  
detailed  
posed by  
an  $\alpha$  cen

† Work  
Contract

\* Preser  
ton, D. C.

<sup>1</sup> R. A.

<sup>2</sup> C. J. I

<sup>3</sup> F. Lüt

<sup>4</sup> Y. Fa

Commun.

<sup>5</sup> W. D.

F. Seitz

Vol. 16, p