


2.97
 2.64
 ,33

$$\frac{.33}{2.64} = 12.5\%$$



DENSITY OF PYROPHYLLITE
 AFTER RELEASE OF PRESSURE

RAM FORCE, TONS

for pyrophyllite tetrahedron $\frac{9}{16}$ " leg
 carbide anvil $\frac{1}{2}$ " leg.

FIG 7

Kilans J