

SYNTHESIS OF LANTHANIDE-IRON LAVES PHASES AT HIGH PRESSURES AND TEMPERATURES

J. F. Cannon, D. L. Robertson and H. T. Hall
Chemistry Department, Brigham Young University
Provo, Utah 84601

(Received November 9, 1971; Communicated by J. B. Goodenough)

ABSTRACT

High pressures and temperatures were used to synthesize the previously unknown compounds PrFe_2 , NdFe_2 and YbFe_2 . These compounds have the cubic MgCu_2 -type structure with lattice parameters 7.467, 7.452 and 7.239 Å respectively. The relative importance of $4f$ bonding and size effects in the formation of LFe_2 compounds (L = lanthanide) is discussed.

Introduction

The lanthanide compounds of general formula LFe_2 (L = lanthanide) have been studied by a number of investigators (1-15). The known compounds in this series are isomorphous with a cubic Laves-phase structure of the MgCu_2 -type. There are eight formula weights per unit cell, and the space group is $\text{Fd}\bar{3}\text{m}$. None of the previous investigators has reported the synthesis of LaFe_2 , PrFe_2 , NdFe_2 , EuFe_2 or YbFe_2 , and some (6, 11, 13-14) report that attempts to prepare these compounds by high-temperature methods were unsuccessful.

Recently H. T. Hall (16) suggested that high-pressure synthesis methods may be useful in preparing otherwise unknown lanthanide compounds when certain conditions are met. These conditions are, first, that the compounds must be unknown for the lower molecular weight lanthanides, second, that the lanthanide component must be more compressible than the non-lanthanide, and, third, that the increase in radius of the lanthanide component be primarily responsible for the premature termination of the series. Under these circumstances the application of high pressure will create a condition suitable for a successful synthesis by reducing the radius of the lanthanide to a greater degree than that of the non-lanthanide. Since the LFe_2 series seems to meet these conditions, high-pressure techniques were applied to the synthesis of the unknown members of this series.

Experimental

The tetrahedral anvil press developed by Hall (17-18) was used to generate the high pressures and temperatures needed for this work. Details of the pressure and temperature calibrations, the sample geometry, and details of the experimental procedure have been described elsewhere (19).

Powders of La (under oil) and Fe as well as ingots of Yb and Lu were obtained from Research Organic/Inorganic Chemical Corporation, Sun Valley, California. The other lanthanides (Pr, Nd, Sm, Gd, Tb, Ho) were obtained in ingot form from Research Chemicals Incorporated, Phoenix, Arizona.

The ingots were filed and those filings that passed a 100-mesh sieve were used. Each synthesis run was prepared from a stoichiometric mixture of the appropriate powders. No oxide contamination was observed in the powder X-ray spectra taken during the course of this study.

X-ray data were taken using a G. E. XRD-5 with a Debye-Scherrer powder camera of 143.2 mm diameter. Samples were crushed and without further preparation X-rayed in 0.5 mm glass capillaries which were rotated during exposure. Copper ($\lambda = 1.54178 \text{ \AA}$) and chromium ($\lambda = 2.29092 \text{ \AA}$) radiation were used as circumstances dictated. The Nelson-Riley extrapolation method (20) was used to determine the lattice constants.

Results

Although the syntheses were made from 1:2 L/Fe mixtures, none of the reaction products was free of impurity. In each case the X-ray spectrum showed minor lines which could not be identified. In determining the minimum pressure required to prepare a given compound, the synthesis was considered successful if the most intense lines characteristic of the MgCu_2 -type structure were present in the X-ray spectrum of the product.

The new compounds successfully prepared were PrFe_2 , NdFe_2 and YbFe_2 . Conditions as severe as 90 kbars at 1350°C for 5 minutes and 69 kbars at 1050°C for 60 minutes failed to cause any detectable reaction in the La-Fe runs. Several runs at various temperatures and pressures (up to 69 kbars) resulted in reactions between Eu and Fe, but X-ray spectra of the products showed no evidence of the MgCu_2 -type structure. Previously known compounds prepared for comparison with the literature include SmFe_2 , GdFe_2 , TbFe_2 , HoFe_2 and LuFe_2 .

Lattice parameters and synthesis data for the compounds prepared in this study are shown in Table I along with some of the more recent literature

TABLE I
Synthesis Data and Lattice Parameters

Compound	Min. Pressure Req.		Lattice Parameters		
	for Prep. at 1000°C (kbar)	This Work	(13)	(14)	(15)
PrFe_2	32-35	7.467(4)			
NdFe_2	20-28	7.452(5)			
SmFe_2		7.415(4)	7.401		7.417
GdFe_2		7.394(5)	7.376	7.390	7.396
TbFe_2		7.345(6)	7.341	7.341	7.347
HoFe_2		7.303(6)	7.287	7.306	7.304
YbFe_2	<6	7.239(5)			
LuFe_2		7.229(4)		7.217	

data for the previously known compounds. The numbers in parentheses following our lattice parameters represent the standard deviation in the last significant figure. The pressures shown in the second column represent for each new compound the pressure of the last unsuccessful synthesis to the pressure of the first successful synthesis. Each run above the higher of these pressures (with temperature at 1000°C or higher) resulted in successful synthesis. The synthesis of YbFe_2 was successful down to the lowest pressure attainable in our apparatus (about 6 kbar). Table 2 shows the X-ray data for the new compounds.

TABLE 2
X-ray Data for New Compounds

hk1	$1/1_0$	PrFe_2		NdFe_2		YbFe_2	
		d(Obs)	d(Cal)	d(Obs)	d(Cal)	d(Obs)	d(Cal)
111	1	4.283	4.311	4.285*	4.303	4.167	4.179

220	6	2.630	2.640	2.622	2.635	2.552	2.559
311	10	2.244	2.251	2.239	2.247	2.179	2.183
222	3	2.149	2.156	2.143	2.151	2.085	2.090
400	1	N.O.	--	N.O.	--	1.806	1.810
331	1	1.710	1.713	1.710*	1.710	1.660	1.661
420	1	1.658*	1.670	1.644*	1.666	1.623*	1.619
422	5	1.522	1.524	1.519	1.521	1.477	1.478
511	5	1.436	1.437	1.434	1.434	1.393	1.393
440	5	1.319	1.320	1.316	1.317	1.280	1.280
531	3	1.263	1.262	1.256*	1.260	1.224	1.224
620	2	1.180	1.181	1.179	1.178	N.O.	--

N.O. = Not Observed
All d values in angstroms

* Not used in lattice constant determination

Discussion

In this study, as in many others, Yb and Eu show their usual "anomalous" behavior. The lattice parameter that we found for YbFe₂ (see Table 1) indicates that the size of the Yb is such that a favorable synthesis condition should exist at atmospheric pressure. Nevertheless Mansey, Raynor and Harris (13) clearly state that their attempts to prepare YbFe₂ at atmospheric pressure did not succeed. This behavior is apparently associated with the tendency of Yb to exhibit divalent character. This same tendency in Eu is probably responsible for our lack of success in preparing EuFe₂.

The data in Table I show that increasing pressure is required for a successful synthesis as the size of the lanthanide increases. This suggests that the increasing size of the lanthanide component is primarily responsible for the previous lack of success in preparing PrFe₂ and NdFe₂. This could also explain our failure to prepare LaFe₂, i.e. La is apparently not sufficiently reduced in size at 90 kbars to effect the synthesis. We realize, however, that other factors may come into play in the La-Fe system since, surprisingly, no binary La-Fe compound of any composition is known (14, 21).

Gschneidner (22-24) and others (25-28) have suggested that 4f bonding, rather than size effect, is a determining factor in the formation of certain lanthanide compounds. In a recent paper, Burzo (28) applied Gschneidner's arguments on this subject to the LFe₂, LCo₂ and LNi₂ series. By examining the difference between R_M (lanthanide radius in the compound) and R_{4f} (the lanthanide 4f shell radius) as a function of the lanthanide atomic number, he concluded that the smaller the value of (R_M-R_{4f}) the more the 4f electrons are exposed and the greater will be their contribution to the bonding. The value of (R_M-R_{4f}) is essentially constant from Lu down to Gd but decreases rapidly after Gd as the La end of the series is approached. This indicates that the 4f contribution to the bonding in the LFe₂ compounds is greatest for the earlier members of the series, decreases to Gd and then remains essentially constant from that point through Lu. Burzo further observes that R_M is smaller in the LFe₂ compounds than in pure lanthanide metals. This implies small L-L distances and thus indicates the existence of 4f bonding even in LuFe₂. He concludes finally that "in the compounds examined the contribution of the 4f electrons to the bonding is a predominant factor in the forming of the crystal cell."

If Burzo's conclusion is correct, then one might be tempted to say that 4f bonding is responsible for the lack of success in preparing LaFe₂, PrFe₂ and NdFe₂ at atmospheric pressure since these compounds would have the largest 4f bonding contribution of any in the series (with the exception of CeFe₂ which is unusual because of its tetravalent character). Because high pressure tends to increase the 4f contribution to the bonding (22), this would mean that high pressure should impede the formation of these compounds. Since our studies have shown the opposite effect, we conclude that an increase in 4f bonding does not account for the failure to prepare LaFe₂, PrFe₂ and NdFe₂ at atmospheric pressure.

Gschneidner (22) has suggested a test for determining whether 4f bonding or size effect is the determining factor in polymorphic changes within a lanthanide compound series. If high pressure causes the heavier lanthanide compounds to behave more like the lighter ones, then 4f bonding plays an important part, but if the reverse occurs, size effects are the predominant factor. Applying this criterion to our findings, it is evident that size effects are the determining factor in the formation of LFe₂ compounds.

It should not be concluded that our experiments rule out the existence of 4f bonding in these compounds. It is entirely possible that 4f bonding does exist, but our work shows that, if it does, the effect is small. This conclusion is in accord with Gschneidner's earlier statements (22) that 4f bonding has no appreciable effect in Lanthanide compound series which do not exhibit a polymorphic change. In

accordance with this, we can also say that $4f$ bonding is probably not a significant factor in the formation of LCo_2 or LNi_2 compounds.

Acknowledgments

We wish to thank the Army Research Office (Durham) for their support of this work. We are also grateful for helpful suggestions made by N. L. Eatough of the California Polytechnic College in San Luis Obispo and by A. E. Ray of the University of Dayton.

References

1. R. Vogel, *Z. Anorg. Chem.* **99**, 25 (1917).
2. F. Endter and W. Klemm, *Z. Anorg. Chem.* **252**, 377 (1944).
3. J. O. Jepsen and P. Duwez, *Trans. ASM* **47**, 543 (1955).
4. J. H. Wernick and S. Geller, *Trans. AIME* **218**, 866 (1960).
5. S. E. Haszko, *Trans. AIME* **218**, 958 (1960).
6. K. Nassau, L. V. Cherry and W. E. Wallace, *J. Phys. Chem. Solids* **16**, 123 (1960).
7. A. E. Dwight, *Trans. ASM* **53**, 479 (1961).
8. V. F. Novy, R. C. Vickery and E. V. Kleber, *Trans. AIME* **221**, 580 (1961).
9. N. C. Baenziger and J. O. Moriarty, *Acta Crystallogr.* **14**, 948 (1961)
10. M. I. Copeland, M. Krug, C. E. Armantrout and H. Kato, *U. S. Bur. Mines Rept. Invest. No. 5925* (1962).
11. V. F. Terekhova, E. V. Maslova and Ye. M. Savitskiy, *Russ. Met.* **1965**, 50 (1965). *Transl. of Izv. Akad. Nauk SSSR, Metal.* **1965**, 128 (1965).
12. P. I. Kripyakevich, M. Yu. Teslyuk and D. P. Frankevich, *Sov. Phys. Crystallogr.* **10**, 344 (1965). *Transl. of Kristallografiya* **10**, 422 (1965).
13. R. C. Mansey, G. V. Raynor and I. R. Harris, *J. Less-Common Metals* **14**, 329 (1968).
14. A. E. Ray, *Proc. 7th Rare Earth Res. Conf.*, p. 473. J. F. Nachmann, Editor (1968).
15. K. H. J. Buschow and R. P. Van Stapele, *J. Phys. (Paris) Colloq.* **32**, 672 (1971).
16. H. T. Ball, *Rev. Phys. Chem. Jap.* **39**, 110 (1969).
17. H. T. Hall, *Rev. Sci. Instrum.* **29**, 267 (1958).
18. H. T. Hall, *Rev. Sci. Instrum.* **33**, 1278 (1962).
19. J. F. Cannon and H. T. Hall, *Inorg. Chem.* **9**, 1639 (1970).
20. J. B. Nelson and D. P. Riley, *Proc. Phys. Soc. (London)* **57**, 160 (1945).
21. C. E. Lundin, *The Rare Earths*, p. 280. F. H. Spedding and A. H. Daane, Editors, Wiley and Sons, New York (1961).
22. K. A. Gschneidner and R. M. Valletta, *Acta Met.* **16**, 477 (1968).
23. K. A. Gschneidner and W. B. Pearson, *Mat. Res. Bull.* **3**, 951 (1968).
24. K. A. Gschneidner, *Les Elements des Terres Rares*, Vol. 1, p. 81. Centre National de la Recherche Scientifique, Paris (1970).
25. G. A. Bandurkin and B. F. Dzhurinskii, *Dokl. Chem.* **168**, 618 (1966). *Transl. of Dokl. Akad. Nauk SSSR* **168**, 1315 (1966).
26. W. B. Pearson, *J. Less-Common Metals* **13**, 626 (1967).
27. I. J. McColm, N. J. Clark and B. Mortimer, *J. Inorg. Nucl. Chem.* **33**, 49 (1971).
28. E. Burzo, *J. Less-Common Metals* **23**, 123 (1971).