

Pressure Calibration to 100 kbar Based on the Compression of NaCl*

R. N. JEFFERY,[†] J. D. BARNETT, H. B. VANFLEET, AND H. T. HALL

Departments of Physics and Chemistry, Brigham Young University, Provo, Utah

(Received 21 February 1966)

An independent determination has been made of the transformation pressures assigned to the high-pressure transformations in Ba and Bi which are generally used for calibration points. The metals were imbedded in NaCl, and the transitions were detected by the resistance change of the metal while the NaCl lattice parameter was simultaneously measured by x-ray diffraction. The NaCl compression values determined at the fixed points were related to pressure by reference to the semiempirical compression curve of Decker. The Ba I-II and Bi III-V transformations at room temperature were assigned thermodynamic equilibrium values of 53.3 ± 1.2 kbar and 73.8 ± 1.3 kbar, respectively, corresponding to NaCl linear compression values of $\Delta a/a_0=0.0510$ and 0.0637 , respectively. Hysteresis in the transformation pressures was investigated and sample hysteresis was separated from apparatus hysteresis. The hysteresis measurements imply a stress energy which inhibits nucleation of the new phase and causes a sizable sample hysteresis in solid-media systems.

I. INTRODUCTION

ACCURATE calibration of very high pressure devices has been a major problem since the early days of high-pressure research. In simple piston-cylinder devices, pressure can be calculated from applied force per unit piston area if sufficient corrections are included. In many high-pressure devices, particularly the solid-media systems, such a direct calculation of pressure is not possible, and a calibration must be made by other means. The pressure calibration generally used is based upon the observation of certain "sharp" phase transitions which occur in materials such as Tl, Ba, and Bi.¹ The pressures at which these transitions occur is taken from previous measurements in an apparatus where pressures could be determined. Although no precise, fundamental determination of the points above 50 kbar has been carried out, the fixed-point calibration technique is in widespread use.

Bridgman, in volume displacement² and electrical resistance³ measurements, determined pressures by direct calculation based on force per unit area in two different pressure systems. Although he never intended these measurements to represent precision calibration values, his

observations of phase transitions were used to designate two different pressure scales, the so-called "volume" and "resistance" scales. Bridgman had forced agreement between the two scales below 30 kbar, but rather large discrepancies existed at higher pressures. For example, a volume discontinuity was reported for Ba at 59 kbar, and a resistance discontinuity in Ba was reported at 78 kbar. Kennedy and LaMori⁴ first proposed these two transitions to be the same phase transformation and the correct pressure values to be given by the volume scale. Barnett, Bennion, and Hall⁵ demonstrated experimentally the identity of these two transitions by measuring the volume and resistance of Ba simultaneously, although no pressure calibration was attempted. Kennedy and LaMori⁶ later redetermined the transition pressures of Bi, Tl, and Cs with pressure to 50 kbar. Because of the generally good agreement with Bridgman's volume scale, the latter is currently accepted as the calibration standard with minor corrections from Kennedy and LaMori's work. Errors in the resistance scale are now felt to be due to the unknown pressure distribution in the Bridgman anvil device used in the, resistance measurements. Attempts to check the Ba point at 59 kbar by an independent

* Supported by the U.S. Army Research Office, Durham, North Carolina.

[†] Present address: Physics Department, University of Illinois, Urbana, Illinois

method have not been conclusive, and no attempts at independent pressure determinations in static pressure systems have been made at pressures above 60 kbar. Recent work by Stark and Jura,⁷ Giardini and Samara,⁸ and others indicates serious discrepancies between Bridgman's pressure value of the upper Bi transition and calibration curves based on the Ba point.

Drickamer and co-workers^{9,10} have reported static pressures of several hundred kilobars using supported Bridgman anvils for resistance and x-ray studies. The resistance cell⁹ was calibrated by extrapolating Bridgman's resistance data on Pb, Pt, and In and using the Ba and high Bi transitions (volume scale) as fixed points. The x-ray cell¹⁰ was calibrated by observing the change in lattice parameter of a "marker" of Ag, Rh, or Pd and comparing with compression data obtained in shock measurements. By shock techniques¹¹ dynamic pressures of over a megabar have been obtained where pressures are calculated using the basic conservation laws of mechanics and measuring shock velocities. Apparent support for the accuracy of the Drickamer resistance-cell calibration was found in the observation of a transition in Fe at 133 kbar, corresponding to a shock-induced transformation measured at 131 kbar¹². This apparent agreement is in contradiction to the results obtained in the present work as described below and again raises the fundamental question of equality of static equilibrium, quasihydrostatic pressures in the solid systems, and the unidirectional pressures created in the dynamic shock front. Evidence is accumulating to indicate that the pressure in shock measurements has a much higher shear component than is present in the static systems, and especially in those static systems with a three-dimensional pressure chamber. The amount of shear in the Bridgman anvil device is still undetermined but is undoubtedly much greater than in the three-dimensional high-pressure systems in use.

Due to the inherent pressure limitations of piston-cylinder devices, it is commonly felt that for pressures above 50 kbar a calibration must be obtained by some other technique. We propose the use of a pressure scale based on the atomic separation of a simple substance for which the compression can be theoretically predicted with some degree of certainty. NaCl was chosen for this substance because it is theoretically amenable, experimentally easy to work with, and there is a large amount of accurate data available to support the theory. One advantage of such an

approach, is that the pressure calibration points are tied to a physical parameter independent of any apparatus and, in fact, independent of any theory. We report herein the actual compression values, of NaCl. We then relate these values to the absolute pressure scale by reference to the semiempirical theoretical equation of state for NaCl calculated by Decker.¹³ Should an improved theoretical treatment become available, the measured compression values would yield an improved absolute pressure scale. Decker's equation of state has been solved to yield pressure as a function of lattice parameter and temperature over the range 0-500 kbar and 0°-1500°C. Lattice parameters have been measured at high pressure using the x-ray diffraction tetrahedral press described previously.¹⁴

The use of a lattice parameter as a pressure gauge as discussed herein has several major advantages over the fixed-point technique for use in high-pressure studies. First, it is a single-valued variable with pressure; hence, the pressure may be known for both increasing and decreasing pressure cycles of a particular experiment or after a number of cycles. This makes possible a direct observation of hysteresis. Second, the lattice parameter is a continuous variable with pressure, which allows one to obtain pressure values over an extended range with one calibrant and to measure pressures at any desired working pressure of interest. Third, the calibrant is located within the pressure chamber in intimate contact with the sample. One can thus observe local pressure changes due to effects within the pressure chamber itself, independent of oil pressure. These advantages, shared with the manganin gauge and similar devices, have been taken for granted by workers using hydrostatic liquid systems, but the lack of them has been a serious limitation in high-pressure studies with solid-media environments.

The primary purpose of this paper is to determine the calibration values of the fixed-point calibration transitions, in particular the Ba I-II and the Bi III-V transitions. It has been necessary, however, to discuss hysteresis effects in these transformations since they have a bearing on the interpretation of the results. In addition, the results of this work have value as an important link between theory and experiment for NaCl when correlation of other pressure-calibration techniques at the lower pressures are taken into account.

Much of the inherent advantage of the techniques described herein would be lost if NaCl were itself to exhibit a phase




FIG. 1. Construction of calibration samples showing location of calibrant, NaCl, and x-ray beam.

transformation under high pressure. The transformation previously reported by Evdokimova and Vereshchagin¹⁵ has not been observed in our laboratory using the tetrahedral apparatus, even to pressures of 100 kbar at 25°C for periods up to a week, and at 30 kbar at 600°C for several hours. Other workers in the field have also searched in vain for this transition.¹⁶ It seems probable that if such a transition does exist, it is initiated by shearing forces present in the apparatus. A recent indication of this transformation by shock measurements¹⁷ seems to indicate that this is the case. Since our measurements are based on the x-ray diffraction lines of the low-pressure form, and since we see no indication of the transformation in our apparatus on a microscopic level, we have full confidence in the data reported here.

II. TECHNIQUE

Several inherent features of the tetrahedral x-ray diffraction apparatus make it feasible to evaluate the fixed transition pressures in the manner described herein. First, the pressure resolution is greatly superior to other pressure devices. This resolution is clearly demonstrated in the work on cesium metal by Hall, Merrill, and Barnett¹⁸ wherein the cusp in the resistance-pressure curve of Bridgman near 42 kbar was actually found to be a flat-topped spike only 0.5 kbar wide. This measurement implies that pressure gradients over a sizable volume are much less than 0.5 kbar, a condition highly desirable in a calibration study. Second, the precision of lattice parameter determinations

made using the "B" x-ray geometry of the press¹⁴ is approximately 0.1%. When used in connection with the NaCl compression curve, this represents a pressure difference of less than 1.0 kbar. Third, simultaneous x-ray and electrical resistance measurements can be made, thus allowing the measurement of the NaCl compression coincident with the observation of the resistance transitions in the calibration materials in the same manner as generally used.

The metal calibration specimen was imbedded in NaCl to insure equal pressure in both materials and was placed in such a position that the x-ray beam passed through the NaCl which was in intimate contact with the metal. The x-ray beam itself is approximately 0.020 in. wide. Two geometries used are illustrated in Fig. 1. The sample of Fig. 1 (top) allows for x-ray diffraction patterns to be recorded for both the NaCl and metal specimens simultaneously while the resistance of the metal is being measured. Volume and resistance transitions in the metal are thus measured coincidentally. For the sample of Fig. 1 (bottom) only the NaCl diffraction pattern is recorded, and the transition in the metal is detected by the resistance change alone. The Ba transitions were recorded using both techniques whereas the Bi were recorded using only the latter. As the calibration points were determined, the pressure was increased very slowly as the transition point was approached.

All of the calibration experiments have been conducted using 50-50 wt% boron-plastic tetrahedra described elsewhere.¹⁴ Two different anvil sizes were used depending upon maximum pressures desired. Three-quarter-inch anvils were used with 1-in. tetrahedra for most experiments in the range from 0-50 kbar. For experiments to 100 kbar, a modified anvil was used which was tapered in the normal gasket region such as to produce a wedge-shaped gasket of 8° angle followed by the normal parallel gasket area. The face of the anvil was 5/16 in. along the triangular edge, and the tapered area was 0.150 in. wide. It has been our experience that having the positive-wedge region before the parallel-gasket region results in greater gasket stability at higher pressures.

III. MEASUREMENTS

The major effort of this work was directed toward determining the pressures associated with the Ba I-II and the Bi III-V transformations since these two calibration points are the most widely

Table I. NaCl linear and corresponding pressures from Decker's theory with sample hysteresis and a comparison of previously accepted values for each transition.

Transition	%NaCl compression at transition			Corresponding pressure (kbar)					
	Increas- ing	Decreas- ing	Equi- librium	Increas- ing	Decreas- ing	Hys- teresis	Equi- librium ^b	Bridg- man's volume ^a	Discre- pancy ($P_b - P_{NaCl}$)
Bi I-II (Strip)	2.97±0.07	2.70±0.07	2.84±0.07	26.2±0.8	23.4±0.8	2.8	24.8±0.8	25.4	0.6
Bi I-II (Wire)	2.99±0.12	2.49±0.12	2.74±0.12	26.5±1.3	21.2±1.2	5.3	23.8±1.3	25.4	1.6
Bi II-III(Strip)	3.23±0.07	3.03±0.07	3.13±0.07	29.1±0.8	26.9±0.8	2.2	28.0±0.8	27.0	-1.0
Bi II-III(Wire)	3.28±0.12	2.89±0.12	3.09±0.12	29.7±1.4	25.5±1.3	4.2	27.6±1.4	27.0	-0.6
Tl II-III	3.77±0.17	3.63±0.17	3.70±0.17	35.4±2.1	33.8±2.1	1.6	34.6±2.1	36.7	2.1
Yb I-II	3.99±0.12	1.82±0.12	...	38.2±1.5	14.7±1.1
Ba I-II	5.19±0.06	5.01±0.10	5.10±0.08	54.6±0.9	52.0±1.5	2.6	53.3±1.2	58.8	5.5
Bi III-V	6.49±0.07	6.27±0.07	6.37±0.07	75.7±1.3	71.9±1.3	3.8	73.8±1.3	88	14.2
Sn I-II	7.36±0.15	92.0±3.0	114	22

^a Bi and Tl taken from Ref. 6 and Sm from Ref. 25 in which correlation is made to Bridgman's volume scale.

^b Average of increasing and decreasing transition pressure as "best" estimate of equilibrium value from data. See text for details on Bi.

used, and the higher pressure data are almost completely based upon them. One measurement each was also made on the Tl, Yb and Sn transitions as supporting data. An associated study was also made of the Bi I-II and Bi II-III transitions to determine hysteresis effects and to check on the accuracy of Decker's theory. During many of our high-pressure experiments, x-ray data were taken at regular intervals to determine the efficiency of pressure transmission of the tetrahedral press, the characteristics of the pressure release cycle, and pressure cycling effects. A compilation of the NaCl linear compression data taken at each of the seven transformations studied is given in Table I. The values for Ba and for the three Bi transformations represent the average of several measurements taken on both increasing and decreasing pressure cycles as indicated. Only one measurement was made on each of the other three transformations. The actual NaCl linear compressions are given for future reference, as well as the associated hysteresis intervals and equilibrium pressure values as determined using Decker's theory. All measurements correspond to a temperature of 25°C. The nomenclature for the Bi III-V transition reported at 88 kbar by Bridgman in volume measurements follows that of Klement, Jayaraman, and Kennedy.¹⁹ This transition is commonly known as the "upper bismuth" transition and is clearly the "VI-VIII" transition reported by Bundy²⁰ at 122.5 kbar on the resistance scale.

Due to the magnitude of the sample hysteresis effects measured in this work, an understanding of the hysteresis phenomena becomes important in relationship to calibration

of high-pressure systems by the fixed-point method since sizable errors can result even when one has a calibrant within the pressure chamber and measurements are being made near one of the calibration points. The error intervals associated with the NaCl lattice compressions in Table I arise from two sources: (a) the variation of lattice parameter as determined by various lines in the x-ray pattern and (b) the variation of the determined parameter from experiment to experiment. For Ba and Bi, different orientations and configurations were used to demonstrate any systematic errors, but these variations were of the same order as the experiment to experiment variations and are thus included in (b) above. Since each diffraction line determines a lattice parameter with compound errors associated with both sources above, the error interval was evaluated by assuming the error in each lattice parameter obtained from each diffraction line of all patterns at a given transformation was Gaussian. An estimate was made of the standard deviation or for this statistical error by analyzing the Bi III-IV and Ba I-II data in which several independent experiments were made each involving several x-ray lines. The error interval given in Table I is $2s_n$, where $s_n = s/\sqrt{n}$ is the estimated standard deviation of the mean of n measurements. Error intervals in pressure values were taken from corresponding errors in NaCl compressions using Decker's theory. The decrease in compressibility at higher pressures thus yields higher pressure error intervals at the higher pressure points. If absolute pressures are desired, an allowance reflecting the reliability of the theory must also be made in addition to the experimental errors given here.




FIG. 2. Apparatus load vs pressure curves for the two different anvil sizes for both increasing and decreasing pressures. The separation of apparatus hysteresis from sample hysteresis in the Yb I-II and in the three Bi transitions is clearly evident.

A. Apparatus Calibration

A typical calibration curve for a solid-media high pressure apparatus gives sample pressure as a function of ram load or hydraulic oil pressure. Calibration curves for the tetrahedral apparatus with $\frac{3}{4}$ in. anvils and the modified $\frac{5}{16}$ in. anvils discussed above are shown in Fig. 2. The lower and upper curves, corresponding to the $\frac{3}{4}$ in. and $\frac{5}{16}$ in. anvils, respectively, were obtained during calibration experiments on Yb and Bi. The points at which the transitions occurred are indicated, both on the increasing and decreasing cycles, and the effect of pressure cycling around the upper Bi transition is also indicated. The anomalous curvature at very low pressures for the $\frac{3}{4}$ in. anvils and the decreasing efficiency at higher pressures, especially for the $\frac{5}{16}$ in. anvils, are clearly revealed. The loss of efficiency at higher pressures which has often been discussed qualitatively by various workers is in direct contrast to the linear calibration curves often assumed, and implies that at the higher pressures, previously reported values have been overestimated. Apparatus hysteresis due to gasket friction is clearly shown in Fig. 2 by the displacement of the calibration curve to the left on the decreasing pressure cycle. Sample hysteresis in the Yb and three Bi transformations

is also illustrated on the graph by the vertical displacement of the transition point between the increasing and decreasing cycles. This clearly shows the separation of the apparatus hysteresis from sample hysteresis, and in the case of Yb defines the region of metastability. This same measurement was made on each of the transitions studied, and a measurable amount of sample hysteresis has been exhibited in each case, although none is as dramatic as Yb. Such measurements have not previously been possible in solid pressure systems. The curve for the $\frac{3}{4}$ in. anvils shown in Fig. 2 is reproducible in actual pressure values at a given load within 2 kbar on the increasing pressure cycle, but the curve for the $\frac{5}{16}$ in. modified anvils is only representative, since pressures at a given load are not as consistent with the smaller anvils. Apparently the calibration curve depends rather critically on the initial size of the tetrahedron used, and adequate control has not been exercised in this regard. The use of a calibration curve without reference to an internal calibrant is not as meaningful for the small anvil design as with the standard size tetrahedron.

B. Hysteresis Phenomena

In the initial measurement on the Bi I-II transitions made to establish confidence in the technique and the theory, sizable sample hysteresis was observed even though the average of the up and down cycle pressure determinations agreed well with the accepted equilibrium value for the transformation. Further work indicated a larger amount of hysteresis for cylindrical wire samples than for flat strip samples of Bi when imbedded in NaCl. The transitions are also "sharper" for strips than for wires when imbedded in NaCl. Under liquid hydrostatic conditions, Bridgman²¹ measured a "region of indifference" of from 60 to 100 bars necessary to cause the transition to "run" in the two opposite directions starting from an equilibrium point where a portion of the sample was already transformed. Davidson and Lee,²² also using a hydrostatic system, have measured the sample hysteresis in the conventional manner in which the pressure at the initiation of the transformation on the up and down cycle was measured. They reported hysteresis of from 0.55 to 0.90 kbar, which is approximately ten times the region of indifference reported by Bridgman. With the Bi sample surrounded by NaCl, an average hysteresis of 5.3 kbar for a cylindrical wire 0.010 in. in diameter and 2.8

kbar for a 0.002-in. thick flat strip was observed where pressures were measured at the initiation of the transformation. The best explanation of the sample hysteresis measured in this investigation, and also by Davidson is found in the nucleation process of the new phase, which would not be of importance in Bridgman's measurement of the "region of indifference" since large amounts of both phases were simultaneously present.

The thermodynamic equilibrium transformation pressure is defined by the equality of the Gibbs free energy for the two phases. If one approaches the equilibrium pressure from phase I, for example, there will exist with increasing probability statistically created nuclei of phase II having some probability distribution with respect to size. When the equilibrium pressure is reached, since the Gibbs free energy in the two phases is equal, the transformation will take place only if the nuclei surface energies are less than or equal to zero so that nuclei growth would result in a lower energy state for the system. In real solids one would expect the nucleus surface energy, which is nothing more than the microscopic strain energy of a nucleus of phase II in a matrix of phase I, to be positive with the result that there is no nuclei growth; hence, the transformation does not occur. In fact it can be easily shown that the condition for nuclei growth is that the pressure must be increased above the equilibrium pressure by an amount ΔP_{I-II} such that $G_I(P) - G_{II}(P) > 2\alpha V_0 \mathbf{s} / R$, where $G_I(P)$ and $G_{II}(P)$ are the Gibbs functions per atom at a pressure P for the phases I and II, \mathbf{s} is the energy per unit surface, α is a factor of order unity which depends on the geometry of the nuclei, V_0 is the atomic volume, and R is a characteristic dimension of the nuclei. It should be pointed out that this surface energy will vary with (a) the size and shape of the nuclei, (b) the elastic properties and configuration of the surrounding media, (c) the crystal structure and crystalline orientation of the nucleus and its surrounding media, and (d) particularly the volume change associated with the transformation.

It is now easy to understand Bridgman's small "region of indifference" with half of the sample being in phase I and half in phase II, R is very large and hence a very small ΔP_{I-II} and ΔP_{II-I} will satisfy the growth inequality for either direction. However, if one is relying on statistically created nuclei where the nuclei have at least a dimension large enough to define a new phase, a hysteresis

of $\Delta P_{I-II} + \Delta P_{II-I}$ characteristic of the nuclei involved will be observed. It should be pointed out that the size distribution of these statistically created nuclei may depend on the purity and shear strain within the sample, and in some instances the probability of creating a minimum nucleus may increase in a strained system. There exists, in addition to the above phenomena, an effect due to pressure gradients that may be produced in solid pressure-transmitting media as a result of the phase transformation itself. If phase II has a smaller volume than phase I and the system is surrounded by a nonhydrostatic solid pressure-transmitting medium, the net result will be that the pressure relative to the bulk material will decrease at the nuclei by δP_{I-II} on the forward transition and increase by δP_{II-I} on the reverse transition by an amount characteristic of the critical nucleus size. The measured sample hysteresis in this case will be the sum $\Delta P_{I-II} + \delta P_{I-II} + \Delta P_{II-I} + \delta P_{II-I}$.

One must clearly distinguish between the strain energy associated with the nucleation center, as discussed above, and any gross strains or pressure gradients inherent in the apparatus. It must be remembered that the discussion above relates to the balance between growth and decay of nucleation centers, and that at the initiation of the transformation the size of these nuclei are still very small, containing at most a few hundred atoms.²³ After initiation, the transformation will continue to progress until the pressure within the calibrant and environment decreases because of volume contraction to the point where the growth criterion is violated and then will cease. In order to cause further progress of the transformation in a solid system, one must increase the ram load continuously to cause the transformation to complete. In a good configuration with Bi (for example) surrounded by AgCl, over half the resistance transition will usually take place following the initiation. The latter "sluggishness" which exists after stabilization following the initiation is well known to workers in the field, and is caused, we propose, by the pressure gradients mentioned.

The existence of the sizable hysteresis in the Bi I-II transformation when measured in a liquid hydrostatic system as reported by Davidson and Lee indicates that the nucleation centers are statistically formed at points within the bulk region of the sample rather than on the surface since any strain energy for a nucleation center on the surface would be relieved by the hydrostatic liquid pressure. Furthermore, since they reported no essential difference between polycrystalline

samples and single-crystal samples, one can infer that the nucleation centers are not associated with grain boundaries but rather with lattice vibrations, dislocations, or other crystal defects within the crystal proper.

One would expect a significant increase in the microscopic strain energy discussed above and thus a change in the hysteresis accompanying the transformation when one includes the strain in the environmental media due to nonhydrostatic conditions inherent in the apparatus. This nucleation phenomenon also explains the smaller hysteresis measured using a flat, metal calibration strip rather than a cylindrical wire since the more favorable configuration would result in reduced pressure gradients around the sample. Although only in the case of Bi do we have hydrostatic data to support the above interpretation in hysteresis effects, we assume the same basic phenomena are involved in the other transformations reported herein. The Yb transition exhibits, in addition, a rather large distinctive metastability which might well be due to other phenomena. Since the primary objective of this work was the calibration of the fixed points, thin-strip calibrant specimens were used for all higher pressure calibration studies in order to reduce the hysteresis effects.

The equilibrium values of the transformations were taken as the average of the increasing and decreasing pressure cycle transitions, since there is no way with the present data to ascertain with any certainty in which direction the nucleation energy might be the largest. There is no reason, however, to expect the overpressure in the up cycle and the underpressure in the down cycle to be equal. A slight indication of differing energies in the Bi I-II and Bi II-I transformations can be obtained by noting that the average transition values obtained for the wire calibrant is lower than for the strip calibrant. If one assumes the ratio of the amount of overpressure in the Bi I-II transition to the amount of underpressure in the Bi II-I transition is the same for the above situations, the measured average values can be explained by letting this ratio be less than one. This interpretation would mean the nucleation energy in the Bi I-II transformation is less than in the reverse Bi II-I transformation.

A second minor point of interest arises due to the small pressure interval between the Bi I-II and Bi II-III transformations, which implies the nucleation for the Bi II-III transformation - probably takes place in an environment which is

still under gross strain resulting from the Bi I-II transformation. Similarly, on the pressure decrease cycle the Bi II-I transformation is affected by the Bi III-II transformation. Since strain energy varies as the square of the strain, this would tend to place the Bi II-III transition average higher than its equilibrium value and the Bi I-II average lower. A perusal of the literature in which both the Bi I-II and Bi II-III transitions are shown on a calibration curve indicates a consistent and significantly larger pressure interval between these two transitions when measured in a solid medium compared to measurements in a hydrostatic medium, a result consistent with the above reasoning. It should be emphasized that the differences implied here are not measurement errors; rather, the initiation of the transformation actually takes place at pressures different from the equilibrium pressures, and the error is in assigning the equilibrium values to the pressure at the transition point. The implications of this are discussed later.

C. Higher-Pressure Transformations

The thermodynamic equilibrium pressure value of 24 ± 0.8 kbar (see Table I) obtained for the Bi I-II transformation is in good agreement with the accepted value as determined by more precise techniques in hydrostatic systems. In the light of the discussion in the previous section, the slightly lower value (although within the estimated accuracy) is to be expected. Thus, the Bi I-II transformation results provide good evidence for the feasibility of the calibration technique and also for the accuracy of Decker's theory, at least to 25 kbar, and gives one confidence in the method and theory at higher pressures.

Due to the unexpected low value determined for the Ba I-II transition in early experiments, an extensive program was initiated to eliminate possible systematic errors. The transition was measured three or more times with each of two different sized anvils. The different sized anvils required drastically different load pressures, which one might expect to give systematic errors due to warping of the press and associated x-ray geometry. Two different orientations of the x-ray system relative to the pressure system were used, and both resistance and volume change associated with the transformation were monitored. A comparison of the measured values under any of these differing conditions showed no variation greater than the estimated error

described above. As indicated in Table 1, the Ba I-II transformation was measured at 54.6 ± 0.9 kbar and the Ba II-I at 52.0 ± 1.5 kbar. A hysteresis of more than 2 kbar was observed in each measurement with the indicated error being largely a result of experiment-to-experiment variation. Sample hysteresis was also implied by x-ray measurements of Ba compressions in which the compressions at the Ba II-I were smaller than at the Ba I-II transformation. The resistance of Ba has been measured to 105 kbar as determined by the NaCl scale, but the high Ba transition reported by Balchan and Drickamer⁹ to occur at 144 kbar has not been reached.

The Bi III-V transition was observed to take place at 75.7 ± 1.3 kbar in three separate experiments, and the reverse transition Bi V-III was observed at 71.9 ± 1.3 kbar in three determinations. Due to the consistency of these experiments it was felt that no further data were necessary. Again a sizable sample hysteresis was evident. One experimental determination was also made of the transition pressure in thallium, ytterbium, and tin to see if there was general agreement or if serious discrepancies would arise. The data on these three transitions are not intended to represent precise calibration data, but are given rather to indicate the consistency of the data on the Ba I-II and Bi III-V transformations. Values of 35.4 ± 2.1 kbar and 33.8 ± 2.1 kbar were obtained for the Tl II-III respectively. The decreasing pressure value is rather poorly defined due to a poor-quality x-ray diffraction pattern of NaCl in that particular measurement. The data indicate a rather small hysteresis, however, which is consistent with the small associated volume change. The Yb I-II transitions were carefully measured at the value of 38.2 ± 1.5 kbar and the reverse Yb II-I transitions at 14.7 ± 1.1 kbar. No equilibrium value is recorded for this transformation because of the pronounced metastability. The Sn I-II transformation²⁴ was detected by the structure change in the tin itself, and no resistance measurement was made. Tin powder was intimately mixed with NaCl, and both x-ray patterns were observed simultaneously. A value of 92 ± 3 kbar was obtained for the Sn I-II transformation, but the reverse Sn II-I transformation was not measured. Thus, no hysteresis value was previously reported at 113 to 115 kbar by Stager, Balchan, and Drickamer²⁵ by resistance measurements.

IV. Discussion




FIG. 3. Differences between NaCl pressure scale and Bridgman's volume scale. The volume scale used here includes Sn at 114 kbar, which was not measured by Bridgman but was determined using apparatus calibration curves based on Bridgman's data.

A comparison of the measured transitions pressures reported in this work with the accepted scale from Bridgman's volume scale as corrected by Kennedy and LaMori is given in Table I. The differences are surprisingly large even at the Ba transformation, although at lower pressures agreement is much better. The discrepancy between the two scales is shown in graphical form in Fig. 3 to illustrate the smooth departure of the two scales at the higher pressures. In reality the complete volume scale above 40 kbar is based on the Ba and upper Bi transformations since the Sn transformation was tied to Ba and Bi by Stager, Balchan, and Drickamer.

In the present work as well as in Bridgman's original volume work measurements were made on both the increasing and decreasing pressure cycles, and an equilibrium value estimated for the transformation. Thus, the curve shown in Fig. 3 corresponds only to equilibrium values. For this reason, the Yb point is not used. The Sn point is utilized, however, since the measurement by Stager, Balchan, and Drickamer and the measurement reported here were both increasing pressure measurements. Overpressuring effects would thus tend to compensate.

The discrepancy ($P_B - P_{NaCl}$) is plotted against Bridgman's pressures in Fig. 3 for convenience in using the curve as a correction curve for data previously reported relative to the volume scale. Curiously, a plot of $\log(P_B - P_{NaCl})$ vs $\log(P_{NaCl})$ yields a straight line, implying a power-law relationship. Whether this is coincidental or has significance is not obvious, and we can offer no explanation.

Since generally in solid-media systems one calibrates on the pressure-increase cycle only, a most important result of this work is the elucidation of the effect of nonhydrostatic environment on the transition pressure. Many workers in the field have been assigning

equilibrium pressure values to transitions which have actually taken place at a significantly higher pressure depending on the calibrant environment. If an accurate calibration is to be obtained, some knowledge of the environmental effect must be known. This implies that one does not, in general, know accurately the pressure even if a calibrant is included within the pressure chamber and measurements are made near the transition pressure. It is felt that improved pressure data will result if this problem is understood and some allowance made for it. For standard calibration of solid-media systems we propose the use of flat strip configuration and the use of the transition pressures given in Table I for the pressure increasing cycle rather than the equilibrium pressure value.

Several possible systematic errors which would give rise to the divergence of the higher pressure scales shown in Fig. 3 come to mind.

1) A systematic error exists in our x-ray geometry at the high load. As mentioned above the use of both small and large tetrahedra sample chambers should have demonstrated the existence of such an error. Furthermore, the sign of the discrepancy observed would indicate that our measured compressions are too small, whereas compression data on Ba⁵ and Cs¹⁸ measured with our apparatus have yielded compressions slightly larger than those reported by Bridgman. In fact, in two experiments simultaneous compression values of Ba and NaCl were measured.

2) The theory used to determine pressures from compressibility data could be in error at the higher pressures. Decker claims an expected pressure accuracy of 2%-3%. His estimate is based on agreement with shock data at very high pressures where such data are generally thought to be more accurate, Bridgman's own NaCl volume data, and the lack of variation due to changing parameters in the theory. Further confirmation of Decker's theory is found by comparing the theory with recent data by Perez-Albuerne and Drickamer²⁶ in which the theory fits the data better than the empirical equation used by the authors. Decker's theory also gives a better fit to the shock data of Christian,²⁷ exhibited for comparison by Perez-Albuerne and Drickamer. Since the theory agrees with Bridgman's NaCl compression values, the present work demonstrates that Bridgman's volume pressures are not consistent but depend upon sample material. One must thus choose to calibrate on Bridgman's NaCl data or his Ba and Bi data where the discrepancies are

approximately as shown in Fig. 3. In the absence of a good reason to select one set of Bridgman's data and reject the other, we feel it only consistent to base a calibration on a theoretical curve and thus be completely independent of Bridgman's data. The correlation of Decker's theory with the Bi I-II transition and Christian's shock data does however indicate Bridgman's NaCl compressibility data is more reliable than his corresponding Ba and Bi data.

(3) The third possible explanation of the divergence illustrated in Fig. 3 is that in Bridgman's system an unknown and differing percentage of the load at higher pressures was taken up with friction in measurement of each different sample material. The existence of errors in the correction made to Bridgman's raw data is not at all unlikely. Bridgman himself did not hesitate to correct previous data in light of new measurements in order to obtain consistency. We propose this is necessary at this time. It should be noted that Bridgman never intended these volume measurements to be used for calibration points when the measurements were made. Even a casual reading of his original paper indicates that this was the case. If he had so intended, he would have expended much more effort as he did for the Bi I-II transformation.

Recent results of other workers have also given indications of inconsistencies in the high-pressure range. Klement, Jayaraman, and Kennedy¹⁹ in a phase diagram of Bi to 70 kbar found indications that the Bi III-V phase line extrapolates to room temperature at about 78 to 82 kbar. Stark and Jura⁷ and Giardini⁸ have also found indications that Bi III-V transition takes place at pressures much lower than 88 kbar. Since these determinations were themselves based upon the Ba point at 59 kbar, a lowering of this point will reduce the Bi point even further.

V. CONCLUSIONS

Due to the inconsistencies in Bridgman's volume data above 40 kbar, we conclude that it is not meaningful to utilize any of his data as calibration points since they were not so intended. Because of the inherent pressure limitations of the piston-cylinder type apparatus and the excessive correction terms involved at the higher pressures, we conclude that a pressure scale must be defined in some manner independent of a given apparatus. We propose an NaCl pressure scale based upon, the linear compression of NaCl in which pressure is defined by a theoretically predicted equation of

state, and we accept Decker's equation as the best available equation evaluated in the pressure region of interest. We propose that where possible, other transitions be related to the compression of NaCl and that the compression values themselves be reported in the literature, thus tying to a substance rather than a particular theory. We report our determinations of the Ba I-II and Bi III-V equilibrium transformation pressures at 53.3 kbar and 73.8 kbar as the initial secondary calibration points on such a scale to be improved upon as improvement in technique arises. Data given for Tl, Yb, and Sn are not so intended. In light of the increasing divergence of the previously accepted scale at higher pressures, we propose an examination of pressure calibration points above 100 kbar along the lines followed here. We further conclude that transition pressures as typically measured in solid-media apparatus are not equilibrium pressures and that measurable and significant errors result if they are thus assumed. The existence of hysteresis effects in the sample itself due to its environment as measured by the initiation of the transformation in the increasing and decreasing pressure cycles has been demonstrated for all transformations studied.

ACKNOWLEDGMENTS

We wish to thank Dr. Daniel L. Decker for kindly making available the numerical results of his equation of state for NaCl used in this work and for his interest and encouragement. We also thank Vern Bean and Roy Bennion for assistance in the experimentation.

¹ F.P. Bundy, in *Modern Very High Pressure Techniques*, R.H. Wentorf, Jr., Ed. (Butterworth Scientific Publications, Washington, D.C. 1962) pp. 18-21.

² P.W. Bridgman, Proc. Am. Acad. Arts Sci. **74**, 425 (1942), and Phys. Rev. **60**, 351 (1941).

³ P.W. Bridgman, Proc. Am. Acad. Arts Sci. **81**, 167 (1952).

⁴ G.C. Kennedy and P.N. LaMori, in *Progress in Very High Pressure Research*, F. Bundy, W. Hibbard, and H. Strong, Eds. (John Wiley & Sons, New York, 1961), pp. 304-314.

⁵ J.D. Barnett, R.B. Bennion, and H.T. Hall, Science **141**, 534 (1963).

⁶ G.C. Kennedy and P.N. LaMori, J. Geophys. Res. **67**, 851 (1962)

⁷ W. Stark and G. Jura, ASME paper 64-Wa/Pt-28, presented at winter meeting 1-3 December 1964, New York

⁸ A.A. Giardini and G.A. Samara, J. Phys. Chem. Solids **26**, 1523 (1965)

⁹ A.S. Balchan and H.G. Drickamer, Rev. Sci. Instr. **32**, 308 (1961).

¹⁰ E.A. Perez-Albuerna, K.F. Forsgren, and H.G. Drickamer, Rev. Sci. Instr. **35**, 29, (1964)

¹¹ G.E. Duvall and G.R. Fowles, *High Pressure Physics and Chemistry* (Academic Press Inc., New York, 1963), Vol. II, pp. 209-291.

¹² D. Bancroft, E. L. Peterson, and S. Minshall, J. Appl. Phys. **27**, 291 (1956)

¹³ D.L. Decker, J. Appl. Phys. **36**, 157 (1965).

¹⁴ J.D. Barnett and H.T. Hall, Rev. Sci. Instr. **35**, 175 (1964).

¹⁵ V. V. Evdokimova and L. F. Vereshchagin, Soviet Phys.-JETP **16**, 855 (1963).

¹⁶ J. C. Jamieson, in *Physics of Solids at High Pressure*, C. T. Tomizuka, and R. M. Emrick, Eds. (Academic Press Inc., New York, 1965), pp. 444-459.

¹⁷ D. B. Larson et al., J. Phys. Chem. Solids **27**, 476 (1966)

¹⁸ H. T. Hall, L. Merrill, and J. D. Barnett, Science **146**, 1297 (1964).

¹⁹ W. Klement, Jr., A. Jayaraman, -and G. C. Kennedy, Phys. Rev. **131**, 632 (1963).

²⁰ F. P. Bundy, Phys. Rev. **110**, 314 (1958).

²¹ P. W. Bridgman, Proc. Am. Acad. Arts Sci. **74**, 1 (1940).

²² T. E. Davidson and A.P. Lee, Trans. Met. Soc. AIME, **230**, 1035 (1964).

²³ R. Smoluchowski, *Phase Transformations in Solids* (John Wiley & Sons, Inc., New York, 1951), pp. 149-182.

²⁴ J. D. Barnett, V. E. Bean, and H. T. Hall, J. Appl. Phys. **37**, 875 (1966).

²⁵ R. A. Stager, A. S. Balchan, and H. G. Drickamer, J. Chem. Phys. **37**, 1154 (1962).

²⁶ E. A. Perez-Albuerna and H. G. Drickamer, J. Chem. Phys. **43**, 1381 (1965).

²⁷ R. H. Christian, "The Equation of State of the Alkali Halides at High Pressures," Report UCRL-4900, University of California, Lawrence Radiation Laboratory, 1957.